

TITLE

OLEFIN POLYMERIZATION CATALYSTS, TRANSITION METAL  
COMPOUNDS, PROCESSES FOR OLEFIN POLYMERIZATION,  
AND  $\alpha$ -OLEFIN/CONJUGATED DIENE COPOLYMERS

5

FIELD OF THE INVENTION

The present invention relates to novel olefin  
polymerization catalysts, transition metal compounds and  
processes for olefin polymerization using the olefin  
polymerization catalysts.

The present invention also relates to  $\alpha$ -  
olefin/conjugated diene copolymers which have narrow  
molecular weight distribution and are favorably used as  
rubbers.

15

BACKGROUND OF THE INVENTION

As olefin polymerization catalysts, "Kaminsky  
catalysts" are well known. The Kaminsky catalysts have  
extremely high polymerization activities, and by the use  
of them, polymers of narrow molecular weight  
distribution can be obtained. Transition metal  
compounds which are known as those employable for the  
Kaminsky catalysts are, for example,  
bis(cyclopentadienyl)zirconium dichloride (see: Japanese  
Patent Laid-Open Publication No. 19309/1083) and

ethylenebis(4,5,6,7-tetrahydroindenyl)zirconium  
dichloride (see: Japanese Patent Laid-Open Publication  
No. 130314/1086). It is also known that the olefin  
polymerization activities or the properties of the  
5 resulting polyolefins greatly vary when different  
transition metal compounds are used in the  
polymerization. Further, transition metal compounds  
having a ligand of diimine structure have been recently  
proposed as novel olefin polymerization catalysts (see:  
10 International Patent Publication No. 9623010).

By the way, polyolefins generally have excellent  
mechanical properties, and therefore they are used in  
many fields such as fields of various molded products.  
However, with variation of requirements for the  
15 polyolefins, polyolefins of various properties have been  
desired in recent years. Moreover, increase of  
productivity has been also desired.

Under such circumstances as mentioned above, there  
has been desired development of olefin polymerization  
20 catalysts having excellent olefin polymerization  
activities and capable of producing polyolefins of  
excellent properties.

It is well known that copolymerization of several  
kinds of  $\alpha$ -olefins and non-conjugated dienes proceeds  
25 when Ziegler-Natta polymerization catalysts are used.

09942706-083401

Since the copolymers thus obtained are useful as rubbers, copolymers of various types have been produced. However, the non-conjugated dienes used in the copolymerization are generally expensive and have low reactivity. Therefore, diene components which are inexpensive and have high reactivity are desired.

Examples of such diene components include conjugated dienes such as 1,3-butadiene and isoprene. Though these conjugated dienes are more inexpensive and have higher reactivity as compared with the conventional non-conjugated dienes, they have problem such that the activities are markedly lowered or only ununiform copolymers of wide composition distribution or wide molecular weight distribution are obtained if the copolymerization is conducted by the use of the conventional Ziegler-Natta polymerization catalysts. In case of a Ziegler-Natta catalyst system using a vanadium compound, the polymerization activities are extremely low, though relatively uniform copolymers are obtainable. In the circumstances, copolymerization of ethylene and butadiene using metallocene catalysts which have been studied extensively and thus known to exhibit high polymerization activities has been investigated (National Publication of International Patent No. 501633/1989).

00942706.003101

In the above case, however, it has been reported that from the diene unit and ethylene incorporated into the polymeric form together cyclopentane skeleton in the polymer chain, and that the proportion of the cyclopentane skeleton becomes not less than 50 % of all the diene units. The conversion of double bonds of the diene unit into the cyclopentane skeleton is very disadvantageous in the procedure of "vulcanization" required to use the copolymers as rubbers. Further, the cyclopentane skeleton is an unfavorable skeleton because it functions to increase glass transition temperature of the copolymers and is detrimental to the low-temperature properties of the rubbers.

Under these circumstances, as mentioned above, there has been eagerly desired development of copolymers of  $\alpha$ -olefins and conjugated dienes, which have narrow molecular weight distribution and uniform composition and contain almost no cyclopentane skeleton in their polymer chains.

#### OBJECT OF THE INVENTION

It is an object of the present invention to provide an olefin polymerization catalyst having excellent olefin polymerization activities.



It is another object of the invention to provide a novel transition metal compound useful for such catalyst.

It is a further object of the invention to provide  
5 a process for olefin polymerization using the catalyst.

It is a still further object of the invention to provide an  $\alpha$ -olefin/conjugated diene copolymer having a narrow molecular weight distribution and containing almost no cyclopentane skeleton in its polymer chain.

10

#### SUMMARY OF THE INVENTION

The first olefin polymerization catalyst according to the present invention comprises:

(A) a transition metal compound represented by the  
15 following formula (I), and


(B) at least one compound selected from:

(B-1) an organometallic compound,

(B-2) an organoaluminum oxy-compound, and

(B-3) a compound which reacts with the  
20 transition metal compound (A) to form an ion pair:

09942706-083101



wherein M is a transition metal atom of Group 3 to Group 11 of the periodic table,

m is an integer of 1 to 6,

$R^1$  to  $R^6$  may be the same or different, and are each a hydrogen atom, a halogen atom, a hydrocarbon group, a heterocyclic compound residue, an oxygen-containing group, a nitrogen-containing group, a boron-containing group, a sulfur-containing group, a phosphorus-containing group, a silicon-containing group, a germanium-containing group or a tin-containing group, and two or more of them may be bonded to each other to form a ring,

when m is 2 or greater, two of the groups  $R^1$  to  $R^6$  may be bonded to each other, with the proviso that the groups  $R^1$  are not bonded to each other,


n is a number satisfying a valence of M, and

X is a hydrogen atom, a halogen atom, a hydrocarbon group, an oxygen-containing group, a sulfur-containing

group, a nitrogen-containing group, a boron-containing group, an aluminum-containing group, a phosphorus-containing group, a halogen-containing group, a heterocyclic compound residue, a silicon-containing group, a germanium-containing group or a tin-containing group, and when n is 2 or greater, plural groups X may be the same or different and may be bonded to each other to form a ring.

In the present invention, R<sup>6</sup> in the formula (I) is preferably a halogen atom, a hydrocarbon group, a heterocyclic compound residue, an oxygen-containing group, a nitrogen-containing group, a boron-containing group, a sulfur-containing group, a phosphorus-containing group, a silicon-containing group, a germanium-containing group or a tin-containing group.

In the present invention, the transition metal compound represented by the formula (I) is preferably a transition metal compound represented by the following formula (I-a):



(I-a)

wherein M is a transition metal atom of Group 3 to Group 11 of the periodic table,

m is an integer of 1 to 3,

- 5         $R^1$  to  $R^6$  may be the same or different, and are each a hydrogen atom, a halogen atom, a hydrocarbon group, a heterocyclic compound residue, a hydrocarbon-substituted silyl group, a hydrocarbon-substituted siloxy group, an alkoxy group, an alkylthio group, an aryloxy group, an
- 10        arylthio group, an acyl group, an ester group, a thioester group, an amido group, an imido group, an amino group, an imino group, a sulfonester group, a sulfonamido group, a cyano group, a nitro group, a carboxyl group, a sulfo group, a mercapto group or a
- 15        hydroxyl group, and two or more of them may be bonded to each other to form a ring,

when m is 2 or greater, two of the groups  $R^1$  to  $R^6$  may be bonded to each other, with the proviso that the groups  $R^1$  are not bonded to each other,

- 20        n is a number satisfying a valence of M, and


X is a hydrogen atom, a halogen atom, a hydrocarbon group, an oxygen-containing group, a sulfur-containing group, a nitrogen-containing group, a boron-containing group, an aluminum-containing group, a phosphorus-

25        containing group, a halogen-containing group, a

heterocyclic compound residue, a silicon-containing group, a germanium-containing group or a tin-containing group, and when n is 2 or greater, plural groups X may be the same or different and may be bonded to each other to form a ring.

In the above formula (I-a), R<sup>6</sup> is preferably a halogen atom, a hydrocarbon group, a heterocyclic compound residue, a hydrocarbon-substituted silyl group, a hydrocarbon-substituted siloxy group, an alkoxy group, an alkylthio group, an aryloxy group, a arylthio group, an acyl group, an ester group, a thioester group, an amido group, an imido group, an amino group, an imino group, a sulfonester group, a sulfonamido group, a cyano group, a nitro group, a carboxyl group, a sulfo group, a mercapto group or a hydroxyl group.

Further, the transition metal compound represented by the formula (I) is preferably a transition metal compound represented by the following formula (I-a-1):



(I-a-1)

wherein M is a transition metal atom of Group 3 to Group 11 of the periodic table,

m is an integer of 1 to 3,

R<sup>1</sup> to R<sup>6</sup> may be the same or different, and are each  
5 a hydrogen atom, a halogen atom, a hydrocarbon group, a heterocyclic compound residue, a hydrocarbon-substituted silyl group, a hydrocarbon-substituted siloxy group, an alkoxy group, an alkylthio group, an aryloxy group, an arylthio group, an acyl group, an ester group, a  
10 thioester group, an amido group, an imido group, an amino group, an imino group, a sulfonester group, a sulfonamido group, a cyano group, a nitro group or a hydroxyl group, and two or more of them may be bonded to each other to form a ring,


15 when m is 2 or greater, two of the groups R<sup>1</sup> to R<sup>6</sup> may be bonded to each other, with the proviso that the groups R<sup>1</sup> are not bonded to each other,

n is a member satisfying a valence of M, and

X is a hydrogen atom, a halogen atom, a hydrocarbon  
20 group of 1 to 20 carbon atoms, a halogenated hydrocarbon group of 1 to 20 carbon atoms, an oxygen-containing group, a sulfur-containing group or a silicon-containing group, and when n is 2 or greater, plural groups X may  
25 be the same or different and may be bonded to each other to form a ring.

In the formula (I-a-1),  $R^6$  is preferably a halogen atom, a hydrocarbon group, a heterocyclic compound residue, a hydrocarbon-substituted silyl group, a hydrocarbon-substituted siloxy group, an alkoxy group, an alkylthio group, an aryloxy group, an arylthio group, an acyl group, an ester group, a thioester group, an amido group, an imido group, an amino group, an imino group, a sulfonester group, a sulfonamido group, a cyano group, a nitro group or a hydroxyl group.

In the present invention, further, the transition metal compound represented by the formula (I) is preferably a transition metal compound represented by the following formula (I-b):



wherein M is a transition metal atom of Group 3 to Group 11 of the periodic table,

m is an integer of 1 to 6,

$R^1$  to  $R^6$  may be the same or different, and are each a hydrogen atom, a halogen atom, a hydrocarbon group, a

hydrocarbon-substituted silyl group, an alkoxy group, an aryloxy group, an ester group, an amido group, an amino group, a sulfonamido group, a cyano group or a nitro group, and two or more of them may be bonded to each other to form a ring, and

when  $m$  is 2 or greater, two of the groups  $R^1$  to  $R^6$  may be bonded to each other, with the proviso that the groups  $R^1$  are not bonded to each other.

In the formula (I-b),  $R^6$  is preferably a halogen atom, a hydrocarbon group, a hydrocarbon-substituted silyl group, an alkoxy group, an aryloxy group, an ester group, an amido group, an amino group, a sulfonamido group, a cyano group or a nitro group.

It is preferred that  $M$  in the transition metal compound (A) is at least one transition metal atom selected from Groups 3 to 5 and Group 9 of the periodic table.

The first olefin polymerization catalyst according to the invention may further comprise a carrier (C), in addition to the transition metal compound (A) and at least one compound (B) selected from the organometallic compound (B-1), the organoaluminum oxy-compound (B-2) and the compound (B-3) which reacts with the transition metal compound (A) to form an ion pair.




The first process for olefin polymerization according to the present invention comprises polymerizing or copolymerizing an olefin in the presence of the above-mentioned olefin polymerization catalyst.

5 The second olefin polymerization catalyst according to the present invention comprises:

(A') a transition metal compound represented by the following formula (II), and

(B) at least one compound selected from:

- 10 (B-1) an organometallic compound,  
 (B-2) an organoaluminum oxy-compound, and  
 (B-3) a compound which reacts with the transition metal compound (A') to form an ion pair.



wherein M is a transition metal atom of Group 3 to Group 11 of the periodic table,

20 R<sup>1</sup> to R<sup>10</sup> may be the same or different, and are each a hydrogen atom, a halogen atom, a hydrocarbon group, a heterocyclic compound residue, an oxygen-containing group, a nitrogen-containing group, a boron-containing

group, a sulfur-containing group, a phosphorus-containing group, a silicon-containing group, a germanium-containing group or a tin-containing group, and two or more of them may be bonded to each other to  
5 form a ring,

n is a number satisfying a valence of M,


X is a hydrogen atom, a halogen atom, a hydrocarbon group, an oxygen-containing group, a sulfur-containing group, a nitrogen-containing group, a boron-containing  
10 group, an aluminum-containing group, a phosphorus-containing group, a halogen-containing group, a heterocyclic compound residue, a silicon-containing group, a germanium-containing group or a tin-containing group, and when n is 2 or greater, plural groups X may  
15 be the same or different and may be bonded to each other to form a ring, and

Y is a divalent bonding group containing at least one element selected from the group consisting of oxygen, sulfur, carbon, nitrogen, phosphorus, silicon,  
20 selenium, tin and boron, and when it is a hydrocarbon group, the hydrocarbon group has 3 or more carbon atoms.

In the above formula (II), at least one of  $R^6$  and  $R^{10}$  is preferably a halogen atom, a hydrocarbon group, a heterocyclic compound residue, an oxygen-containing  
25 group, a nitrogen-containing group, a boron-containing

group, a sulfur-containing group, a phosphorus-containing group, a silicon-containing group, a germanium-containing group or a tin-containing group.

The transition metal compound represented by the formula (II) is preferably a transition metal compound represented by the following formula (II-a).



wherein M is a transition metal atom of Group 3 to Group 11 of the periodic table,

$R^1$  to  $R^{10}$  may be the same or different, they are each a hydrogen atom, a halogen atom, a hydrocarbon group, a hydrocarbon-substituted silyl group, an alkoxy group, an aryloxy group, an ester group, an amido group, an amino group, a sulfonamido group, a cyano group or a nitro group, and two or more of them may be bonded to each other to form a ring,

$n$  is a number satisfying a valence of M,

$X$  is a hydrogen atom, a halogen atom, a hydrocarbon group of 1 to 20 carbon atoms, a halogenated hydrocarbon group of 1 to 20 carbon atoms, an oxygen-containing

group, a sulfur-containing group or a silicon-containing group, and when n is 2 or greater, plural groups X may be the same or different and may be bonded to each other to form a ring, and

5        Y is a divalent bonding group containing at least one element selected from the group consisting of oxygen, sulfur, carbon, nitrogen, phosphorus, silicon, selenium, tin and boron, and when it is a hydrocarbon group, the hydrocarbon group has 3 or more carbon atoms.


10        In the above formula (II-a), at least one of  $R^6$  and  $R^{10}$  is preferably a halogen atom, a hydrocarbon group, a hydrocarbon-substituted silyl group, an alkoxy group, an aryloxy group, an ester group, an amido group, an amino group, a sulfonamido group, a cyano group or a nitro  
15        group.

It is preferred that M in the transition metal compound (A') is at least one transition metal atom from Groups 4 and 5 of the periodic table.

The second olefin polymerization catalyst according  
20        to the invention may further comprise a carrier (C), in addition to the transition metal compound (A') and at least one compound (B) selected from the organometallic compound (B-1), the organoaluminum oxy-compound (B-2) and the compound (B-3) which reacts with the transition  
25        metal compound (A') to form an ion pair.

The second process for olefin polymerization comprises polymerizing or copolymerizing an olefin in the presence of the above-mentioned olefin polymerization catalyst.

- 5 The novel transition metal compound according to the present invention is represented by the following formula (III):



10

wherein M is a transition metal atom of Group 4 or Group 5 of the periodic table,

m is an integer of 1 to 3,

- 15  $R^1$  is a hydrocarbon group, a hydrocarbon-substituted silyl group, a hydrocarbon-substituted siloxy group, an alkoxy group, an alkylthio group, an aryloxy group, an arylthio group, an ester group, a thioester group, a sulfonester group or a hydroxyl group,

- 20  $R^2$  to  $R^5$  may be the same or different, and are each a hydrogen atom, a halogen atom, a hydrocarbon group, a

heterocyclic compound residue, a hydrocarbon-substituted silyl group, a hydrocarbon-substituted siloxy group, an alkoxy group, an alkylthio group, an aryloxy group, an arylthio group, an ester group, a thioester group, an  
 5 amido group, an imido group, an amino group, an imino group, a sulfonester group, a sulfonamido group, a cyano group, a nitro group, a carboxyl group, a sulfo group, a mercapto group or a hydroxyl group,

$R^6$  is a halogen atom, a hydrocarbon group, a  
 10 hydrocarbon-substituted silyl group, a hydrocarbon-substituted siloxy group, an alkoxy group, an alkylthio group, an aryloxy group, an arylthio group, an ester group, a thioester group, an amido group, an imido group, an imino group, a sulfonester group, a  
 15 sulfonamido group or a cyano group,

two or more of  $R^1$  to  $R^6$  may be bonded to each other to form a ring,


when  $m$  is 2 or greater, two of the groups  $R^1$  to  $R^6$  may be bonded to each other, with the proviso that the  
 20 groups  $R^1$  are not bonded to each other,

$n$  is a number satisfying a valence of  $M$ , and

$X$  is a halogen atom, a hydrocarbon group, an oxygen-containing group, a sulfur-containing group, a nitrogen-containing group, a boron-containing group, an  
 25 aluminum-containing group, a phosphorus-containing

group, a halogen-containing group, a heterocyclic compound residue, a silicon-containing group, a germanium-containing group or a tin-containing group, and when n is 2 or greater, plural groups X may be the same or different and may be bonded to each other to form a ring.

The above-mentioned transition metal compound is preferably a compound represented by the following formula (III-a):



(III-a)

wherein M is a transition metal atom of Group 4 or Group 5 of the periodic table,

m is an integer of 1 to 3,

R<sup>1</sup> to R<sup>5</sup> may be the same or different, and are each a hydrocarbon group, an alkoxy group or a hydrocarbon-substituted silyl group,

R<sup>6</sup> is a halogen atom, a hydrocarbon group, a hydrocarbon-substituted silyl group, an alkoxy group, an alkylthio group or a cyano group,

when  $m$  is 2 or greater, two groups of the groups  $R^1$  to  $R^6$  may be bonded to each other, with the proviso that  
5 the groups  $R^1$  are not bonded to each other.

X is a halogen atom, a hydrocarbon group, an oxygen-containing group, a sulfur-containing group, a nitrogen-containing group, a halogen-containing group or a silicon-containing group, and when n is 2 or greater, plural groups X may be the same or different and may be bonded to each other to form a ring.

The third olefin polymerization catalyst according  
15 to the present invention comprises:

(B) at least one compound selected from:

The third olefin polymerization catalyst according to the present invention may further comprise a carrier (C) in addition to the transition metal compound (A")



and at least one compound (B) selected from the organometallic compound (B-1), the organoaluminum oxy-compound (B-2) and the compound (B-3) which reacts with the transition metal compound (A") to form an ion pair.

5       The third process for olefin polymerization comprises polymerizing or copolymerizing an olefin in the presence of the above-mentioned olefin polymerization catalyst."

10       The  $\alpha$ -olefin/conjugated diene copolymer according to the present invention is an  $\alpha$ -olefin/conjugated diene copolymer having a molecular weight distribution ( $M_w/M_n$ ) of not more than 3.5, a content of constituent units derived from an  $\alpha$ -olefin in the range of 1 to 99.9 % by mol and a content of constituent units derived from a  
15       conjugated diene in the range of 99 to 0.1 % by mol, in which the polymer chain contains 1,2-cyclopentane skeleton derived from the conjugated diene in an amount of not more than 1 % by mol, and preferably the polymer chain does not substantially contain the 1,2-  
20       cyclopentane skeleton.

In the  $\alpha$ -olefin/conjugated diene copolymer according to the invention, it is preferred that the content of the constituent units derived from the  $\alpha$ -olefin is in the range of 50 to 99.9 % by mol and the

content of the constituent units derived from the conjugated diene is in the range of 50 to 0.1 % by mol.

In the  $\alpha$ -olefin/conjugated diene copolymer according to the invention, it is preferred that the  $\alpha$ -olefin is ethylene and/or propylene and the conjugated diene is butadiene and/or isoprene.

#### BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 shows steps for preparing the first olefin polymerization catalyst according to the invention.

Fig. 2 shows steps for preparing the second olefin polymerization catalyst according to the invention.

Fig. 3 shows the structure of transition metal compound A-1 prepared in Synthesis Example 1, which was determined by X-ray structure analysis.

Fig. 4 shows the structure of transition metal compound B-1 prepared in Synthesis Example 2, which was determined by X-ray crystal structure analysis.

#### DETAILED DESCRIPTION OF THE INVENTION

The olefin polymerization catalyst of the present invention and the process for olefin polymerization using the catalyst are described in detail hereinafter.

The meaning of the term "polymerization" used herein is not limited to "homopolymerization" but may

comprehend "copolymerization". Also, the meaning of the term "polymer" used herein is not limited to "homopolymer" but may comprehend "copolymer".

5                   First olefin polymerization catalyst

The first olefin polymerization catalyst of the invention is formed from:

(A) a transition metal compound represented by the below-described formula (I), and

10           (B) at least one compound selected from:

(B-1) an organometallic compound,

(B-2) an organoaluminum oxy-compound, and


(B-3) a compound which reacts with the transition metal compound (A) to form an ion pair.

15           First, the catalyst components for forming the olefin polymerization catalyst of the invention are described.

(A) Transition metal compound

20           The transition metal compound (A) for use in the invention is a compound represented by the following formula (I).

09442706.083101



In the formula (I), M is a transition metal atom of Group 3 to Group 11 of the periodic table (Group 3 includes lanthanoids), preferably Groups 3 to 9 (Group 3 includes lanthanoids), more preferably Group 3 to Group 5 and Group 9, and particularly preferably Groups 4 or 5. Specific Examples of transition metal atoms M include scandium, titanium, zirconium, hafnium, vanadium, niobium, tantalum, cobalt, rhodium, yttrium, chromium, molybdenum, tungsten, manganese, rhenium, iron and ruthenium. Of these, preferred are scandium, titanium, zirconium, hafnium, vanadium, niobium, tantalum, cobalt and rhodium; more preferred are titanium, zirconium, hafnium, vanadium, niobium, tantalum, cobalt and rhodium; and particularly preferred are titanium, zirconium and hafnium.

m is an integer of 1 to 6, preferably 1 to 4.

R<sup>1</sup> to R<sup>6</sup> may be the same or different, and are each a hydrogen atom, a halogen atom, a hydrocarbon group, a heterocyclic compound residue, an oxygen-containing

group, a nitrogen-containing group, a boron-containing group, a sulfur-containing group, a phosphorus-containing group, a silicon-containing group, a germanium-containing group or a tin-containing group, and two or more of them may be bonded to each other to form a ring,

The halogen atom is fluorine, chlorine, bromine or iodine.

Examples of the hydrocarbon groups include straight-chain or branched alkyl groups of 1 to 30, preferably 1 to 20 carbon atoms, such as methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, neopentyl and n-hexyl;

straight-chain or branched alkenyl groups of 2 to 30, preferably 2 to 20 carbon atoms, such as vinyl, allyl and isopropenyl;

straight-chain or branched alkynyl groups of 2 to 30, preferably 2 to 20 carbon atoms, such as ethynyl and propargyl;

cyclic saturated hydrocarbon groups of 3 to 30, preferably 3 to 20 carbon atoms, such as cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl and adamantyl;

cyclic unsaturated hydrocarbon groups of 5 to 30, preferably 5 to 20 carbon atoms, such as cyclopentadienyl, indenyl and fluorenyl; and

aryl groups of 6 to 30, preferably 6 to 20 carbon atoms, such as phenyl, benzyl, naphthyl, biphenyl and terphenyl.

The hydrocarbon groups may be substituted with  
5 halogen atoms and for such examples halogenated hydrocarbon groups of 1 to 30, preferably 1 to 20 carbon atoms, such as trifluoromethyl, pentafluorophenyl and cholophenyl may be mentioned.

The hydrocarbon groups may also be substituted with  
10 other hydrocarbon groups and for such examples aryl-substituted alkyl groups such as benzyl and cumyl may be mentioned.

Further, the hydrocarbon groups may have heterocyclic compound residues; oxygen-containing groups  
15 such as alkoxy, aryl, ester, ether, acyl, carboxyl, carbonato, hydroxy, peroxy and carboxylic acid anhydride groups; nitrogen-containing groups such as ammonium salts of amino, imino, amide, imide, hydrazino, hydrazono, nitro, nitroso, cyano, isocyano, cyanic acid  
20 ester, amidino and diazo groups; boron-containing groups such as borandiyl, borantriyl and diboranyiyl groups; sulfur-containing groups such as mercapto, thioester, dithioester, alkylthio, arylthio, thioacyl, thioether, thiocyanic acid ester, isothiocyanic acid ester, sulfon  
25 ester, sulfon amide, thiocarboxyl, dithiocarboxyl, sulfo, sulfonyl, sulfinyl and sulfenyl groups; phosphorus-containing groups such as phosphido,

phosphoryl, thiophosphoryl and phosphato groups;  
silicon-containing groups; germanium-containing groups;  
and tin-containing groups.

Of these, particularly preferable are straight-  
5 chain or branched alkyl groups of 1 to 30, preferably 1  
to 20 carbon atoms, such as methyl, ethyl, n-propyl,  
isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl,  
neopentyl and n-hexyl; aryl groups of 6 to 30,  
preferably 6 to 20 carbon atoms, such as phenyl,  
10 naphthyl, biphenyl, terphenyl, phenanthryl and  
anthracenyl; and these aryl groups which are substituted  
with 1 to 5 substituents such as alkyl or arkoxy groups  
of 1 to 30, preferably 1 to 20 carbon atoms, aryl or  
aryloxy groups of 6 to 30, preferably 6 to 20 carbon  
15 atoms.

Examples of nitrogen-containing groups, boron-  
containing groups, sulfur-containing groups and  
phosphorus-containing groups are those exemplified  
above.

20 Examples of the heterocyclic residues include those  
of nitrogen-containing compounds (e.g., pyrrole,  
pyridine, pyrimidine, quinoline and triazine), oxygen-  
containing compounds (e.g., furan and pyran) and sulfur-  
containing compounds (e.g., thiophene), and these  
25 heterocyclic residues, which are substituted with

substituents such as alkyl or alkoxy groups of 1 to 20 carbon atoms.

Examples of the silicon-containing groups include silyl, siloxy, hydrocarbon-substituted silyl groups such as methylsilyl, dimethylsilyl, trimethylsilyl, ethylsilyl, diethylsilyl, triethylsilyl, diphenylmethylsilyl, triphenylsilyl, dimethylphenylsilyl, dimethyl-t-butylsilyl and dimethyl(pentafluorophenyl)silyl, preferably methylsilyl, dimethylsilyl, trimethylsilyl, ethylsilyl, diethylsilyl, triethylsilyl and triphenylsilyl, particularly preferably trimethylsilyl, triethylsilyl, triphenylsilyl and dimethylphenylsilyl, and hydrocarbon-substituted siloxy groups such as trimethylsiloxy.

The germanium-containing groups and the tin-containing groups include the above-mentioned silicon-containing groups in which silicon is replaced by germanium and tin, respectively.

The more specific illustration on the above  $R^1$  to  $R^6$  is given below.

Examples of the alkoxy groups include methoxy, ethoxy, n-propoxy, isopropoxy, n-butoxy, isobutoxy and tert-butoxy.

Examples of the alkylthio groups include methylthio and ethylthio.



Examples of the aryloxy groups include phenoxy, 2,6-dimethylphenoxy and 2,4,6-trimethylphenoxy.

Examples of the arylthio groups include phenylthio, methylphenylthio and naphthylthio.

- 5        Examples of the acyl groups include formyl, acyl, benzoyl, p-chlorobenzoyl and p-methoxybenzoyl.

Examples of the ester groups include acetyloxy, benzoyloxy, methoxycarbonyl, phenoxycarbonyl and p-chlorophenoxycarbonyl.

- 10       Examples of the thioester groups include acetylthio, benzoylthio, methylthiocarbonyl and phenylthiocarbonyl.

Examples of the amido groups include acetamido, N-methylacetamido and N-methylbenzamido.

- 15       Examples of the imido groups include acetimido and benzimido.

Examples of the amino groups include dimethylamino, ethylmethylamino and diphenylamino.

- 20       Examples of the imino groups include methylimino, ethylimino, propylimino, butylimino and phenylimino.

Examples of the sulfonester groups include methylsulfonato, ethylsulfonato and phenylsulfonato.

- 25       Examples of the sulfonamido groups include phenylsulfonamido, N-methylsulfonamido and N-methyl-p-toluenesulfonamido.

R<sup>6</sup> is preferably a substituent other than hydrogen. That is, a hydrogen atom, a halogen atom, a hydrocarbon group, a heterocyclic compound residue, an oxygen-containing group, a nitrogen-containing group, a boron-containing group, a sulfur-containing group, a phosphorus-containing group, a silicon-containing group, a germanium-containing group or a tin-containing group, and two or more of them may be bonded to each other to form a ring. R<sup>6</sup> is particularly preferably a halogen atom, a hydrocarbon group, a heterocyclic compound residual group, a hydrocarbon-substituted silyl group, a hydrocarbon-substituted siloxy group, an alkoxy group, an alkylthio group, an aryloxy group, an arylthio group, an acyl group, an ester group, a thioester group, an amido group, an imido group, an amino group, an imino group, a sulfonester group, a sulfonamido group, a cyano group, a nitro group or a hydroxyl group.

Preferred examples of the hydrocarbon groups available as R<sup>6</sup> include straight-chain or branched alkyl groups of 1 to 30, preferably 1 to 20 carbon atoms, such as methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, neopentyl and n-hexyl; cyclic saturated hydrocarbon groups of 3 to 30, preferably 3 to 20 carbon atoms, such as cyclopropyl, cyclobutanyl, cyclopentanyl, cyclohexyl and adamantyl;

aryl groups of 6 to 30, preferably 6 to 20 carbon atoms, such as phenyl, benzyl, naphthyl, biphenyl and terphenyl; and these groups which are substituted with substituents such as alkyl or alkoxy groups of 1 to 30, preferably 1 to 20 carbon atoms, halogenated alkyl groups of 1 to 30, preferably 1 to 20 carbon atoms, aryl or alkoxy groups of 6 to 30, preferably 6 to 20 carbon atoms, halogen, cyano, nitro and hydroxyl.

Preferred examples of the hydrocarbon-substituted silyl groups as  $R^6$  include methylsilyl, dimethylsilyl, trimethylsilyl, ethylsilyl, diethylsilyl, triethylsilyl, diphenylmethylsilyl, triphenylsilyl, dimethylphenylsilyl, dimethyl-t-butylsilyl and dimethyl(pentafluorophenyl)silyl. Particularly preferable are trimethylsilyl, triphenylsilyl, diphenylmethylsilyl, isophenylsilyl, dimethylphenylsilyl, dimethyl-t-butylsilyl and dimethyl(pentafluorophenyl)silyl.

In the present invention,  $R^6$  is a preferably selected from branched alkyl groups of 3 to 30, preferably 3 to 20 carbon atoms (e.g., isopropyl, isobutyl, sec-butyl and tert-butyl neopentyl), these alkyl groups which are substituted with aryl groups of 6 to 30, preferably 6 to 20 carbon atoms (e.g., cumyl), and cyclic saturated hydrocarbon groups of 3 to 30,

preferably 3 to 20 carbon atoms (e.g., adamantyl, cyclopropyl, cyclobutyl, cyclopentyl and cyclohexyl).

Also, preferable  $R^6$  is an aryl group of 6 to 30, preferably 6 to 20 carbon atoms (e.g., phenyl, naphthyl, fluorenyl, anthranyl or phenanthryl) or a hydrocarbon-substituted silyl group.

Two or more of the groups  $R^1$  to  $R^6$ , preferably adjacent groups, may be bonded to each other to form an aliphatic ring, an aromatic ring or a hydrocarbon ring containing a hetero atom such as a nitrogen atom, and these rings may further have a substituent.

When  $m$  is 2 or greater, two of the groups  $R^1$  to  $R^6$  may be bonded to each other, with the proviso that the groups  $R^1$  are not bonded to each other.  $R^1$ s,  $R^2$ s,  $R^3$ s,  $R^4$ s,  $R^5$ s, or  $R^6$ s may be the same as or different from each other.

$n$  is a number satisfying a valence of  $M$ , specifically an integer of 0 to 5, preferably 1 to 4, more preferably 1 to 3.

$X$  is a hydrogen atom, a halogen atom, a hydrocarbon group, an oxygen-containing group, a sulfur-containing group, a nitrogen-containing group, a boron-containing group, an aluminum-containing group, a phosphorus-containing group, a halogen-containing group, a heterocyclic compound residue, a silicon-containing

group, a germanium-containing group or a tin-containing group, and when  $n$  is 2 or greater, plural groups  $X$  may be the same or different and may be bonded to each other to form a ring.

- 5        Examples of the halogen atom include fluorine, chlorine, bromine and iodine.

- 10       Examples of the hydrocarbon groups include those exemplified for  $R^1$  to  $R^6$ . Specifically, there can be mentioned, but not limited to, alkyl groups, such as methyl, ethyl, propyl, butyl, hexyl, octyl, nonyl, dodecyl and eicosyl; cycloalkyl groups of 3 to 30 carbon atoms, such as cyclopentyl, cyclohexyl, norbornyl and adamantyl; alkenyl groups, such as vinyl, propenyl and cyclohexenyl; arylalkyl groups, such as benzyl, phenylethyl and phenylpropyl; and aryl groups, such as phenyl, tolyl, dimethylphenyl, trimethylphenyl, ethylphenyl, propylphenyl, biphenyl, naphthyl, methylnaphthyl, anthryl and phenanthryl.

- 20       These hydrocarbon groups include halogenated hydrocarbon groups, and more specifically at least one hydrogen of the hydrocarbon groups of 1 to 30 carbon atoms may be substituted with a halogen atom.

Of these, preferable are those of 1 to 20 carbon atoms.

Examples of the heterocyclic compound residues include those exemplified for  $R^1$  to  $R^6$

Examples of the oxygen-containing groups include those exemplified for  $R^1$  to  $R^6$ . Specifically, there  
5 can be mentioned, but not limited to, hydroxyl; alkoxy groups, such as methoxy, ethoxy, propoxy and butoxy; aryloxy groups, such as phenoxy, methylphenoxy, dimethylphenoxy and naphthoxy; arylalkoxy groups, such as phenylmethoxy and phenylethoxy; acetoxy groups; and  
10 carbonyl group.

Examples of the sulfur-containing groups include those exemplified for  $R^1$  to  $R^6$ . Specifically, there can be mentioned, but not limited to, sulfonato groups, such as methylsulfonato, trifluoromethanesulfonato,  
15 phenylsulfonato, benzylsulfonato, p-toluenesulfonato, trimethylbenzenesulfonato, triisobutylbenzenesulfonato, p-chlorobenzenesulfonato and pentafluorobenzenesulfonato; sulfinato groups, such as methylsulfinato, phenylsulfinato, benzylsulfinato, p-toluenesulfinato, trimethylbenzenesulfinato and  
20 pentafluorobenzenesulfinato; alkylthio groups; and arylthio groups.

Examples of the nitrogen-containing groups include those exemplified for  $R^1$  to  $R^6$ . Specifically, there can  
25 be mentioned, but not limited to, amino group; alkylamino groups, such as methyl amino, dimethylamino;

diethylamino; dipropylamino, dibutylamino and dicyclohexylamino; arylamino groups and alkylarylamino groups, such as phenylamino, diphenylamino, ditolylamino, dinaphthylamino and methylphenylamino.

5        Examples of the boron-containing groups include  $BR_4$  groups (where R is a hydrogen, an aryl group which may have a substituent, a halogen, etc.).

10        Examples of the silicon-containing groups include those exemplified for  $R^1$  to  $R^6$ . Specifically, there can be mentioned, but not limited to, hydrocarbon-substituted silyl groups, such as phenylsilyl, diphenylsilyl, trimethylsilyl, triethylsilyl, tripropylsilyl, tricyclohexylsilyl, triphenylsilyl, methyldiphenylsilyl, tritolylsilyl and trinaphthylsilyl; 15 hydrocarbon-substituted silylether groups, such as trimethylsilylether; silicon-substituted alkyl groups, such as trimethylsilylmethyl; and silicon-substituted aryl groups, such as trimethylsilylphenyl.

20        Examples of the germanium-containing groups include those exemplified for  $R^1$  to  $R^6$ . Specifically, there can be mentioned the above-mentioned silicon-containing groups in which silicon is replaced by germanium.

25        Examples of the tin-containing groups include those exemplified for  $R^1$  to  $R^6$ . Specifically, there can be mentioned the above-mentioned silicon-containing groups in which silicon is replaced by tin.


Examples of the halogen-containing groups include fluorine-containing groups, such as  $\text{PF}_6$  and  $\text{BF}_4$ ; chlorine-containing groups, such as  $\text{ClO}_4$  and  $\text{SbCl}_6$ ; and iodine-containing groups, such as  $\text{IO}_4$ , but not limited thereto.

Examples of the aluminium-containing groups include  $\text{AR}_4$  groups (where R is a hydrogen, an alkyl group, an aryl group which may have a substituent, a halogen atom, etc.), but not limited thereto.

When n is 2 or greater, plural groups X may be the same or different and may be bonded to each other to form a ring.

#### Transition metal compound (I-a)

The transition compound represented by the formula (I) is preferably a compound represented by the formula (I-a).





In the formula (I-a), M is a transition metal atom of Group 3 to Group 11 of the periodic table. Examples of M include the above-mentioned transition metal atoms.

m is an integer of 1 to 3, preferably 2.

- 5         $R^1$  to  $R^6$  may be the same or different, and are each a hydrogen atom, a halogen atom, a hydrocarbon group, a heterocyclic compound residues, a hydrocarbon-substituted silyl group, a hydrocarbon-substituted siloxy group, an alkoxy group, an alkylthio group, an
- 10        aryloxy group, an arylthio group, an acyl group, an ester group, a thioester group, an amido group, an imido group, an amino group, an imino group, a sulfonester group, a sulfonamido group, a cyano group, a nitro group, a carboxyl group, a sulfo group, a mercapto
- 15        group or a hydroxyl group, and two or more of them may be bonded to each other to form a ring. Examples of  $R^1$  to  $R^6$  include those described above.

- 20        When m is 2 or greater, two of the groups  $R^1$  to  $R^6$  may be bonded to each other, with the proviso that the groups  $R^1$  are not bonded to each other.


n is a number satisfying a valence of M, specifically an integer of 0 to 5, preferably 1 to 4, more preferably 1 to 3.

- 25        X is a hydrogen atom, a halogen atom, a hydrocarbon group, an oxygen-containing group, a nitrogen-containing group, a boron-containing group, a sulfur-containing

group, a phosphorus-containing group, a silicon-containing group, a germanium-containing group or a tin-containing group. Examples of X include those described above.

- 5 When n is 2 or greater, plural groups X may be the same or different and may be bonded to each other to form a ring.

The transition metal compound represented by the formula (I) is preferably a compound represented by the  
10 following formula (I-a-1).



- 15 In the formula (I-a-1),  $R^1$  to  $R^6$ , M and X have the same meanings as mentioned above, and are preferably those described below.

M is a transition metal atom of Group 3 to Group 11 of the periodic table, preferably of Group 3 to Group 5 and Group 9, e.g., scandium, titanium, zirconium,  
20 hafnium, vanadium, niobium, tantalum, cobalt or rhodium, more preferably titanium, zirconium, hafnium, cobalt or

rhodium, particularly preferably titanium, zirconium or hafnium.

m is an integer of 1 to 3.

- 5      $R^1$  to  $R^6$  may be the same or different, and are each a hydrogen atom, a halogen atom, a hydrocarbon group, a heterocyclic compound residues, a hydrocarbon-substituted silyl group, a hydrocarbon-substituted siloxy group, an alkoxy group, an alkylthio group, an aryloxy group, an arylthio group, a thioester group, an ester group, an acyl group, an amido group, an imido group, an amino group, an imino group, a sulfonester group, a sulfonamido group, a cyano group, a nitro group or a hydroxyl group. Of these, particularly preferable is a hydrogen atom, a halogen atom, a hydrocarbon-substituted silyl group, an alkoxy group, an aryloxy group, an ester group, an amido group, an amino group, a sulfonamido group, a cyano group or a nitro group.
- 10
- 15

Examples of the halogen atom include fluorine, chlorine, bromine and iodine.

- 20     Examples of the hydrocarbon groups include straight-chain or branched alkyl groups of 1 to 20 carbon atoms, such as methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, pentyl and hexyl; straight-chain or branched alkenyl groups of 2 to 20 carbon atoms, such as vinyl, allyl and
- 25

isopropenyl; straight-chain or branched alkynyl groups of 2 to 20 carbon atoms, such as ethynyl and propargyl; cyclic saturated hydrocarbon groups of 3 to 20 carbon atoms, such as cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl and adamantyl; aryl groups of 6 to 20 carbon atoms, such as phenyl, benzyl, naphthyl, biphenyl and triphenyl; cyclic unsaturated hydrocarbon groups of 5 to 20 carbon atoms, such as cyclopentadienyl, indenyl and fluorenyl; and these groups which are substituted with substituents such as alkyl groups of 1 to 20 carbon atoms, halogenated alkyl groups of 1 to 20 carbon atoms, aryl groups of 6 to 20 carbon atoms, alkoxy groups of 1 to 20 carbon atoms, aryloxy groups of 6 to 20 carbon atoms, halogen, cyano, nitro and hydroxyl. Of these, particularly preferable are straight-chain or branched alkyl groups of 1 to 20 carbon atoms, such as methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, pentyl and hexyl; aryl groups of 6 to 20 carbon atoms, such as phenyl and naphthyl; and these aryl groups which are substituted with 1 to 5 substituents such as alkyl groups of 1 to 20 carbon atoms, aryl groups of 6 to 20 carbon atoms, alkoxy groups of 1 to 20 carbon atoms and aryloxy groups of 6 to 20 carbon atoms.

0942706-083404

Examples of the heterocyclic residues include residues of nitrogen-containing compounds (e.g., pyrrole, pyridine, pyrimidine, quinoline and triazine), oxygen-containing compounds (e.g., furan and pyran) and sulfur-containing compounds (e.g., thiophene), and these heterocyclic residues which are substituted with substituents such as alkyl groups and alkoxy groups for 1 to 20 carbon atoms.

Examples of the hydrocarbon-substituted silyl groups include methylsilyl, dimethylsilyl, trimethylsilyl, ethylsilyl, diethylsilyl, triethylsilyl, diphenylmethylsilyl, triphenylsilyl, dimethylphenylsilyl, dimethyl-t-butylsilyl and dimethyl(pentafluorophenyl)silyl. Of these, particularly preferable are methylsilyl, dimethylsilyl, trimethylsilyl, ethylsilyl, diethylsilyl, triethylsilyl and triphenylsilyl.

Examples of the hydrocarbon-substituted siloxy groups include trimethylsiloxy.

Examples of the alkoxy groups include methoxy, ethoxy, n-propoxy, isopropoxy, n-butoxy, isobutoxy and tert-butoxy.

Examples of the alkylthio groups include methylthio and ethylthio.

Examples of the aryloxy groups include phenoxy, 2,6-dimethylphenoxy and 2,4,6-trimethylphenoxy.

Examples of the arylthio groups include phenylthio, methylphenylthio and naphthylthio.

- 5        Examples of the acyl groups include formyl, acetyl, benzoyl, p-chlorobenzoyl and p-methoxybenzoyl.

Examples of the ester groups include acetyloxy, benzoyloxy, methoxycarbonyl, phenoxycarbonyl and p-chlorophenoxycarbonyl.

- 10       Examples of the thioester groups include acetylthio, benzoylthio, methylthiocarbonyl and phenylthiocarbonyl.

Examples of the amido groups include acetamido, N-methylacetamido and N-methylbenzamido.

- 15       Examples of the imido groups include acetimido and benzimido.

Examples of the amino groups include dimethylamino, ethylmethylamino and diphenylamino.

- 20       Examples of the imino groups include methylimino, ethylimino, propylimino, butylimino and phenylimino.

Examples of the sulfonester groups include methylsulfonato, ethylsulfonato and phenylsulfonato.

- 25       Examples of the sulfonamido groups include phenylsulfonamido, N-methylsulfonamido and N-methyl-p-toluenesulfonamido.

R<sup>6</sup> is preferably a substituent other than hydrogen. That is, R<sup>6</sup> is preferably a halogen atom, a hydrocarbon group, a heterocyclic compound residues, a hydrocarbon-substituted silyl group, a hydrocarbon-substituted siloxy group, an alkoxy group, an alkylthio group, an aryloxy group, an arylthio group, an acyl group, an ester group, a thioester group, an amido group, an imido group, an amino group, an imino group, a sulfonester group, a sulfonamido group, a cyano group, a nitro group or a hydroxyl group.

Preferred examples of the hydrocarbon groups as R<sup>6</sup> include straight-chain or branched alkyl groups of 1 to 20 carbon atoms, such as methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, pentyl and hexyl; cyclic saturated hydrocarbon groups of 3 to 20 carbon atoms, such as cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl and adamantyl; aryl groups of 6 to 20 carbon atoms, such as phenyl, benzyl, naphthyl, biphenyl and triphenyl; and these groups which are substituted with substituents such as alkyl groups of 1 to 20 carbon atoms, halogenated alkyl groups of 1 to 20 carbon atoms, aryl groups of 6 to 20 carbon atoms, alkoxy groups of 1 to 20 carbon atoms, aryloxy groups of 6 to 20 carbon atoms, halogen, cyano, nitro and hydroxyl.

Preferred examples of the hydrocarbon-substituted silyl groups as  $R^6$  include methylsilyl, dimethylsilyl, trimethylsilyl, ethylsilyl, diethylsilyl, triethylsilyl, diphenylmethylsilyl, triphenylsilyl,

5 dimethylphenylsilyl, dimethyl-t-butylsilyl and dimethyl(pentafluorophenyl)silyl.

In the present invention,  $R^6$  is preferably selected from branched alkyl groups of 3 to 20 carbon atoms (e.g., isopropyl, isobutyl, sec-butyl and tert-butyl),  
10 these alkyl groups which are substituted with aryl groups of 6 to 20 carbon atoms (e.g., cumyl), and cyclic saturated hydrocarbon groups of 3 to 20 carbon atoms (e.g., adamantyl, cyclopropyl, cyclobutyl, cyclopentyl and cyclohexyl). Also, preferable  $R^6$  is a hydrocarbon-  
15 substituted silyl group.

Two or more groups  $R^1$  to  $R^6$ , preferably adjacent groups, may be bonded to each other to form an aliphatic ring, an aromatic ring or a hydrocarbon ring containing a hetero atom such as a nitrogen atom, and these rings  
20 may further have a substituent.

When  $m$  is 2 or greater, two of the the groups  $R^1$  to  $R^6$  may be bonded to each other, with the proviso that the groups  $R^1$  are not bonded to each other.  $R^1$ s,  $R^2$ s,  $R^3$ s,  $R^4$ s,  $R^5$ s, or  $R^6$ s may be the same as or different  
25 from each other.



n is a number satisfying a valence of M,  
specifically an integer of 1 to 3.

5 X is a hydrogen atom, a halogen atom, a hydrocarbon  
group of 1 to 20 carbon atoms, a halogenated hydrocarbon  
group of 1 to 20 carbon atoms, an oxygen-containing  
group, a sulfur-containing group or a silicon-containing  
group, and when n is 2 or greater, plural groups X may  
be the same or different.

10 Examples of the he halogen atoms include fluorine,  
chlorine, bromine and iodine.

Examples of the hydrocarbon groups of 1 to 20  
carbon atoms include alkyl groups, cycloalkyl groups,  
alkenyl groups, arylalkyl groups and aryl groups.  
Specifically, there can be mentioned alkyl groups, such  
15 as methyl, ethyl, propyl, butyl, hexyl, octyl, nonyl,  
dodecyl and eicosyl; cycloalkyl groups, such as  
cyclopentyl, cyclohexyl, norbornyl and adamantyl;  
alkenyl groups, such as vinyl, propenyl and  
cyclohexenyl; arylalkyl groups, such as benzyl,  
20 phenylethyl and phenylpropyl; and aryl groups, such as  
phenyl, tolyl, dimethylphenyl, trimethylphenyl,  
ethylphenyl, propylphenyl, biphenyl, naphthyl,  
methylnaphthyl, anthryl and phenanthryl.

Examples of the halogenated hydrocarbon groups of 1  
25 to 20 carbon atoms include the above-mentioned

hydrocarbon groups of 1 to 20 carbon atoms which are substituted with halogens.

Examples of the oxygen-containing groups include hydroxyl; alkoxy groups, such as methoxy, ethoxy, 5 propoxy and butoxy; aryloxy groups, such as phenoxy, methylphenoxy, dimethylphenoxy and naphthoxy; and arylalkoxy groups, such as phenylmethoxy and phenylethoxy.

Examples of the sulfur-containing groups include 10 the above-exemplified oxygen-containing groups in which oxygen is replaced with sulfur; sulfonato groups, such as methylsulfonato, trifluoromethanesulfonato, phenylsulfonato, benzylsulfonato, p-toluenesulfonato, trimethylbenzenesulfonato, triisobutylbenzenesulfonato, 15 p-chlorobenzenesulfonato and pentafluorobenzenesulfonato; and sulfinato groups, such as methylsulfinato, phenylsulfinato, benzylsulfinato, p-toluenesulfinato, trimethylbenzenesulfinato and pentafluorobenzenesulfinato.

20 Examples of the silicon-containing groups include monohydrocarbon-substituted silyl groups, such as methylsilyl and phenylsilyl; dihydrocarbon-substituted silyl groups, such as dimethylsilyl and diphenylsilyl; trihydrocarbon-substituted silyl groups, such as 25 trimethylsilyl, triethylsilyl, tripropylsilyl,


05942706-003401  
101E80-9024660

tricyclohexylsilyl, triphenylsilyl, dimethylphenylsilyl, methyldiphenylsilyl, tritolylsilyl and trinaphthylsilyl; silyl ether groups of hydrocarbon-substituted silyl, such as trimethylsilyl ether; silicon-substituted alkyl groups, such as trimethylsilylmethyl; and silicon-substituted aryl groups, such as trimethylsilylphenyl.

Of these, preferable groups X are halogen atoms, hydrocarbon atoms of 1 to 20 carbon atoms and sulfonato groups.

10 When n is 2 or greater, groups X may be bonded to each other to form a ring.

Of the transition metal compounds represented by the formula (I-a-1), the compound wherein m is 2 and two of the groups  $R^1$  to  $R^6$  (except for the groups  $R^1$ ) are bonded to each other is, for example, a compound represented by the following formula (I-a-2).



In the formula (I-a-2), M, R<sup>1</sup> to R<sup>6</sup>, and X are identical with M, R<sup>1</sup> to R<sup>6</sup>, and X in the formula (I).

R<sup>1</sup> to R<sup>16</sup> may be the same or different, and are each a hydrogen atom, a halogen atom, a hydrocarbon group, a heterocyclic compound residue, a hydrocarbon-substituted silyl group, a hydrocarbon-substituted siloxy group, an alkoxy group, an alkylthio group, an aryloxy group, an arylthio group, an acyl group, an ester group, a thioester group, an amido group, an imido group, an amino group, an imino group, a sulfonester group, a sulfonamido group, a cyano group or a nitro group, specifically, the same atom or group as described for R<sup>1</sup> to R<sup>6</sup>. Two or more of groups R<sup>1</sup> to R<sup>16</sup>, preferably adjacent groups, may be bonded to each other to form an aliphatic ring, an aromatic ring or a hydrocarbon ring containing a hetero atom such as a nitrogen atom.

Y' is a bonding group or a single bond for bonding at least one group selected from R<sup>1</sup> to R<sup>6</sup> to at least one group selected from R<sup>11</sup> to R<sup>16</sup> (except a case of bonding R<sup>1</sup> and R<sup>11</sup> to each other).

The bonding group Y' is a group containing at least one element selected from among oxygen, sulfur, carbon, nitrogen, phosphorus, silicon, selenium, tin, boron and the like. Examples of such groups include groups containing chalcogen atoms such as -O-, -S- and -Se-;

5 carbon atoms, such as benzene, naphthalene and anthracene; residues of heterocyclic compounds having 3 to 20 carbon atoms and containing hetero atoms, such as pyridine, quinoline, thiophene and furan; silicon atom-containing groups, such as  $-\text{SiH}_2-$  and  $-\text{Si}(\text{CH}_3)_2$ ; tin

10 atom-containing groups, such as  $-\text{SnH}_2-$  and  $-\text{Sn}(\text{CH}_3)_2$ ; and boron atom-containing groups, such as  $-\text{BH}-$ ,  $-\text{B}(\text{CH}_3)-$  and  $-\text{BF}-$ .






15 are not limited thereto.


20 Ph(III), Ph(IV). Of these, particularly preferable is  
Ti(IV), Zr(IV) or Hf(IV).

X is halogen such as Cl or Br, or an alkyl group such as methyl, but not limited thereto. When plural X are present, they may be the same or different.


n depends on a valence of the metal M. For example, when two monoanion species are bonded to the metal,  $n = 0$  in case of a divalent metal,  $n = 1$  in case of a trivalent metal,  $n = 2$  in case of a tetravalent metal, and  $n = 3$  in case of a pentavalent metal. More specifically, there can be mentioned  $n = 2$  in case of Ti(IV),  $n = 2$  in case of Zr(IV), and  $n = 2$  in case of Hf(IV).


0394706-03404  
TOP SECRET

































































































































In the above chemical formulae, Me is methyl, Et is ethyl, iPr is isopropyl, tBu is tert-butyl and Ph is phenyl.


- 5 More specific examples of compounds having a center metal Ti are given below. There can also be mentioned those compounds in which titanium is replaced with zirconium, hafnium, cobalt or rhodium.














09942706-083401







































In the olefin polymerization catalyst according to the invention, it is particularly preferable to use a novel transition metal compound of the formula (III), which will be described in detail below, as the catalyst component (A').

Transition metal compound (I-b)

Also employable as the transition metal compound (A) in the invention is a transition metal compound represented by the following formula (I-b).



In the formula (I-b), M is a transition metal atom of Group 3 to Group 11 of the periodic table, preferably of Group 4 or Group 9, and particularly preferably, titanium, zirconium, hafnium, cobalt or rhodium.

m is an integer of 1 to 6, preferably 1 to 4.

R<sup>1</sup> to R<sup>6</sup> may be the same or different, and are each a hydrogen atom, a halogen atom, a hydrocarbon group, a hydrocarbon-substituted silyl group, an alkoxy group, an

aryloxy group, an ester group, an amido group, an amino group, a sulfonamido group, a cyano group or a nitro group.


Of these, particularly preferable is a halogen  
5 atom, a hydrocarbon group, a hydrocarbon-substituted silyl group, an alkoxy group, an aryloxy group, an ester group, an amido group, an amino group, a sulfonamido group, a cyano group or a nitro group.

Examples of the groups  $R^1$  to  $R^6$  are those  
10 exemplified for the transition metal compounds of the formulae (I) and (I-a).


When  $m$  is 2 or greater, two or more groups  $R^1$  to  $R^6$ , preferably adjacent groups, may be bonded to each other to form a ring, with the proviso that the groups  $R^1$  are  
15 not bonded to each other.

Examples of the transition metal compounds represented by the formula (I-b) are given below, but not limited thereto.

09443706-083104  
101E80-90/24660







09412705-083104


In the present invention, transition metal compounds wherein cobalt is replaced with titanium, zirconium, hafnium, iron, copper or rhodium in the above-exemplified compounds are also employable.

- 5        The transition metal compounds (A) mentioned above are used singly or in combination of two or more kinds, and they can be used in combination with other transition metal compounds, for example known transition metal compounds comprising a ligand which has a hetero  
10    atom such as nitrogen, oxygen, sulfur, boron or phosphorus.

Other transition metal compound

- Some examples of the other transition metal  
15    compounds are given below, but the compounds are not limited those examples.

(a-1) Transition metal imide compound (I-c)



(I-c)

In the above formula, M is a transition metal atom of Group 8 to Group 10 of the periodic table, preferably nickel, palladium or platinum.


R<sup>21</sup> to R<sup>24</sup> may be the same or different, and are  
 5 each a hydrocarbon group of 1 to 50 carbon atoms, a halogenated hydrocarbon group of 1 to 50 carbon atoms, a hydrocarbon-substituted silyl group, or a hydrocarbon group substituted with a substituent containing at least one element selected from nitrogen, oxygen, phosphorus,  
 10 sulfur and silicon.

Two or more groups, preferably adjacent groups, of R<sup>21</sup> to R<sup>24</sup> may be bonded to each other to form a ring.

q is an integer of 0 to 4.

X is a hydrogen atom, a halogen atom, a hydrocarbon  
 15 group of 1 to 20 carbon atoms, a halogenated hydrocarbon group of 1 to 20 carbon atoms, an oxygen-containing group, a sulfur-containing group, a silicon-containing group or nitrogen-containing group, and when q is 2 or greater, plural groups X may be the same or different.

20 (a-2) Transition metal amide compound (I-d)



In the above formula, M is a transition metal atom of Group 3 to Group 6 of the periodic table, preferably titanium, zirconium or hafnium.

- 5        R' and R" may be the same or different, and are each a hydrogen atom, a hydrocarbon group of 1 to 50 carbon atoms, a halogenated hydrocarbon group of 1 to 50 carbon atoms, a hydrocarbon-substituted silyl group, or a substituent containing at least one element selected  
10      from nitrogen, oxygen, phosphorus, sulfur and silicon.

m is an integer of 0 to 2.

n is an integer of 1 to 5.

- A is an atom of Group 13 to Group 16 of the periodic table, specifically boron, carbon, nitrogen,  
15      oxygen, silicon, phosphorus, sulfur, germanium, selenium, tin or the like, preferably carbon or silicon.

When n is 2 or greater, plural atoms A may be the same or different.


- E is a substituent containing at least one element  
20      selected from carbon, hydrogen, oxygen, halogen, nitrogen, sulfur, phosphorus, boron and silicon. When plural groups E are present, they may be the same or different, and two or more groups E may be bonded to form a ring.

- 25        p is an integer of 0 to 4.

X is a hydrogen atom, a halogen atom, a hydrocarbon group of 1 to 20 carbon atoms, a halogenated hydrocarbon group of 1 to 20 carbon atoms, an oxygen-containing group, a sulfur-containing group, a silicon-containing group or nitrogen-containing group. When p is 2 or greater, plural groups X may be the same or different.

X is preferably a halogen atom, a hydrocarbon group of 1 to 20 carbon atoms or a sulfonato group.

(a-3) Transition metal diphenoxy compound (I-e)



In the above formula, M is a transition metal atom of Group 3 to Group 11 of the periodic table; l and m are each an integer of 0 or 1; A and A' are each a hydrocarbon group of 1 to 50 carbon atoms, a halogenated hydrocarbon group of 1 to 50 carbon atoms, a hydrocarbon group having a substituent containing oxygen, sulfur or silicon, or a halogenated hydrocarbon group having a substituent containing oxygen, sulfur or silicon; and A and A' may be the same or different.


B is a hydrocarbon group of 0 to 50 carbon atoms, a halogenated hydrocarbon group of 1 to 50 carbon atoms,

$R^1R^2Z$ , oxygen or sulfur, where  $R^1$  and  $R^2$  are each a hydrocarbon group of 1 to 20 carbon atoms or a hydrocarbon group having 1 to 20 carbon atoms and containing at least one hetero atom, and Z is carbon, nitrogen, sulfur, phosphorus or silicon.

n is a number satisfying a valence of M.

X is a hydrogen atom, a halogen atom, a hydrocarbon group of 1 to 20 carbon atoms, a halogenated hydrocarbon group of 1 to 20 carbon atoms, an oxygen-containing group, a sulfur-containing group, a silicon-containing group or nitrogen-containing group, and when n is 2 or greater, plural groups X may be the same or different and may be bonded to form a ring.

(a-4) Transition metal compound (I-f) containing at least one hetero atom and containing a ligand having cyclopentadienyl skeleton



In the above formula, M is a transition metal atom of Group 3 to Group 11 of the periodic table. X is an

atom of Group 13, Group 14 or Group 15, and at least one of X contains an element other than carbon.

Each R may be the same or different, and is a hydrogen atom, a halogen atom, a hydrocarbon group, a halogenated hydrocarbon group, a hydrocarbon-substituted silyl group or a hydrocarbon group substituted with a substituent containing at least one element selected from nitrogen, oxygen, phosphorus, sulfur and silicon. Two or more of R may be bonded to form a ring, and a is 0 or 1.

b is an integer of 1 to 4, when b is a number of 2 or greater, the moieties  $[(R)_a]_5X_5$  may be the same or different, and the groups R may be bonded to form a bridge.

c is a number satisfying a valence of M.

Y is a hydrogen atom, a halogen atom, a hydrocarbon group of 1 to 20 carbon atoms, a halogenated hydrocarbon group of 1 to 20 carbon atoms, an oxygen-containing group, a sulfur-containing group, a silicon-containing group, or nitrogen-containing group. When c is a number of 2 or greater, plural groups Y may be the same or different and may be bonded to form a ring.


(a-5) Transition metal compound represented by the formula  $RB(Pz)_3MX_n$

In the above formula, M is a transition metal atom of Group 3 to Group 11 of the periodic table; R is a hydrogen atom, a hydrocarbon group of 1 to 20 carbon atoms or a halogenated hydrocarbon group of 1 to 20 carbon atoms; and Pz is a pyrazolyl group or a substituted pyrazolyl group.

n is a number satisfying a valence of M.

X is a hydrogen atom, a halogen atom, a hydrocarbon group of 1 to 20 carbon atoms, a halogenated hydrocarbon group of 1 to 20 carbon atoms, an oxygen-containing group, a sulfur-containing group, a silicon-containing group or nitrogen-containing group, and when n is a number of 2 or greater, plural groups X may be the same or different and may be bonded to form a ring.

(a-6) Transition metal compound represented by the following formula (I-g)




In the above formula, Y<sub>1</sub> and Y<sub>3</sub> are each an element of Group 15 of the periodic table; Y<sub>2</sub> is an element of Group 16 of the periodic table; and R<sup>21</sup> to R<sup>28</sup> may be the




same or different, they are each a hydrogen atom, a halogen atom, a hydrocarbon group of 1 to 20 carbon atoms, a halogenated hydrocarbon group of 1 to 20 carbon atoms, an oxygen-containing group, a sulfur-containing group or a silicon-containing group, and two or more of them may be bonded to form a ring.

(a-7) Transition metal compound comprising a compound represented by the following formula (I-h) and a transition metal atom of Group VIII



In the above formula,  $R^{31}$  to  $R^{34}$  may be the same or different, they are each a hydrogen atom, a halogen atom, a hydrocarbon group of 1 to 20 carbon atoms or a halogenated hydrocarbon group of 1 to 20 carbon atoms, and two or more of them may be bonded to form a ring.

(a-8) Transition metal compound represented by the following formula (I-i)



In the above formula, M is a transition metal atom of Group 3 to Group 11 of the periodic table.

m is an integer of 0 to 3.

5 n is an integer of 0 or 1.

p is an integer of 1 to 3.

q is a number satisfying a valence of M.

R<sup>41</sup> to R<sup>48</sup> may be the same or different, and are each a hydrogen atom, a halogen atom, a hydrocarbon group of 1 to 20 carbon atoms or a halogenated hydrocarbon group of 1 to 20 carbon atoms, an oxygen-containing group, a sulfur-containing group, a silicon-containing group or nitrogen-containing group, and two or more of them may be bonded to form a ring.

15 X is a hydrogen atom, a halogen atom, a hydrocarbon group of 1 to 20 carbon atoms, a halogenated hydrocarbon group of 1 to 20 carbon atoms, an oxygen-containing group, a sulfur-containing group, a silicon-containing group or a nitrogen-containing group, and when q is 2 or greater, plural X may be the same or different and may be bonded to each other to form a ring.


20 Y is a group bridging the borata benzen ring, and Y is carbon, silicon or germanium.

A is an element of Group 14, Group 15 or Group 16 of the periodic table.

(B-1) Organometallic compound


As the organometallic compound (B-1), the below-described organometallic compounds of metals of Group 1, Group 2, Group 12 and Group 13 of the periodic table are employable in the invention.

(B-1a) Organoaluminum compound represented by the following formula:




- 10 wherein  $R^a$  and  $R^b$  may be the same or different, and are each a hydrocarbon group of 1 to 15 carbon atoms, preferably a hydrocarbon group of 1 to 4 carbon atoms;  $X$  is a halogen atom; and  $m$ ,  $n$ ,  $p$  and  $q$  are numbers satisfying the conditions of  $0 < m \leq 3$ ,  $0 \leq n < 3$ ,  $0 \leq p < 3$ ,  $0 \leq q < 3$  and  $m+n+p+q = 3$ .

(B-1b) Alkyl complex compound of Group 1 metal and aluminum, that is represented by the following formula:



- 20 wherein  $M^2$  is Li, Na or K; and  $R^a$  is a hydrocarbon group of 1 to 15 carbon atoms, preferably a hydrocarbon group of 1 to 4 carbon atoms.


(B-1c) Dialkyl compound of Group 2 metal or Group 12 metal, that is represented by the following formula:



wherein  $R^a$  and  $R^b$  may be the same or different, and are each a hydrocarbon group of 1 to 15 carbon atoms, preferably a hydrocarbon group of 1 to 4 carbon atoms; and  $M^3$  is Mg, Zn or Cd.


- 5        Examples of the organoaluminum compounds (B-1a) include the following compounds.

Organoaluminum compound represented by the following formula:




- 10       wherein  $R^a$  and  $R^b$  may be the same or different, and are each a hydrocarbon group of 1 to 15 carbon atoms, preferably a hydrocarbon group of 1 to 4 carbon atoms; and  $m$  is preferably a number satisfying the condition of  $1.5 \leq m \leq 3$ .

- 15       Organoaluminum compound represented by the following formula:




- wherein  $R^a$  is a hydrocarbon group of 1 to 15 carbon atoms, preferably a hydrocarbon group of 1 to 4 carbon  
20       atoms;  $X$  is a halogen atom; and  $m$  is preferably a number satisfying the condition of  $0 < m < 3$ .

Organoaluminum compound represented by the following formula:



wherein  $R^a$  is a hydrocarbon group of 1 to 15 carbon atoms, preferably a hydrocarbon group of 1 to 4 carbon atoms; and  $m$  is preferably a number satisfying the condition of  $2 \leq m < 3$ .

- 5           Organoaluminum compound represented by the following formula:



- wherein  $R^a$  and  $R^b$  may be the same or different, and are each a hydrocarbon group of 1 to 15 carbon atoms,  
 10           preferably a hydrocarbon group of 1 to 4 carbon atoms;  $X$  is a halogen atom; and  $m$ ,  $n$  and  $q$  are numbers satisfying the conditions of  $0 < m \leq 3$ ,  $0 \leq n < 3$ ,  $0 \leq q < 3$  and  $m+n+q = 3$ .

Particular examples of the organoaluminum compounds (B-1a) include:

- 15           tri-n-alkylaluminums, such as trimethylaluminum, triethylaluminum, tri-n-butylaluminum, tripropylaluminum, tripentylaluminum, trihexylaluminum, trioctylaluminum and tridecylaluminum;  
               branched-chain trialkylaluminums, such as  
 20           triisopropylaluminum, triisobutylaluminum, tri-sec-butylaluminum, tri-tert-butylaluminum, tri-2-methylbutylaluminum, tri-3-methylbutylaluminum, tri-2-methylpentylaluminum, tri-3-methylpentylaluminum, tri-4-methylpentylaluminum, tri-2-methylhexylaluminum, tri-3-  
 25           methylhexylaluminum and tri-2-ethylhexylaluminum;

tricycloalkylaluminums, such as  
 tricyclohexylaluminum and tricyclooctylaluminum;  
 triarylaluminums, such as triphenylaluminum and  
 tritolylaluminum;

- 5        dialkylaluminum hydrides, such as  
 diisobutylaluminum hydride;

trialkenylaluminums represented by the formula (i-  
 $C_4H_9)_xAl_y(C_5H_{10})_z$  (wherein x, y and z are positive  
 numbers, and  $z \geq 2x$ ), such as isoprenylaluminum;

- 10        alkylaluminum alkoxides, such as isobutylaluminum  
 methoxide, isobutylaluminum ethoxide and  
 isobutylaluminum isopropoxide;

dialkylaluminum alkoxides, such as dimethylaluminum  
 methoxide, diethylaluminum ethoxide and dibutylaluminum

- 15        butoxide;

alkylaluminum sesquialkoxides, such as  
 ethylaluminum sesquiethoxide and butylaluminum  
 sesquibutoxide;

- 20        partially alkoxyated alkylaluminums having an  
 average composition represented by  $R^{a_{2.5}}Al(OR^b)_{0.5}$ ;

dialkylaluminum aryloxides, such as diethylaluminum  
 phenoxide, diethylaluminum(2,6-di-t-butyl-4-  
 methylphenoxide), ethylaluminumbis(2,6-di-t-butyl-4-  
 methylphenoxide), diisobutylaluminum(2,6-di-t-butyl-4-

methoxyphenoxide) and isobutylaluminumbis(2,6-di-t-butyl-4-methoxyphenoxide);

dialkylaluminum halides, such as dimethylaluminum chloride, diethylaluminum chloride, dibutylaluminum chloride, diethylaluminum bromide and diisobutylaluminum chloride;

alkylaluminum sesquihalides, such as ethylaluminum sesquichloride, butylaluminum sesquichloride and ethylaluminum sesquibromide,

10 partially halogenated alkylaluminums, such as ethylaluminum dichloride, propylaluminum dichloride and butylaluminum dibromide;

dialkylaluminum hydrides, such as diethylaluminum hydride and dibutylaluminum hydride;

15 partially hydrogenated alkylaluminums, e.g., alkylaluminum dihydrides, such as ethylaluminum dihydride and propylaluminum dihydride; and

partially alkoxylated and halogenated alkylaluminums, such as ethylaluminum ethoxychloride, butylaluminum butoxychloride and ethylaluminum ethoxybromide.

Also employable are compounds analogous to the organoaluminum compound (B-1a). For example, there can be mentioned organoaluminum compounds wherein two or

03942706.083404  
TORERO 90724560

more aluminum compounds are combined through a nitrogen atom, such as  $(C_2H_5)_2AlN(C_2H_5)Al(C_2H_5)_2$ .

Examples of the organoaluminum compounds (B-1b) include  $LiAl(C_2H_5)_4$  and  $LiAl(C_7H_{15})_4$ .

5 Further, other compounds such as methyllithium, ethyllithium, propyllithium, butyllithium, methylmagnesium bromide, methylmagnesium chloride, ethylmagnesium bromide, ethylmagnesium chloride, propylmagnesium bromide, propylmagnesium chloride,  
10 butylmagnesium bromide, butylmagnesium chloride, dimethylmagnesium, diethylmagnesium, dibutylmagnesium and butylethylmagnesium are also employable as the organometallic compounds (B-1).

Furthermore, combinations of compounds capable of  
15 producing the above-mentioned organoaluminum compounds in the polymerization system, e.g., a combination of halogenated aluminum and alkylolithium and a combination of halogenated aluminum and alkylmagnesium, are also employable.

20 Of the organometallic compounds (B-1) mentioned above, the organoaluminum compounds are preferable.

The organometallic compounds (B-1) can be used singly or in combination of two or more kinds.

25 (B-2) Organoaluminum oxy-compound



The organoaluminum oxy-compound (B-2) for use in the invention may be conventional aluminoxane or a benzene-insoluble organoaluminum oxy-compound exemplified in Japanese Patent Laid-Open Publication No.

5 78687/1990.

The conventional aluminoxane can be prepared by, for example, the following processes, and is generally obtained as a hydrocarbon solvent solution.

(1) An organoaluminum compound such as  
10 trialkylaluminum is added to a hydrocarbon medium suspension of a compound containing adsorbed water or a salt containing water of crystallization, e.g., magnesium chloride hydrate, copper sulfate hydrate, aluminum sulfate hydrate, nickel sulfate hydrate or  
15 cerous chloride hydrate, to allow the organoaluminum compound to react with the adsorbed water or the water of crystallization.

(2) Water, ice or water vapor is allowed to directly act on an organoaluminum compound such as  
20 trialkylaluminum in a medium such as benzene, toluene, ethyl ether or tetrahydrofuran.

(3) An organotin oxide such as dimethyltin oxide or dibutyltin oxide is allowed to react with an organoaluminum compound such as trialkylaluminum in a  
25 medium such as decane, benzene or toluene.

0944706-033404  
TOP SECRET

The aluminoxane may contain a small amount of an organometallic component. Further, it is possible that the solvent or the unreacted organoaluminum compound is distilled off from the recovered solution of aluminoxane and the remainder is redissolved in a solvent or suspended in a poor solvent for aluminoxane.

Examples of the organoaluminum compounds used for preparing the aluminoxane include the same organoaluminum compounds as described for the organoaluminum compound (B-1a).

Of these, preferable are trialkylaluminums and tricycloalkylaluminums. Particularly preferable is trimethylaluminum.

The organoaluminum compounds can be used singly or in combination of two or more kinds.


Examples of the solvents used for preparing the aluminoxane include aromatic hydrocarbons, such as benzene, toluene, xylene, cumene and cymene; aliphatic hydrocarbons, such as pentane, hexane, heptane, octane, decane, dodecane, hexadecane and octadecane; alicyclic hydrocarbons, such as cyclopentane, cyclohexane, cyclooctane and methylcyclopentane; petroleum fractions, such as gasoline, kerosine and gas oil; and halides of these aromatic, aliphatic and alicyclic hydrocarbons, particularly chlorides and bromides thereof. Also

00942706-033101

employable are ethers such as ethyl ether and tetrahydrofuran. Of the solvents, particularly preferable are aromatic hydrocarbons and aliphatic hydrocarbons.

- 5 In the benzene-insoluble organoaluminum oxy-compound for use in the invention, the content of Al component which is soluble in benzene at 60 °C is usually not more than 10 %, preferably not more than 5 %, particularly preferably not more than 2 %, in terms  
 10 of Al atom, and the benzene-insoluble organoaluminum oxy-compound is insoluble or sparingly soluble in benzene.

- The organoaluminum oxy-compound employable in the invention is, for example, an organoaluminum oxy-  
 15 compound containing boron and represented by the following formula (IV):



- 20 wherein R<sup>17</sup> is a hydrocarbon group of 1 to 10 carbon atoms; and each R<sup>18</sup> may be the same or different and is a hydrogen atom, a halogen atom or a hydrocarbon group of 1 to 10 carbon atoms.

The organoaluminum compound containing boron and represented by the formula (IV) can be prepared by causing an alkylboronic acid represented by the following formula (V) to react with an organoaluminum compound in an inert solvent under an inert gas atmosphere at a temperature of -80 °C to room temperature for 1 minute to 24 hours.



10

wherein  $R^{17}$  is the same group as described above.

Examples of the alkylboronic acids represented by the formula (V) include methylboronic acid, ethylboronic acid, isopropylboronic acid, n-propylboronic acid, n-butylboronic acid, isobutylboronic acid, n-hexylboronic acid, cyclohexylboronic acid, phenylboronic acid, 3,5-difluoroboronic acid, pentafluorophenylboronic acid and 3,5-bis(trifluoromethyl)phenylboronic acid. Of these, preferable are methylboronic acid, n-butylboronic acid, isobutylboronic acid, 3,5-difluorophenylboronic acid and pentafluorophenylboronic acid. The alkylboronic acids are used singly or in combination of two or more kinds.

20

Examples of the organoaluminum compounds to be reacted with the alkylboronic acid include the same

05942706-083404  
TOTAL 90224560

organoaluminum compounds as described for the  
organoaluminum compound (B-1a).

Of these, preferable are trialkylaluminums and  
tricycloalkylaluminums. Particularly preferable are  
5 trimethylaluminum, triethylaluminum and  
triisobutylaluminum. The organoaluminum compounds can  
be used singly or in combination of two or more kinds.

The organoaluminum oxy-compounds (B-2) mentioned  
above are used singly or in combination of two or more  
10 kinds.

(B-3) Compound which reacts with the transition metal  
compound to form ion pair


The compound (B-3) which reacts with the transition  
15 metal compound to form an ion pair (referred to as  
"ionizing ionic compound" hereinafter), that is used in  
the invention, is a compound which reacts with the  
transition metal compound (A) to form an ion pair, and  
includes Lewis acid, an ionic compound, a borane  
20 compound and a carborane compound described in Japanese  
Patent Laid-Open Publications No. 501950/1989, No.  
502036/1989, No. 179005/1991, No. 179006/1991, No.  
207703/1991 and No. 207704/1991, and U.S. Patent No.  
5,321,106. Further, as ionizing ionic compound,  
25 heteropoly-compound or isopoly-compound may be used.

0942706-003404  
TOTERO-9074650

The Lewis acid is, for example, a compound represented by  $BR_3$  (R is a phenyl group which may have a substituent such as fluorine, methyl or trifluoromethyl, or a fluorine atom). Examples of such compounds include

5 trifluoroboron, triphenylboron, tris(4-fluorophenyl)boron, tris(3,5-difluorophenyl)boron, tris(4-fluoromethylphenyl)boron, tris(pentafluorophenyl)boron, tris(p-tolyl)boron, tris(o-tolyl)boron and tris(3,5-dimethylphenyl)boron.

10 The ionic compound is, for example, a compound represented by the following formula (VI).



15 In the above formula,  $R^{19}$  is  $H^+$ , carbonium cation, oxonium cation, ammonium cation, phosphonium cation, cycloheptyltrienyl cation, ferrocenium cation having a transition metal, or the like.

$R^{20}$  to  $R^{23}$  may be the same or different, and are

20 each an organic group, preferably an aryl group or a substituted aryl group.

Examples of the carbonium cations include tri-substituted cations, such as triphenylcarbonium cation,

tri(methylphenyl)carbonium cation and  
tri(dimethylphenyl)carbonium cation.

Examples of the ammonium cations include  
trialkylammonium cations, such as trimethylammonium  
5 cation, triethylammonium cation, tripropylammonium  
cation and tributylammonium cation; N,N-dialkylanilinium  
cations, such as N,N-dimethylanilinium cation, N,N-  
diethylanilinium cation and N,N-2,4,6-  
pentamethylanilinium cation; and dialkylammonium  
10 cations, such as di(isopropyl)ammonium cation and  
dicyclohexylammonium cation.

Examples of the phosphonium cations include  
triarylphosphonium cations, such as triphenylphosphonium  
cation, tri(methylphenyl)phosphonium cation and  
15 tri(dimethylphenyl)phosphonium cation.

R<sup>19</sup> is preferably carbonium cation or ammonium  
cation, particularly preferably triphenylcarbonium  
cation, N,N-dimethylanilinium cation or N,N-  
diethylanilinium cation.

20 Also available as the ionic compound is a trialkyl-  
substituted ammonium salt, a N,N-dialkylanilinium salt,  
a dialkylammonium salt and a triarylphosphonium salt.

Examples of the trialkyl-substituted ammonium salts  
include triethylammoniumtetra(phenyl)boron,  
25 tripropylammoniumtetra(phenyl)boron, tri(n-

09442706-003404  
T0420-002450


butyl) ammoniumtetra(phenyl)boron,  
 trimethylammoniumtetra(p-tolyl)boron,  
 trimethylammoniumtetra(o-tolyl)boron, tri(n-  
 butyl) ammoniumtetra(pentafluorophenyl)boron,  
 5 tripropylammoniumtetra(o,p-dimethylphenyl)boron, tri(n-  
 butyl) ammoniumtetra(m,m-dimethylphenyl)boron, tri(n-  
 butyl) ammoniumtetra(p-trifluoromethylphenyl)boron,  
 tri(n-butyl) ammoniumtetra(3,5-  
 ditrifluoromethylphenyl)boron and tri(n-  
 10 butyl) ammoniumtetra(o-tolyl)boron.

Examples of the N,N-dialkylanilinium salts include  
 N,N-dimethylaniliniumtetra(phenyl)boron, N,N-  
 diethylaniliniumtetra(phenyl)boron and N,N-2,4,6-  
 pentamethylaniliniumtetra(phenyl)boron.

15 Examples of the dialkylammonium salts include di(1-  
 propyl) ammoniumtetra(pentafluorophenyl)boron and  
 dicyclohexylammoniumtetra(phenyl)boron.


Further employable as the ionic compound is  
 triphenylcarbeniumtetrakis(pentafluorophenyl)borate,  
 20 N,N-dimethylaniliniumtetrakis(pentafluorophenyl)borate,  
 ferroceniumtetra(pentafluorophenyl)borate,  
 triphenylcarbeniumpentaphenylcyclopentadienyl complex,  
 N,N-diethylaniliniumpentaphenylcyclopentadienyl complex  
 or a boron compound represented by the following formula  
 25 (VII) or (VIII).





wherein Et is an ethyl group.

5



Examples of the borane compounds include:

decaborane(14);

10

salts of anions, such as bis[tri(n-

butyl)ammonium]nonaborate, bis[tri(n-

butyl)ammonium]decaborate, bis[tri(n-butyl)ammonium]

undecaborate, bis[tri(n-butyl)ammonium]dodecaborate,

bis[tri(n-butyl)ammonium]decachlorodecaborate and

15

bis[tri(n-butyl)ammonium]dodecachlorododecaborate; and

salts of metallic borane anions, such as tri(n-

butyl)ammoniumbis(dodecahydridedodecaborate)cobaltate(II

I) and bis[tri(n-butyl)ammonium]bis-

(dodecahydridedodecaborate)nickelate(III).

20

Examples of the carborane compounds include:

- salts of anions, such as 4-carbanonaborane(14),  
 1,3-dicarbanonaborane(13), 6,9-dicarbadecaborane(14),  
 dodecahydride-1-phenyl-1,3-dicarbanonaborane,  
 dodecahydride-1-methyl-1,3-dicarbanonaborane,  
 5 undecahydride-1,3-dimethyl-1,3-dicarbanonaborane, 7,8-  
 dicarbaundecaborane(13), 2,7-dicarbaundecaborane(13),  
 undecahydride-7,8-dimethyl-7,8-dicarbaundecaborane,  
 dodecahydride-11-methyl-2,7-dicarbaundecaborane, tri(n-  
 butyl)ammonium-1-carbadecaborate, tri(n-butyl)ammonium-  
 10 1-carbaundecaborate, tri(n-butyl)ammonium-1-  
 carbadodecaborate, tri(n-butyl)ammonium-1-  
 trimethylsilyl-1-carbadecaborate, tri(n-  
 butyl)ammoniumbromo-1-carbadodecaborate, tri(n-  
 butyl)ammonium-6-carbadecaborate(14), tri(n-  
 15 butyl)ammonium-6-carbadecaborate(12), tri(n-  
 butyl)ammonium-7-carbaundecaborate(13), tri(n-  
 butyl)ammonium-7,8-dicarbaundecaborate(12), tri(n-  
 butyl)ammonium-2,9-dicarbaundecaborate(12), tri(n-  
 butyl)ammoniumdodecahydride-8-methyl-7,9-  
 20 dicarbaundecaborate, tri(n-butyl)ammoniumundecahydride-  
 8-ethyl-7,9-dicarbaundecaborate, tri(n-  
 butyl)ammoniumundecahydride-8-butyl-7,9-  
 dicarbaundecaborate, tri(n-butyl)ammoniumundecahydride-  
 8-allyl-7,9-dicarbaundecaborate, tri(n-  
 25 butyl)ammoniumundecahydride-9-trimethylsilyl-7,8-

00042706-003101  
 TOP SECRET

dicarbaundecaborate and tri(n-butyl) ammoniumundecahydride-4,6-dibromo-7-carbaundecaborate; and

salts of metallic carborane anions, such as tri(n-

- 5 butyl) ammoniumbis(nonahydride-1,3-dicarbonaborate)cobaltate(III), tri(n-butyl) ammoniumbis(undecahydride-7,8-dicarbaundecaborate)ferrate(III), tri(n-butyl) ammoniumbis(undecahydride-7,8-
- 10 dicarbaundecaborate)cobaltate(III), tri(n-butyl) ammoniumbis(undecahydride-7,8-dicarbaundecaborate)nickelate(III), tri(n-butyl) ammoniumbis(undecahydride-7,8-dicarbaundecaborate)cuprate(III), tri(n-
- 15 butyl) ammoniumbis(undecahydride-7,8-dicarbaundecaborate)aurate(III), tri(n-butyl) ammoniumbis(nonahydride-7,8-dimethyl-7,8-dicarbaundecaborate)ferrate(III), tri(n-
- 20 butyl) ammoniumbis(nonahydride-7,8-dimethyl-7,8-dicarbaundecaborate)chromate(III), tri(n-butyl) ammoniumbis(tribromooctahydride-7,8-dicarbaundecaborate)cobaltate(III), tris[tri(n-
- butyl) ammonium]bis(undecahydride-7-carbaundecaborate)chromate(III), bis[tri(n-
- 25 butyl) ammonium]bis(undecahydride-7-

0094706-00101  
TOTAL 90/3460

carbaundecaborate)manganate(IV), bis[tri(n-butyl) ammonium]bis(undecahydride-7-carbaundecaborate)cobaltate(III) and bis[tri(n-butyl) ammonium]bis(undecahydride-7-

5 carbaundecaborate)nickelate(IV).

The heteropoly-compounds comprise a heteroatom such as silicon, phosphorus, titanium, germanium, arsenic or tin, and at least one polyatom selected from vanadium, niobium molybdenum and tungsten. For example,

- 10 phosphovanadic acid, germanovanadic acid, arsenovanadic acid, phosphoniobic acid, germanoniobic acid, siliconomolybdic acid, phosphomolybdic acid, titanomolybdic acid, germanomolybdic acid, arsenomolybdic acid, stannomolybdic acid,
- 15 phosphotungstic acid, germanotungstic acid, stannotungstic acid, phosphomolybdovanadic acid, phosphotungstovanadic acid, germanotungstovanadic acid, phosphomolybdotungstovanadic acid, germanomolybdotungstovanadic acid,
- 20 phosphomolybdotungstic acid and phosphomolybdoniobic acid, salts of these acid with a metal of Group 1 or 2 of the periodic table such as lithium, sodium, potassium, rubidium, cesium, beryllium, magnesium, calcium, strontium or barium, and further organic salts
- 25 such as triphenylethyl salts of the above acids, as well as isopoly-compounds, but not limited thereto.

The heteropoly-compounds and isopoly-compounds mentioned above may be used singly or in combination of two or more kind.

The ionizing ionic compounds (B-3) mentioned above  
5 can be used singly or in combination of two or more kinds.

If the transition metal compounds according to the invention are used as catalyst in combination with the organoaluminum oxy-compound (B-2) such as  
10 methylaluminoxane as a cocatalyst, olefin compounds can be polymerized with high polymerization activities. If the ionized ionic compound (B-3) such as triphenylcarbonium tetrakis(pentafluorophenyl)borate is used as a cocatalyst, polyolefins having a very high  
15 molecular weight is produced with good activities.

In the olefin polymerization catalyst of the invention, the below-described carrier (C) can be used if necessary, in addition to the above-mentioned transition metal compound (A) and at least one compound  
20 (B) selected from the organometallic compound (B-1), the organoaluminum oxy-compound (B-2) and the ionized ionic compound (B-3).

(C) Carrier

0942706-083401

The carrier (C) for use in the invention is an inorganic or organic compound in the form of granular or particulate solid. As the inorganic compound, porous oxide, inorganic chloride, clay, clay mineral or an ion-exchange layered compound is preferable.

Examples of the porous oxides include  $\text{SiO}_2$ ,  $\text{Al}_2\text{O}_3$ ,  $\text{MgO}$ ,  $\text{ZrO}$ ,  $\text{TiO}_2$ ,  $\text{B}_2\text{O}_3$ ,  $\text{CaO}$ ,  $\text{ZnO}$ ,  $\text{BaO}$ ,  $\text{ThO}_2$ ; and mixtures containing these oxides, such as  $\text{SiO}_2\text{-MgO}$ ,  $\text{SiO}_2\text{-Al}_2\text{O}_3$ ,  $\text{SiO}_2\text{-TiO}_2$ ,  $\text{SiO}_2\text{-V}_2\text{O}_5$ ,  $\text{SiO}_2\text{-Cr}_2\text{O}_3$  and  $\text{SiO}_2\text{-TiO}_2\text{-MgO}$ .

Preferable are compounds each containing at least one of  $\text{SiO}_2$  and  $\text{Al}_2\text{O}_3$  as the main component.

The inorganic oxides may contain a small amount of carbonate, sulfate, nitrate or oxide component, such as  $\text{Na}_2\text{CO}_3$ ,  $\text{K}_2\text{CO}_3$ ,  $\text{CaCO}_3$ ,  $\text{MgCO}_3$ ,  $\text{Na}_2\text{SO}_4$ ,  $\text{Al}_2(\text{SO}_4)_3$ ,  $\text{BaSO}_4$ ,  $\text{KNO}_3$ ,  $\text{Mg}(\text{NO}_3)_2$ ,  $\text{Al}(\text{NO}_3)_3$ ,  $\text{Na}_2\text{O}$ ,  $\text{K}_2\text{O}$  or  $\text{Li}_2\text{O}$ .

Though the porous oxides differ in their properties depending on the type and the preparation process thereof, the carrier preferably used in the invention has a particle diameter of 10 to 300  $\mu\text{m}$ , preferably 20 to 200  $\mu\text{m}$ , a specific surface area of 50 to 1,000  $\text{m}^2/\text{g}$ , preferably 100 to 700  $\text{m}^2/\text{g}$ , and a pore volume of 0.3 to 3.0  $\text{cm}^3/\text{g}$ . The carrier can be used after calcined at 100 to 1,000  $^\circ\text{C}$ , preferably 150 to 700  $^\circ\text{C}$ , if desired.

Examples of the inorganic chlorides employable in the invention include  $\text{MgCl}_2$ ,  $\text{MgBr}_2$ ,  $\text{MnCl}_2$  and  $\text{MnBr}_2$ . In

the invention, the inorganic chloride may be used as it is, or can be used after pulverized by a ball mill, a vibration mill or the like. The inorganic chloride can be used as fine particles of a precipitate obtained by  
5 dissolving the inorganic chloride in a solvent such as alcohol and then precipitating using precipitating agent.

09442706-003404  
TOP SECRET

The clay for use in the invention is generally constituted mainly of clay mineral. The ion-exchange  
10 layered-compound is a compound having a crystal structure wherein planes formed by ionic bonding or the like are laminated in parallel to each other with a weak bond strength, and the ions contained therein are exchangeable. Most of clay minerals are ion-exchange  
15 layered compounds. As the clay, the clay minerals and the ion-exchange layered compounds, not only natural ones but also synthetic ones are employable.

Examples of such clay, clay minerals and ion-exchange layered compounds include clay, clay minerals  
20 and ion crystalline compounds having layered crystal structures such as hexagonal closest packing type, antimony type,  $\text{CdCl}_2$  type and  $\text{CdI}_2$  type.

Particular examples of the clay and the clay minerals include kaolin, bentonite, kibushi clay,  
25 gairome clay, allophane, hisingerite, pyrophyllite,

mica, montmorillonite, vermiculite, chlorite,  
 palygorskite, kaolinite, nacrite, dickite and  
 halloysite. Particular examples of the ion-exchange  
 layered compounds include crystalline acid salts of  
 5 polyvalent metals, such as  $\alpha\text{-Zr(HAsO}_4)_2 \cdot \text{H}_2\text{O}$ ,  $\alpha\text{-Zr(HPO}_4)_2$ ,  
 $\alpha\text{-Zr(KPO}_4)_2 \cdot 3\text{H}_2\text{O}$ ,  $\alpha\text{-Ti(HPO}_4)_2$ ,  $\alpha\text{-Ti(HAsO}_4)_2 \cdot \text{H}_2\text{O}$ ,  $\alpha\text{-}$   
 $\text{Sn(HPO}_4)_2 \cdot \text{H}_2\text{O}$ ,  $\gamma\text{-Zr(HPO}_4)_2$ ,  $\gamma\text{-Ti(HPO}_4)_2$  and  $\gamma\text{-}$   
 $\text{Ti(NH}_4\text{PO}_4)_2 \cdot \text{H}_2\text{O}$ .

As the clay, the clay minerals and the ion-exchange  
 10 layered compounds, preferable are those having a pore  
 volume, as measured on pores having a radius of not less  
 than 20 Å by a mercury penetration method, of not less  
 than 0.1 cc/g, and particularly preferable are those  
 having a pore volume of 0.3 to 5 cc/g. The pore volume  
 15 is measured on the pores having a radius of 20 to  $3 \times 10^4$  Å by a mercury penetration method using a mercury  
 porosimeter. When a compound having a pore volume, as  
 measured on pores having a radius of not less than 20 Å,  
 of less than 0.1 cc/g is used, high polymerization  
 20 activities are apt to be hardly obtained.

It is preferable that the clay and the clay  
 minerals for use in the invention are subjected to  
 chemical treatments. A surface treatment to remove  
 impurities attached to the surface and a treatment  
 25 having an influence on the crystal structure of the clay



are both available. Examples of such treatments include acid treatment, alkali treatment, salt treatment and organic matter treatment. The acid treatment contributes to not only removing impurities from the surface but also eluting cations such as Al, Fe and Mg present in the crystal structure to thereby increase the surface area. The alkali treatment destroys the crystal structure of clay to bring about change in the structure of the clay. The salt treatment and the organic matter treatment can produce ionic complex, molecular complex or organic derivative to change the surface area or the distance between layers.

In the ion-exchange layered compound for use in the invention, the exchangeable ions between layers can be exchanged with other large and bulky ions utilizing ion exchange properties, whereby a layered compound having enlarged distance between layers can be obtained. That is, the bulky ion plays a pillar-like roll to support the layer structure and is called a "pillar".

Introduction of other substances between layers of a layered material is called "intercalation".

Examples of the guest compounds to be intercalated include cationic inorganic compounds, such as  $\text{TiCl}_4$  and  $\text{ZrCl}_4$ ; metallic alcoholates, such as  $\text{Ti(OR)}_4$ ,  $\text{Zr(OR)}_4$ ,  $\text{PO(OR)}_3$  and  $\text{B(OR)}_3$  (R is a hydrocarbon group or the

094706-083404

like); and metallic hydroxide ions, such as  
 $[Al_{13}O_4(OH)_{24}]^{7+}$ ,  $[Zr_4(OH)_{14}]^{2+}$  and  $[Fe_3O(OCOCH_3)_6]^+$ . These  
 compounds can be used singly or in combination of two or  
 more kinds. Intercalation of these compounds can be  
 5 carried out in the presence of polymers obtained by  
 hydrolysis of metallic alcoholates such as  $Si(OR)_4$ ,  
 $Al(OR)_3$  and  $Ge(OR)_4$  (R is a hydrocarbon group or the  
 like) or in the presence of colloidal inorganic  
 compounds such as  $SiO_2$ . Examples of the pillars include  
 10 oxides produced by intercalation of the above-mentioned  
 hydroxide ions between layers and then dehydration under  
 heating.

The clay, clay minerals and the ion-exchange  
 layered compounds mentioned above may be used as they  
 15 are, or may be used after subjected to a treatment of  
 ball milling, sieving or the like.. Moreover, they may  
 be used after subjected to water adsorption or  
 dehydration under heating. The clay, clay minerals and  
 the ion-exchange layered compounds may be used singly or  
 20 in combination of two or more kinds.

Of the above-mentioned materials, preferable are  
 clay and clay minerals, and particularly preferable are  
 montmorillonite, vermiculite, pectolite, teniolite and  
 synthetic mica.

The organic compound is, for example, a granular or particulate organic compound having a particle diameter of 10 to 300  $\mu\text{m}$ . Examples of such compounds include (co)polymers produced using, as main components,  $\alpha$ -

5   olefins of 2 to 14 carbon atoms such as ethylene, propylene, 1-butene and 4-methyl-1-pentene, (co)polymers produced using, as a main component, vinylcyclohexane or styrene, and modified products thereof.

10   In the olefin polymerization catalyst of the invention, the below-described specific organic compound (D) can be used if necessary, in addition to the transition metal compound (A), at least one compound (B) selected from the organometallic compound (B-1), the organoaluminum oxy-compound (B-2) and the ionized ionic  
15   compound (B-3), and the fine particle carrier (C).

(D) Organic compound component

20   The organic compound component which can be used if necessary functions to improve polymerizability and properties of the resulting polymers. Examples of the organic compounds include alcohol, a phenolic compound, a carboxylic acid, a phosphorus compound and sulfonate, but the organic compound employable in the invention is not limited thereto.


09942706-003404

The alcohol and the phenolic compound are represented by  $R^{31}-OH$  wherein  $R^{31}$  is a hydrocarbon group of 1 to 50 carbon atoms or a halogenated hydrocarbon group of 1 to 50 carbon atoms. The alcohol is preferably a halogen atom-containing hydrocarbon. The phenolic compound is preferably a phenolic compound wherein the  $\alpha, \alpha'$ -position of the hydroxyl group is substituted with a hydrocarbon group of 1 to 20 carbon atoms.

10 The carboxylic acid is represented by  $R^{32}-COOH$  wherein  $R^{32}$  is a hydrocarbon group of 1 to 50 carbon atoms or a halogenated hydrocarbon group of 1 to 50 carbon atoms, preferably a halogenated hydrocarbon group of 1 to 50 carbon atoms.

15 Preferred examples of the phosphorus compounds include phosphoric acids having P-O-H bond, phosphates having P-OR bond or P=O bond, and phosphine oxide compounds.

The sulfonate is represented by the following  
20 formula (IX):



wherein M is an atom of Group 1 to Group 14 of the periodic table;  $R^{33}$  is a hydrocarbon group of 1 to 20 carbon atoms or a halogenated hydrocarbon group of 1 to 20 carbon atoms; X is a hydrogen atom, a halogen atom, a hydrocarbon group of 1 to 20 carbon atoms or a halogenated hydrocarbon group of 1 to 20 carbon atoms; m is an integer of 1 to 7; and  $n \leq 7$ .

Fig. 1 shows steps for preparing the first olefin polymerization catalyst according to the invention.

In the polymerization, the components can be used in any way and in any order. Some examples of the processes are given below.

(1) The component (A) and at least one component (B) selected from the organometallic compound (B-1), the organoaluminum oxy-compound (B-2) and the ionized ionic compound (B-3) (referred to simply as "component (B)" hereinafter) are fed to the polymerization reactor in an arbitrary order.

(2) A catalyst obtained by previously contacting the component (A) with the component (B) is fed to the polymerization reactor.

(3) A catalyst component obtained by previously contacting the component (A) with the component (B), and the component (B) are fed to the polymerization reactor

in an arbitrary order. In this case, the components (B) may be the same or different.

(4) A catalyst component wherein the component (A) is supported on the carrier (C), and the component (B) are fed to the polymerization reactor in an arbitrary order.

(5) A catalyst component wherein the component (A) and the component (B) are supported on the carrier (C) is fed to the polymerization reactor.

(6) A catalyst component wherein the component (A) and the component (B) are supported on the carrier (C), and the component (B) are fed to the polymerization reactor in an arbitrary order. In this case, the components (B) may be the same or different.

(7) A catalyst component wherein the component (B) is supported on the carrier (C), and the component (A) are fed to the polymerization reactor in an arbitrary order.

(8) A catalyst component wherein the component (B) is supported on the carrier (C), the component (A) and the component (B) are fed to the polymerization reactor in an arbitrary order. In this case, the components (B) may be the same or different.

(9) A component wherein the component (A) is supported on the carrier (C) and a component wherein the

0944706-03401

component (B) is supported on the carrier (C) are fed to the polymerization reactor in an arbitrary order.

(10) A component wherein the component (A) is supported on the carrier (C), a component wherein the component (B) is supported on the component (C), and the component (B) are fed to the polymerization reactor in an arbitrary order. In this case, the components (B) may be the same or different.

(11) The component (A), the component (B) and the organic compound component (D) are fed to the polymerization reactor in an arbitrary order.

(12) A component obtained by previously contacting the component (B) with the component (D), and the component (A) are fed to the polymerization reactor in an arbitrary order.

(13) A component wherein the component (B) and the component (D) are supported on the carrier (C), and the component (A) are fed to the polymerization reactor in an arbitrary order.

(14) A catalyst component obtained by previously contacting the component (A) with the component (B), and the component (D) are fed to the polymerization reactor in an arbitrary order.

(15) A catalyst component obtained by previously contacting the component (A) with the component (B), the

00942706-083101

component (B) and the component (D) are fed to the polymerization reactor in an arbitrary order.

(16) A catalyst component obtained by previously contacting the component (A) with the component (B), and  
5 a component obtained by previously contacting the component (B) with the component (D) are fed to the polymerization reactor in an arbitrary order.

(17) A component wherein the component (A) is supported on the carrier (C), the component (B) and the  
10 component (D) are fed to the polymerization reactor in an arbitrary order.

(18) A component wherein the component (A) is supported on the carrier (C) and a component obtained by contacting the component (B) with the component (D) are  
15 fed to the polymerization reactor in an arbitrary order.

(19) A catalyst component obtained by previously contacting the component (A), the component (B) and the component (D) with each other is fed to the polymerization reactor.

20 (20) A catalyst component which is obtained by previously contacting the component (A), the component (B) and the component (D) with each other, and the component (B) are fed to the polymerization reactor in an arbitrary order. In this case, the components (B)  
25 may be the same or different.



(21) A catalyst component wherein the component (A), the component (B) and the component (D) are supported on the carrier (C) is fed to the polymerization reactor.

- 5 (22) A catalyst component wherein the component (A), the component (B) and the component (D) are supported on the carrier (C), and the component (B) are fed to the polymerization reactor in an arbitrary order. In this case, the components (B) may be the same or  
10 different.

An olefin may be prepolymerized onto the solid catalyst component wherein the component (A) and the component (B) are supported on the carrier (C).

- In the process for olefin polymerization according  
15 to the invention, an olefin is polymerized or copolymerized in the presence of the above-described olefin polymerization catalyst to obtain an olefin polymer.

- In the present invention, the polymerization can be  
20 carried out as any of liquid phase polymerization, such as solution polymerization or suspension polymerization, and gas phase polymerization.

- Examples of the inert hydrocarbon media used in the liquid phase polymerization include aliphatic  
25 hydrocarbons, such as propane, butane, pentane, hexane,

heptane octane, decane, dodecane and kerosine; alicyclic hydrocarbons, such as cyclopentane, cyclohexane and methylcyclopentane; aromatic hydrocarbons, such as benzene, toluene and xylene; halogenated hydrocarbons, such as ethylene chloride, chlorobenzene and dichloromethane; and mixtures of these hydrocarbons. The olefin itself can be used as the solvent.

In the polymerization of an olefin using the olefin polymerization catalyst, the component (A) is used in an amount of usually  $10^{-12}$  to  $10^{-2}$  mol, preferably  $10^{-10}$  to  $10^{-3}$  mol, based on 1 liter of the reaction volume. In the present invention, an olefin can be polymerized with high polymerization activities, even if the component (A) is used in a relatively low concentration.

The component (B-1) is used in such an amount that the molar ratio of the component (B-1) to the transition metal atom (M) in the component (A)  $((B-1)/(M))$  becomes usually 0.01 to 100,000, preferably 0.05 to 50,000. The component (B-2) is used in such an amount that the molar ratio of the aluminum atom in the component (B-2) to the transition metal atom (M) in the component (A)  $((B-2)/(M))$  becomes usually 10 to 500,000, preferably 20 to 100,000. The component (B-3) is used in such an amount that the molar ratio of the component (B-3) to the

transition metal atom (M) in the component (A) ((B-3)/(M)) becomes usually 1 to 10, preferably 1 to 5.

The ratio of the component (D) to the component (B) is as follows. When the component (B) is the component (B-1), the component (D) is used in such an amount that the (D)/(B-1) ratio by mol becomes 0.01 to 10, preferably 0.1 to 5. When the component (B) is the component (B-2), the component (D) is used in such an amount that the molar ratio of the component (D) to the aluminum atom in the component (B-2) ((D)/(B-2)) becomes 0.001 to 2, preferably 0.005 to 1. When the component (B) is the component (B-3), the component (D) is used in such an amount that the (D)/(B-3) ratio by mol becomes 0.01 to 10, preferably 0.1 to 5.

The temperature for the olefin polymerization using the olefin polymerization catalyst is in the range of usually -50 to 200 °C, preferably 0 to 170 °C. The polymerization pressure is in the range of usually atmospheric pressure to 100 kg/cm<sup>2</sup>, preferably atmospheric pressure to 50 kg/cm<sup>2</sup>. The polymerization reaction can be carried out by any of batchwise, semi-continuous and continuous processes. The polymerization can be conducted in two or more stages under different reaction conditions.

The molecular weight of the resulting polymer can be adjusted by allowing hydrogen to exist in the polymerization system or by varying the polymerization temperature. Further, the molecular weight can be  
5 adjusted also by using the component (B) of different type.

Examples of the olefins which can be polymerized using the olefin polymerization catalyst include:

straight-chain or branched  $\alpha$ -olefins of 2 to 30,  
10 preferably 3 to 20 carbon atoms, such as ethylene, propylene, 1-butene, 1-pentene, 3-methyl-1-butene, 1-hexene, 4-methyl-1-pentene, 3-methyl-1-pentene, 1-octene, 1-decene, 1-dodecene, 1-tetradecene, 1-hexadecene, 1-octadecene and 1-eicosene; and  
15 cycloolefins of 3 to 30, preferably 3 to 20 carbon atoms, such as cyclopentene, cycloheptene, norbornene, 5-methyl-2-norbornene, tetracyclododecene and 2-methyl-1,4,5,8-dimethano-1,2,3,4,4a,5,8,8a-octahydronaphthalene.

20 Also employable are polar monomers. Examples of such monomers include  $\alpha,\beta$ -unsaturated carboxylic acids, such as acrylic acid, methacrylic acid, fumaric acid, maleic anhydride, itaconic acid, itaconic anhydride and bicyclo(2,2,1)-5-heptene-2,3-dicarboxylic acid; metallic  
25 salts of these acids, such as sodium salts, potassium

salts, lithium salts, zinc salts, magnesium salts and calcium salts;  $\alpha,\beta$ -unsaturated carboxylic esters, such as methyl acrylate, ethyl acrylate, n-propyl acrylate, isopropyl acrylate, n-butyl acrylate, isobutyl acrylate, 5 tert-butyl acrylate, 2-ethylhexyl acrylate, methyl methacrylate, ethyl methacrylate, n-propyl methacrylate, isopropyl methacrylate, n-butyl methacrylate and isobutyl methacrylate; vinyl esters, such as vinyl acetate, vinyl propionate, vinyl caproate, vinyl 10 caprate, vinyl laurate, vinyl stearate and vinyl trifluoroacetate; and unsaturated glycidyl esters, such as glycidyl acrylate, glycidyl methacrylate and monoglycidyl itaconate. Furthermore, vinylcyclohexane, diene, polyene and the like are also employable. The 15 diene and the polyene are cyclic or chain compounds having 4 to 30, preferably 4 to 20 carbon atoms and having two or more double bonds. Examples of such compounds include butadiene, isoprene, 4-methyl-1,3-pentadiene, 1,3-pentadiene, 1,4-pentadiene, 1,5- 20 hexadiene, 1,4-hexadiene, 1,3-hexadiene, 1,3-octadiene, 1,4-octadiene, 1,5-octadiene, 1,6-octadiene, 1,7-octadiene, ethylidene norbornene, vinyl norbornene and dicyclopentadiene;

7-methyl-1,6-octadiene, 4-ethylidene-8-methyl-1,7- 25 nonadiene, 5,9-dimethyl-1,4,8-decatriene; and further

aromatic vinyl compounds such as mono or poly alkylstyrenes (e.g., styrene, o-methylstyrene, m-methylstyrene, p-methylstyrene, o,p-dimethylstyrene, o-ethylstyrene, m-ethylstyrene and p-ethylstyrene),  
5 functional group-containing styrene derivatives (e.g., methoxystyrene, ethoxystyrene, vinylbenzoic acid, methyl vinylbenzoate, vinylbenzyl acetate, hydroxystyrene, o-chlorostyrene, p-chlorostyrene and divinylbenzene); and  
3-phenylpropylene, 4-phenylpropylene and  $\alpha$ -  
10 methylstyrene.

The olefin polymerization catalyst of the invention exhibits high polymerization activities, and by the use of the catalyst, polymers of narrow molecular weight distribution can be obtained. When two or more kinds of  
15 olefins are used, olefin copolymers of narrow composition distribution can be obtained.

The olefin polymerization catalyst of the invention can be used also for the copolymerization of an  $\alpha$ -olefin and a conjugated diene.

20 Examples of the  $\alpha$ -olefins used herein include the same straight-chain or branched  $\alpha$ -olefins of 2 to 30, preferably 2 to 20 carbon atoms as described above. Of these, preferable are ethylene, propylene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene and 1-octene.  
25 Particularly preferable are ethylene and propylene.

These  $\alpha$ -olefins can be used singly or in combination or two or more kinds.

Examples of the conjugated dienes include aliphatic conjugated dienes of 4 to 30, preferably 4 to 20 carbon atoms, such as 1,3-butadiene, isoprene, chloroprene, 1,3-cyclohexadiene, 1,3-pentadiene, 4-methyl-1,3-pentadiene, 1,3-hexadiene and 1,3-octadiene. These conjugated dienes can be used singly or in combination of two or more kinds.

10 In the copolymerization of the  $\alpha$ -olefin and the conjugated diene, non-conjugated diene or polyene is further employable, and examples thereof include 1,4-pentadiene, 1,5-hexadiene, 1,4-hexadiene, 1,4-octadiene, 1,5-octadiene, 1,6-octadiene, 1,7-octadiene, ethylidene  
15 norbornene, vinyl norbornene, dicyclopentadiene, 7-methyl-1,6-octadiene, 4-ethylidene-8-methyl-1,7-nonadiene, 5,9-dimethyl-1,4,8-decatriene.

#### Second olefin polymerization catalyst

20 The second olefin polymerization catalyst according to the invention is formed from:

(A') a transition metal compound represented by the below-described formula (II), and

(B) at least one compound selected from:

25 (B-1) an organometallic compound,


(B-2) an organoaluminum oxy-compound, and

(B-3) a compound which reacts with the transition metal compound (A') to form an ion pair.

First, the components for forming the olefin  
5 polymerization catalyst of the invention are described.

(A') Transition metal compound

The transition metal compound (A') for use in the invention is a transition metal compound represented by  
10 the following formula (II):



wherein M is a transition metal atom of Group 3 to Group  
15 11 of the periodic table,

R<sup>1</sup> to R<sup>10</sup> may be the same or different, and are each a hydrogen atom, a halogen atom, a hydrocarbon group, a heterocyclic compound residue, an oxygen-containing group, a nitrogen-containing group, a boron-containing  
20 group, a sulfur-containing group, a phosphorus-containing group, a silicon-containing group, a germanium-containing group or a tin-containing group,



and two or more of them may be bonded to each other to form a ring,

n is a number satisfying a valence of M,

X is a hydrogen atom, a halogen atom, a hydrocarbon group, an oxygen-containing group, a sulfur-containing group, a nitrogen-containing group, a boron-containing group, an aluminum-containing group, a phosphorus-containing group, a halogen-containing group, a heterocyclic compound residue, a silicon-containing group, a germanium-containing group or a tin-containing group, and when n is 2 or greater, plural groups X may be the same or different and may be bonded to each other to form a ring, and


Y is a divalent bonding group containing at least one element selected from the group consisting of oxygen, sulfur, carbon, nitrogen, phosphorus, silicon, selenium, tin and boron, and when it is a hydrocarbon group, the hydrocarbon group has 3 or more carbon atoms.

It is preferable that at least one of  $R^6$  and  $R^{10}$ , especially both of them, in the formula (II) is a halogen atom, a hydrocarbon group, a heterocyclic compound residue, an oxygen-containing group, a nitrogen-containing group, a boron-containing group, a sulfur-containing group, a phosphorus-containing group,

a silicon-containing group, a germanium-containing group or a tin-containing group.

As M, R<sup>1</sup> to R<sup>10</sup> and X in the formula (II), there can be used the same groups as mentioned for M, R<sup>1</sup> to R<sup>6</sup> and X in the formula(I), respectively. Specific examples of Y are described later on.

The transition metal compound represented by the formula (II) is preferably a transition metal compound represented by the following formula (II-a):



wherein M is a transition metal atom of Group 3 to Group 11, preferably Group 4 or 5, more preferably Group 4, of the periodic table, for example titanium, zirconium and hafnium, especially titanium.

R<sup>1</sup> to R<sup>10</sup> may be the same or different, and are each a hydrogen atom, a halogen atom, a hydrocarbon group, a hydrocarbon-substituted silyl group, an alkoxy group, an aryloxy group, an ester group, an amido group, an amino group, a sulfonamido group, a cyano group or a nitro

group, and two or more of them may be bonded to each other to form a ring,

n is a number satisfying a valence of M, usually an integer of 0 to 4, preferably 1 to 4, more preferably 1 to 3.

X is a hydrogen atom, a halogen atom, a hydrocarbon group of 1 to 20 carbon atoms, an oxygen-containing group, a sulfur-containing group or a silicon-containing group, and when n is 2 or greater, plural groups may be the same or different and may be bonded to each other to form a ring.

Y is a divalent bonding group containing at least one element selected from the group consisting of oxygen, sulfur, carbon, nitrogen, phosphorus, silicon, selenium, tin and boron, and when it is a hydrocarbon group, the hydrocarbon group has 3 or more carbon atoms.

The main chain of the bonding group Y has a structure comprising preferably 3 to 40, more preferably 4 to 10 atoms. The bonding group may have a substituent.

It is preferable that at least one of  $R^6$  and  $R^{10}$ , preferably both of them in the formula (II-a) is a halogen atom, a hydrocarbon group, a hydrocarbon-substituted silyl group, an alkoxy group, an aryloxy

group, an ester group, an amido group, an amino group, a sulfonamido group, a cyano group or a nitro group.

Specific examples of X and  $R^1$  to  $R^{10}$  in the formula (II-a) are the same as mentioned for X and  $R^1$  to  $R^6$  in the formulae (I) and (I-a). X is particularly preferably a halogen atom, a hydrocarbon group of 1 to 20 carbon atoms or a sulfinato group. When n is 2 or greater, plural groups X may be bonded to each other to form a ring such as an aromatic ring or an aliphatic ring.


Specific examples of the divalent bonding groups include chalcogen atoms, such as -O-, -S- and -Se-; nitrogen- or phosphorus-containing groups, such as -NH-, -N(CH<sub>3</sub>)-, -PH- and -P(CH<sub>3</sub>)-; silicon atom-containing groups, such as -SiH<sub>2</sub>- and -Si(CH<sub>3</sub>)<sub>2</sub>; tin atom-containing groups, such as -SnH<sub>2</sub>- and -Sn(CH<sub>3</sub>)<sub>2</sub>; and boron atom-containing groups, such as -BH-, -B(CH<sub>3</sub>) and -BF.


Examples of the hydrocarbon groups include saturated hydrocarbon groups of 3 to 20 carbon atoms, such as -(CH<sub>2</sub>)<sub>4</sub>-, -(CH<sub>2</sub>)<sub>5</sub>- and -(CH<sub>2</sub>)<sub>6</sub>-; cyclic saturated hydrocarbon groups, such as cyclohexylidene and cyclohexylene; groups wherein these saturated hydrocarbon groups are partially substituted with 1 to 10 groups or atoms selected from hydrocarbon groups, halogen atoms (e.g., fluorine, chlorine and bromine) and

5

10

	1970	1971	1972	1973	1974	1975	1976	1977	1978	1979	1980	1981	1982	1983	1984	1985	1986	1987	1988	1989	1990	1991	1992	1993	1994	1995	1996	1997	1998	1999	2000	2001	2002	2003	2004	2005	2006	2007	2008	2009	2010	2011	2012	2013	2014	2015	2016	2017	2018	2019	2020	2021	2022	2023	2024	2025	2026	2027	2028	2029	2030	2031	2032	2033	2034	2035	2036	2037	2038	2039	2040	2041	2042	2043	2044	2045	2046	2047	2048	2049	2050	2051	2052	2053	2054	2055	2056	2057	2058	2059	2060	2061	2062	2063	2064	2065	2066	2067	2068	2069	2070	2071	2072	2073	2074	2075	2076	2077	2078	2079	2080	2081	2082	2083	2084	2085	2086	2087	2088	2089	2090	2091	2092	2093	2094	2095	2096	2097	2098	2099	2100	2101	2102	2103	2104	2105	2106	2107	2108	2109	2110	2111	2112	2113	2114	2115	2116	2117	2118	2119	2120	2121	2122	2123	2124	2125	2126	2127	2128	2129	2130	2131	2132	2133	2134	2135	2136	2137	2138	2139	2140	2141	2142	2143	2144	2145	2146	2147	2148	2149	2150	2151	2152	2153	2154	2155	2156	2157	2158	2159	2160	2161	2162	2163	2164	2165	2166	2167	2168	2169	2170	2171	2172	2173	2174	2175	2176	2177	2178	2179	2180	2181	2182	2183	2184	2185	2186	2187	2188	2189	2190	2191	2192	2193	2194	2195	2196	2197	2198	2199	2200	2201	2202	2203	2204	2205	2206	2207	2208	2209	2210	2211	2212	2213	2214	2215	2216	2217	2218	2219	2220	2221	2222	2223	2224	2225	2226	2227	2228	2229	2230	2231	2232	2233	2234	2235	2236	2237	2238	2239	2240	2241	2242	2243	2244	2245	2246	2247	2248	2249	2250	2251	2252	2253	2254	2255	2256	2257	2258	2259	2260	2261	2262	2263	2264	2265	2266	2267	2268	2269	2270	2271	2272	2273	2274	2275	2276	2277	2278	2279	2280	2281	2282	2283	2284	2285	2286	2287	2288	2289	2290	2291	2292	2293	2294	2295	2296	2297	2298	2299	2300	2301	2302	2303	2304	2305	2306	2307	2308	2309	2310	2311	2312	2313	2314	2315	2316	2317	2318	2319	2320	2321	2322	2323	2324	2325	2326	2327	2328	2329	2330	2331	2332	2333	2334	2335	2336	2337	2338	2339	2340	2341	2342	2343	2344	2345	2346	2347	2348	2349	2350	2351	2352	2353	2354	2355	2356	2357	2358	2359	2360	2361	2362	2363	2364	2365	2366	2367	2368	2369	2370	2371	2372	2373	2374	2375	2376	2377	2378	2379	2380	2381	2382	2383	2384	2385	2386	2387	2388	2389	2390	2391	2392	2393	2394	2395	2396	2397	2398	2399	2400	2401	2402	2403	2404	2405	2406	2407	2408	2409	2410	2411	2412	2413	2414	2415	2416	2417	2418	2419	2420	2421	2422	2
--	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	---





In the above examples, Me is methyl, Ph is phenyl.

In the present invention, transition metal compounds wherein titanium is replaced with other metals than titanium, such as zirconium or hafnium, in the  
5 above-exemplified compounds are also employable.

In the second olefin polymerization catalyst according to the invention, the transition metal compound (A') can be used in combination with other transition metal compounds, as for the aforesaid  
10 transition metal compound (A). Examples of the other transition metal compounds include the aforesaid compounds (a-1) to (a-8).

In the second olefin polymerization catalyst according to the invention, examples of the  
15 organometallic compounds (B-1), the organoaluminum oxy-compounds (B-2) and the compounds which react with the transition metal compound (A') to form an ion pair include those previously described.

In the second olefin polymerization catalyst  
20 according to the invention, the aforesaid carrier (C) can be used if necessary, in addition to the above-mentioned transition metal compound (A') and at least one compound (B) selected from the organometallic compound (B-1), the organoaluminum oxy-compound (B-2)  
25 and the ionized ionic compound (B-3), as in the first




olefin polymerization catalyst. Further, the aforesaid specific organic compound (D) can also be used if necessary.

Fig. 2 shows steps for preparing the second olefin polymerization catalyst according to the invention.

The second olefin polymerization catalyst according to the invention can be used for polymerizing the same olefins under the same conditions as described for the first olefin polymerization catalyst.

#### Novel transition metal compound

The novel transition metal compound according to the invention is represented by the following formula (III):



wherein M is a transition metal atom of Group 4 or Group 5 of the periodic table,

m is an integer of 1 to 3,

R<sup>1</sup> is a hydrocarbon group, a hydrocarbon-substituted silyl group, a hydrocarbon-substituted

siloxy group, an alkoxy group, an alkylthio group, an aryloxy group, an arylthio group, an ester group, a thioester group, a sulfonester group or a hydroxyl group,

- 5            $R^2$  to  $R^5$  may be the same or different, and are each a hydrogen atom, a halogen atom, a hydrocarbon group, a heterocyclic compound residue, a hydrocarbon-substituted silyl group, a hydrocarbon-substituted siloxy group, an alkoxy group, an alkylthio group, an aryloxy group, an
- 10   arylthio group, an ester group, a thioester group, an amido group, an imido group, an amino group, an imino group, a sulfonester group, a sulfonamido group, a cyano group, a nitro group, a carboxyl group, a sulfo group, a mercapto group or a hydroxyl group,
- 15            $R^6$  is a halogen atom, a hydrocarbon group, a hydrocarbon-substituted silyl group, a hydrocarbon-substituted siloxy group, an alkoxy group, an alkylthio group, an aryloxy group, an arylthio group, an ester group, a thioester group, an amido group, an imido
- 20   group, an imino group, a sulfonester group, a sulfonamido group or a cyano group,


two or more of  $R^1$  to  $R^6$  may be bonded to each other to form a ring,

when  $m$  is 2 or greater, two of the groups  $R^1$  to  $R^6$  may be bonded to each other, with the proviso that the groups  $R^1$  are not bonded to each other,

$n$  is a number satisfying a valence of  $M$ , and

5  $X$  is a halogen atom, a hydrocarbon group, an oxygen-containing group, a sulfur-containing group, a nitrogen-containing group, a boron-containing group, an aluminum-containing group, a phosphorus-containing group, a halogen-containing group, a heterocyclic  
10 compound residue, a silicon-containing group, a germanium-containing group or a tin-containing group, and when  $n$  is 2 or greater, plural groups  $X$  may be the same or different and may be bonded to each other to form a ring.

15 As the transition metal compound of the formula (III), preferable is a transition metal compound represented by the following formula (III-a).



(III-a)

In the formula (III-a), M is a transition metal atom of Group 4 or Group 5 of the periodic table, specifically titanium, zirconium, hafnium, vanadium, niobium or tantalum.

5        m is an integer of 1 to 3, preferably 2.

$R^1$  to  $R^5$  may be the same or different, and are each a hydrocarbon group, an alkoxy group or a hydrocarbon-substituted silyl group.

10         $R^6$  is a halogen atom, a hydrocarbon group, a hydrocarbon-substituted silyl group, an alkoxy group, an alkylthio group or a cyano group.

Two or more of  $R^1$  to  $R^6$  may be bonded to each other to form a ring.

15        When m is 2 or greater, two of the groups  $R^1$  to  $R^6$  may be bonded to each other, with the proviso that the groups  $R^1$  are not bonded to each other.

n is a number satisfying a valence of M.

20        X is a halogen atom, a hydrocarbon group, an oxygen-containing group, a sulfur-containing group, a nitrogen-containing group, halogen-containing group or a silicon-containing group.


25        Preferable X is a halogen atom, a hydrocarbon group of 1 to 20 carbon atoms, a halogenated hydrocarbon group of 1 to 20 carbon atoms, an oxygen-containing, a sulfur-containing group or a silicon containing group.




When  $n$  is 2 or greater, plural groups  $X$  may be the same or different and may be bonded to each other to form a ring.


Specific examples of  $R^1$  to  $R^6$  and  $X$  include those  
5 described for the above-mentioned formula (I).

Some examples of the novel transition metal compounds are given below.


137633 202460











General process for preparing transition metal compound

The transition metal compounds of the formulae (I), (II) and (III) can be prepared by any processes without specific limitation, for example, in the manner as

5 described below. First, the ligand composing the transition metal compound can be obtained by reacting a salicylaldehyde compound with a primary amine compound of the formula  $R^1-NH_2$  (where  $R^1$  has the meanings as described above), for example an aniline compound or an  
10 alkylamine compound. In more detail, both starting compounds are dissolved in a solvent, for example those commonly used in such reactions, preferably alcohols such as methanol and ethanol, and hydrocarbon solvents such as toluene. The resulting solution is stirred for  
15 about 1 to 48 hours at room temperature to a reflux temperature to obtain the corresponding ligand in a good yield.

In the preparation of ligands, catalysts for example acid catalysts such as formic acid, acetic acid  
20 and toluenesulfonic acid can be used. In order to proceed the reaction effectively, it is also possible to use dehydrating agents such as molecular sieves, magnesium sulfate and sodium sulfate or to perform dehydration by the Dean Stark method.

25 The ligand thus obtained can then be reacted with a transition metal M-containing compound, to synthesize the desired transition metal compound. Specifically,

the ligand is dissolved in a solvent, and if necessary, is contacted with a base to prepare a phenoxide salt, followed by mixing with a metal compound such as a metallic halide or a metallic alkylate at a low temperature and stirring for about 1 to 48 hours at -78°C to room temperature or under reflux. Any solvents usually used in such reactions may be employed and preferable are polar solvents such as ethers, e.g., tetrahydrofuran (THF) and hydrocarbon solvents such as toluene. Examples of the bases which may be used for preparing the phenoxide salt include, but not limited to metallic salts, such as lithium salts (e.g., n-butyllithium) and sodium salts (e.g., sodium hydride) and organic bases such as triethylamine and pyridine.

Depending on the properties of the compound, the step of preparing the phenoxide salt may be omitted, and the ligand can be directly reacted with the metal compound to synthesize the corresponding transition metal compound.

Further, it is possible that the transition metal M in the synthesized compound is replaced with another transition metal by conventional methods. Furthermore, any one of  $R^1$  to  $R^6$  which is H can be substituted by a substituent other than H at any synthesis steps.

The novel transition metal compound represented by the formula (III), preferably the formula (III-a), can be favorably used as an olefin polymerization catalyst.

If the transition metal compound is used as an olefin polymerization catalyst, (co)polymers of narrow molecular weight distribution can be synthesized with high polymerization activities.

5

$\alpha$ -Olefin/conjugated diene copolymer

The  $\alpha$ -olefin/conjugated diene copolymer according to the invention comprises 1 to 99.9 % by mol of constituent units derived from an  $\alpha$ -olefin and 99 to 0.1  
10 % by mol of constituent units derived from a conjugated diene, and preferably comprises 50 to 99.9 % by mol of constituent units derived from an  $\alpha$ -olefin and 50 to 0.1 % by mol of constituent units derived from a conjugated diene.

15 Examples of the  $\alpha$ -olefins include the same straight-chain or branched  $\alpha$ -olefins of 2 to 30, preferably 2 to 20 carbon atoms as described above. Of these, preferable are ethylene, propylene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene and 1-octene.  
20 Particularly preferable are ethylene and propylene. These  $\alpha$ -olefins can be used singly or in combination or two or more kinds.

Examples of the conjugated dienes include aliphatic conjugated dienes of 4 to 30, preferably 4 to 20,  
25 preferably 4 to 20 carbon atoms, such as 1,3-butadiene,

isoprene, chloroprene, 1,3-cyclohexadiene, 1,3-pentadiene, 4-methyl-1,3-pentadiene, 1,3-hexadiene and 1,3-octadiene. These conjugated dienes can be used singly or in combination of two or more kinds.

- 5        In the copolymerization of the  $\alpha$ -olefin and the conjugated diene, non-conjugated diene or polyene is further employable, and examples thereof include 1,4-pentadiene, 1,5-hexadiene, 1,4-hexadiene, 1,4-octadiene, 1,5-octadiene, 1,6-octadiene, 1,7-octadiene, ethylidene  
10 norbornene, vinyl norbornene, dicyclopentadiene, 7-methyl-1,6-octadiene, 4-ethylidene-8-methyl-1,7-nonadiene, 5,9-dimethyl-1,4,8-decatriene.

- In the polymer chain of the  $\alpha$ -olefin/conjugated diene copolymer of the invention, the content of 1,2-cyclopentane skeleton derived from the conjugated diene  
15 is not more than 1 % by mol, preferably such a content that the 1,2-cyclopentadiene skeleton can be regarded to be substantially not contained (i.e., less than 0.1 % by mol). When the content of the 1,2-cyclopentane skeleton  
20 is less than 0.1 % by mol, the content is regarded to be lower than the detection limit and is not introduced into the calculation of all the conjugated diene units.

- In the polymer chain of the  $\alpha$ -olefin/conjugated diene copolymer of the invention, the proportion of the  
25 1,2-cyclopentane skeleton to all the diene units is not

more than 20 %, preferably not more than 10 %. The proportions of other insertions of the dienes (e.g., 1,4-cis, 1,4-trans, 1,2-vinyl) in the  $\alpha$ -olefin/conjugated diene copolymer are arbitrary. The proportions can be determined by  $^{13}\text{C}$ -NMR and  $^1\text{H}$ -NMR in accordance with the method described in "Die Makromolekulare Chemie", volume 192, p. 2591 (1991).

The  $\alpha$ -olefin/conjugated diene copolymer has a molecular weight distribution ( $M_w/M_n$ ) of not more than 3.5 and has a uniform composition distribution. The weight average molecular weight ( $M_w$ ) of the copolymer is not less than 1,000, preferably not less than 5,000.

Since the  $\alpha$ -olefin/conjugated diene copolymer has double bonds in its main chain or side chain, it can be variously modified. For example, by virtue of modification with a peroxide, the double bonds can be epoxidized to introduce epoxy groups of high reactivity into the copolymer. Such a modification makes the copolymer possible to be used as a thermoplastic resin or a reactive resin. The double bonds can also be utilized in the Diels-Alder reaction or the Michael addition reaction. Further, in case of the copolymer having double bonds in the main chain, the copolymer can be improved in heat resistance and ozone resistance by

selectively hydrogenating the double bonds to saturate them.

The  $\alpha$ -olefin/conjugated diene copolymer of the invention may be modified partially or fully with an  
5 unsaturated carboxylic acid, its derivative or an aromatic vinyl compound, and the degree of modification is preferably in the range of .0.01 to 30 % by weight.

The monomer used for the modification (referred to as "graft monomer" hereinafter) is, for example, an  
10 unsaturated carboxylic acid, its derivative or an aromatic vinyl compound. Examples of the unsaturated carboxylic acids include acrylic acid, methacrylic acid, maleic acid, fumaric acid and itaconic acid. Examples of the derivatives of unsaturated carboxylic acids  
15 include acid anhydrides, esters, amides, imides and metallic salts thereof, such as maleic anhydride, citraconic anhydride, itaconic anhydride, methyl acrylate, methyl methacrylate, ethyl acrylate, ethyl methacrylate, butyl acrylate, butyl methacrylate,  
20 glycidyl acrylate, glycidyl methacrylate, monoethyl maleate, diethyl maleate, monomethyl fumarate, dimethyl fumarate, monomethyl itaconate, diethyl itaconate, acrylamide, methacrylamide, maleic acid monoamide, maleic acid diamide, maleic acid-N-monoethylamide,  
25 maleic acid-N,N-diethylamide, maleic acid-N-

monobutylamide, maleic acid-N,N-dibutylamide, fumaric acid monoamide, fumaric acid diamide, fumaric acid-N-monoethylamide, fumaric acid-N,N-diethylamide, fumaric acid-N-monobutylamide, fumaric acid-N,N-dibutylamide, 5 maleimide, N-butylmaleimide, N-phenylmaleimide, sodium acrylate, sodium methacrylate, potassium acrylate and potassium methacrylate. Of the graft monomers, maleic anhydride is preferably employed.

Examples of the aromatic vinyl compounds include:  
10 styrene;  
mono or polyalkylstyrenes, such as o-methylstyrene, m-methylstyrene, p-methylstyrene, o,p-dimethylstyrene, o-ethylstyrene, m-ethylstyrene and p-ethylstyrene;  
functional group-containing styrene derivatives,  
15 such as methoxystyrene, ethoxystyrene, vinylbenzoic acid, methyl vinylbenzoate, vinylbenzyl acetate, hydroxystyrene, o-chlorostyrene, p-chlorostyrene and divinylbenzene; and  
others, such as 3-phenylpropylene, 4-phenylbutene  
20 and a-methylstyrene. Of these, styrene or 4-methoxystyrene is preferable.

For graft copolymerizing the  $\alpha$ -olefin/conjugated diene copolymer with the graft monomer to prepare a modified copolymer, various known processes are  
25 available.



For example, the  $\alpha$ -olefin/conjugated diene copolymer and the graft monomer are heated at a high temperature in the presence or absence of a solvent and in the presence or absence of a radical initiator to perform graft copolymerization. In the reaction, the graft monomers may be used in combination.

In order to prepare a partially or wholly graft-modified  $\alpha$ -olefin/conjugated diene copolymer having a graft ratio of 0.01 to 30 % by weight, it is preferable from the viewpoint of industrial production that a graft-modified  $\alpha$ -olefin/conjugated diene copolymer having a high graft ratio is prepared and the thus graft-modified copolymer is then mixed with an unmodified  $\alpha$ -olefin/conjugated diene copolymer to adjust the graft ratio, because the concentration of the graft monomer in the composition can be adjusted as desired. It is also possible that a given amount of a graft monomer is blended with the  $\alpha$ -olefin/conjugated diene copolymer from the first to perform graft modification.

Referring to the degree of modification of the  $\alpha$ -olefin/conjugated diene copolymer with the graft monomer, the graft ratio to the whole resin composition is in the range of preferably 0.01 to 30 % by weight, particularly preferably 0.05 to 10 % by weight.

The  $\alpha$ -olefin/conjugated diene copolymer of the invention (including the above-mentioned modified product) may be blended with (i) a polyolefin resin and optionally, with (ii) a filler to form resin compositions useful for various applications.

(i) Polyolefin resin

The polyolefin resin (i) which may be blended with the  $\alpha$ -olefin/conjugated diene copolymer of the invention may be any of a crystalline polyolefin and an amorphous polyolefin, or may be a mixture of these polyolefin resins.

The crystalline polyolefin is, for example, a homopolymer or a copolymer of an  $\alpha$ -olefin of 2 to 20 carbon atoms or a cycloolefin. The amorphous polyolefin is, for example, a copolymer of one or more  $\alpha$ -olefins of 2 to 20 carbon atoms and one or more cycloolefins.

Examples of the  $\alpha$ -olefins of 2 to 20 carbon atoms include ethylene, propylene, 1-butene, 2-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene, 4,4-dimethyl-1-pentene, 3-methyl-1-pentene, 4-methyl-1-hexene, 3-ethyl-1-hexene, 4-ethyl-1-hexene, 4,4-dimethyl-1-hexene, 1-octene, 3-methyl-1-butene, 1-nonene, 1-decene, 1-undecene, 1-dodecene, 1-tetradecene, 1-hexadecene, 1-octadecene and 1-eicosene.

Examples of the cycloolefins include cyclopentene, cycloheptene, cyclohexene, norbornene, 5-ethyl-2-norbornene, tetracyclododecene and 2-ethyl-1,4,5,8-dimethano-1,2,3,4,4a,5,8,8a-octahydronaphthalene.

5        Examples of the crystalline polyolefin resins include the following (co)polymers (1) to (11). Of the copolymers, particularly preferable are the copolymers (3) and (5).

10        (1) Ethylene homopolymer (produced by any of low-pressure and high-pressure processes)

      (2) Copolymer of ethylene and not more than 20 % by mol of another  $\alpha$ -olefin, vinyl monomer (e.g., vinyl acetate, ethyl acrylate) or cycloolefin

      (3) Propylene homopolymer

15        (4) Random copolymer of propylene and not more than 20 % by mol of another  $\alpha$ -olefin

      (5) Block copolymer of propylene and not more than 30 % by mol of another  $\alpha$ -olefin

      (6) 1-Butene homopolymer

20        (7) Random copolymer of 1-butene and not more than 20 % by mol of another  $\alpha$ -olefin

      (8) 4-Methyl-1-pentene homopolymer

      (9) Random copolymer of 4-methyl-1-pentene and not more than 20 % by mol of another  $\alpha$ -olefin

25        (10) Cyclopentene homopolymer

(11) Random copolymer of cyclopentene and not more than 20 % by mol of another  $\alpha$ -olefin

As the "another  $\alpha$ -olefin" in the above (co)polymers (1) to (11), ethylene, propylene, 1-butene, 4-methyl-1-pentene, 1-hexene or 1-octene from among the aforesaid examples is preferably employed. As the cycloolefin, cyclopentene, cyclohexene, norbornene or tetracyclododecene is preferably employed.

The crystalline polyolefin resin desirably has a melt flow rate (measured at 230 °C under a load of 2.16 kg in accordance with ASTM D1238-65T) of 0.01 to 100 g/10 min, preferably 0.3 to 70 g/10 min, and a crystallinity, as measured by X-ray diffractometry, of usually 5 to 100 %, preferably 20 to 80 %.

The crystalline polyolefin resin can be prepared by a conventional process.

Examples of the amorphous polyolefin resins include the following (co)polymers.

- (1) Norbornene homopolymer
- (2) Copolymer of ethylene and norbornene, or copolymer of ethylene, norbornene and another  $\alpha$ -olefin
- (3) Copolymer of ethylene and tetracyclododecene, or copolymer of ethylene, tetracyclododecene and another  $\alpha$ -olefin

(ii) Filler

As the fillers (ii), which may be blended with the  $\alpha$ -olefin/conjugated diene copolymer of the invention, those generally used can be used without specific

5 limitation.

Examples of the inorganic fillers include:

powdered fillers, such as silicates (e.g., powdered talc, kaolinite, calcined clay, pyrophyllite, sericite, wollastonite), carbonates (precipitated calcium  
10 carbonate, heavy calcium carbonate, magnesium carbonate), hydroxides (e.g., aluminum hydroxide, magnesium hydroxide), oxides (e.g., zinc oxide, zinc white, magnesium oxide), and synthetic silicic acids or silicates (e.g., hydrated calcium silicate, hydrated  
15 aluminum silicate, hydrated silicic acid, silicic anhydride);

flaky fillers, such as mica;

fibrous fillers, such as basic magnesium sulfate whisker, calcium titanate whisker, aluminum borate  
20 whisker, sepiolite, PMF (processed mineral fiber), xonotlite, potassium titanate and ellestadite; and

balloon fillers, such as glass balloon and fly ash balloon.

These fillers can be used singly or in combination  
25 of two or more kinds.

When the  $\alpha$ -olefin/conjugated diene copolymer is blended with the polyolefin resin (i) and the filler (ii), the  $\alpha$ -olefin/conjugated diene copolymer is desirably contained in an amount of 10 to 90 parts by weight, preferably 15 to 80 parts by weight, more preferably 20 to 75 parts by weight, based on 100 parts by weight of the total of the  $\alpha$ -olefin/conjugated diene copolymer, the polyolefin resin (i) and the filler (ii).

If the content of the  $\alpha$ -olefin/conjugated diene copolymer is used in this amount, the  $\alpha$ -olefin/conjugated diene copolymer composition has excellent moldability and is capable of providing molded products having not only excellent impact resistance, weathering resistance and heat stability but also excellent rigidity, strength and heat resistance.

The polyolefin resin (i) is contained in an amount of 1 to 99 parts by weight, preferably 10 to 85 parts by weight, more preferably 10 to 85 parts by weight, based on 100 parts by weight of the total of the resulting composition.

If the polyolefin resin (i) is used in this amount, the composition having not only excellent impact resistance and cold resistance but also excellent rigidity, strength, heat resistance and moldability can be obtained.

The filler (ii) is contained in an amount of 0 to 40 parts by weight, preferably 0 to 30 parts by weight, based on 100 parts by weight of the total of the resulting composition. If the filler (ii) is contained  
5 in this amount, the composition having excellent rigidity, surface appearance and heat resistance can be obtained.

Further, to the  $\alpha$ -olefin/conjugated diene copolymer composition, various additives, such as nucleating  
10 agents, antioxidants, hydrochloric acid absorbers, heat stabilizers, light stabilizers, ultraviolet light absorbers, lubricants, antistatic agents, flame retardants, pigments, dyes, dispersants, copper harm inhibitors, neutralizing agents, foaming agents,  
15 plasticizers, anti-foaming agents, crosslinking agents, crosslinking aids, crosslinking accelerators, flow property improvers (e.g., peroxide), weld strength improvers, processing aids, weathering stabilizers and blooming inhibitors, may be added in an amount not  
20 detrimental to the objects of the invention. These optional additives may be used in combination of two or more kinds.

#### EFFECT OF THE INVENTION

The olefin polymerization catalyst according to the invention exhibits high polymerization activities on olefins.

In the process for olefin polymerization according to the invention, an olefin (co)polymer of narrow molecular distribution can be produced with high polymerization activities. When an  $\alpha$ -olefin and a conjugated diene are copolymerized, a copolymer containing almost no 1,2-cyclopentane skeleton in the polymer chain can be produced.

The novel transition metal compound according to the invention is useful for an olefin polymerization catalyst, and provides an olefin (co)polymer of narrow molecular weight distribution with high polymerization activities.

The  $\alpha$ -olefin/conjugated diene copolymer according to the invention has a narrow molecular weight distribution and contains almost no cyclopentane skeleton in the polymer chain.

20

#### EXAMPLE

The present invention is further described with reference to the following examples, but it should be construed that the invention is in no way limited to those examples.

25



Structures of the compounds obtained by Synthesis Examples were determined by 270MHz  $^1\text{H}$ -NMR (GSH-270 of Japan Electron Optics Laboratory Co., Ltd.), FT-IR (SHIMAZU FTIR-8200D), FD-mass spectrometry (SX-102A of Japan Electron Optics Laboratory Co., Ltd.), metal content analysis (SHIMAZU ICPS-8000, ICP method after dry ashing and dilute nitric acid dissolution), and carbon, hydrogen and nitrogen content analysis (CHNO type of Helaus Co.).

Structures of the compounds A-1 and B-1 were further decided by X-ray crystal structure analysis. The measurement was made by effecting Mo-K  $\alpha$ -ray irradiation using a Rigaku AFC7R four-axis diffractometer. The structure analysis was made by a direct method (SIR92), and the structure optimization was made in accordance with TeXan crystal structure analysis program.


Further, the intrinsic viscosity  $[\eta]$  was measured in decahydronaphthalene at 135 °C. The molecular weight distribution ( $M_w/M_n$ ) was measured by the gas permeation chromatography (GPC) using o-dichlorobenzene as a solvent at 140 °C.

Specific syntheses of ligands are given below.

## Ligand Synthesis Example 1

Synthesis of ligand (L1)

To a 100 ml reactor thoroughly purged with nitrogen, 40 ml of ethanol, 0.71 g (7.62 mmol) of aniline and 1.35 g (7.58 mmol) of 3-t-butylsalicylaldehyde were introduced, and they were stirred at room temperature for 24 hours. The reaction solution was concentrated under reduced pressure to remove the solvent. Then, 40 ml of ethanol was added again, and the mixture was stirred at room temperature for 12 hours. The reaction solution was concentrated under reduced pressure to obtain 1.83 g (7.23 mmol, yield: 95 %) of a compound represented by the following formula (L1) as an orange oil.




L1

$^1\text{H-NMR}$  ( $\text{CDCl}_3$ ): 1.47 (s, 9H), 6.88 (dd, 1H), 7.24-7.31 (m, 4H), 7.38-7.46 (m, 3H), 8.64 (s, 1H), 13.95 (s, 1H)  
IR (neat): 1575, 1590, 1610  $\text{cm}^{-1}$   
FD-mass spectrometry: 253

Ligand Synthesis Example 2Synthesis of ligand (L2)

To a 100 ml reactor thoroughly purged with  
5 nitrogen, 30 ml of ethanol, 1.34 g (9.99 mmol) of a-  
naphthylamine and 1.40 g (7.86 mmol) of 3-t-  
butylsalicylaldehyde were introduced. After addition of  
5 g of molecular sieves 3A, the mixture was stirred  
under reflux for 8 hours and then at room temperature  
10 for 12 hours. The reaction solution was concentrated  
under reduced pressure and the residue was purified  
using a silica gel column to obtain 2.35 g (7.75 mmol,  
98 % yield) of a compound as an orange oil represented  
by the following formula (L2).

15




L2

<sup>1</sup>H-NMR (CDCl<sub>3</sub>): 1.50 (s, 9H), 6.90-7.90 (m, 11H), 8.30-  
8.50 (m, 1H), 13.90 (s, 1H)

20 FD-mass spectrometry: 303

Ligand Synthesis Example 3Synthesis of ligand (L3)

To a 100 ml reactor thoroughly purged with  
5 nitrogen, 30 ml of ethanol, 0.90 g (12.0 mmol) of t-  
butylamine and 1.78 g (10.0 mmol) of 3-t-  
butylsalicylaldehyde were introduced. After addition of  
5 g of molecular sieves 3A, the mixture was stirred at  
room temperature for 12 hours. The reaction solution  
10 was concentrated under reduced pressure and the residue  
was purified using a silica gel column to obtain 2.17 g  
(9.3 mmol, 93 % yield) of a compound as an fluorescent  
yellow oil represented by the following formula (L3).



L3

<sup>1</sup>H-NMR (CDCl<sub>3</sub>): 1.20 (s, 9H), 1.42 (s, 9H), 6.50-7.50  
(m, 3H), 8.38 (s, 1H), 13.80 (s, 1H)


FD-mass spectrometry: 233

Ligand Synthesis Examples 4 - 42


Ligands L4 to L42 were synthesized in the similar manner as in the forgoing Ligand Synthesis Examples.

The identification of their structures were made by  $^1\text{H}$ -NMR and FD-mass spectrometry.


2025-03-13 14:06:00




L4




L5




L6




L7




L8




L9




L10




L11




L12




L13




L14




L15




L16




L17




L18




L19




L20




L21




L22




L23




L24




L25




L26




L27




L28



L29




L30




L31


172




L 3 2




L 3 3




L 3 4




L 3 5




L 3 6




L 3 7




L 3 8




L 3 9



L 4 0



L 4 1



L 4 2



Specific syntheses of transition metal compounds according to the present invention are given below.

Synthesis of compound A-1


5 To a 300 ml reactor thoroughly dried and purged with argon, 1.785 g (7.05 mmol) of compound L1 and 100 ml of diethyl ether were introduced, and they were cooled to -78 °C and stirred. After 4.78 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 7.40 mmol)  
10 was dropwise added over a period of 5 minutes, the temperature was slowly raised to room temperature, and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was slowly dropwise added to a mixture of 7.05 ml of a  
15 titanium tetrachloride solution (0.5 mmol/ml heptane solution, 3.53 mmol) and 40 ml of diethyl ether which had been been cooled to -78 °C.

After the dropwise addition was completed, the temperature was slowly raised to room temperature with  
20 stirring. After stirring for another 8 hours at room temperature, the reaction solution was filtered with a glass filter, and the resulting solid was dissolved and washed with 50 ml of methylene chloride to remove insolubles. The filtrate was concentrated under reduced  
25 pressure, and the solid precipitated was dissolved in 10

ml of methylene chloride. To the solution was then slowly added 70 ml of pentane with stirring. The mixture was allowed to stand at room temperature to precipitate red brown crystals. The crystals were  
 5 separated by filtration with a glass filter, washed with pentane and then vacuum dried to obtain 1.34 g (2.15 mmol, yield: 61 %) of compound A-1 represented by the following formula as red brown crystals.

10

Compound A-1



$^1\text{H-NMR}$  ( $\text{CDCl}_3$ ): 1.35 (s, 18H), 6.82-7.43 (m, 16H), 8.07  
 15 (s, 2H)

IR (KBr): 1550, 1590, 1600  $\text{cm}^{-1}$

FD-mass spectrometry: 622 ( $\text{M}^+$ )

Elemental analysis:

Ti: 7.7 % (7.7)

20 C: 65.8 % (65.5), H: 6.0 % (5.8), N: 4.5 % (4.5)

Calculated values in parentheses.

Melting point: 265 °C

X-ray crystal structure analysis: The structure of compound A-1 is shown in Fig. 3.

## 5 Synthesis Example 2


### Synthesis of compound B-1

To a 200 ml reactor thoroughly dried and purged with argon, 1.53 g (6.04 mmol) of compound L1 and 60 ml of tetrahydrofuran were introduced, and they were cooled to -78 °C and stirred. After 4.1 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 6.34 mmol) was dropwise added over a period of 5 minutes, the temperature was slowly raised to room temperature, and stirring was continued at room temperature for 4 hours. To the reaction solution was added 10 ml of tetrahydrofuran, and the mixture was slowly added to a solution of 0.70 g of zirconium tetrachloride (purity: 99.9 %, 3.02 mmol) in 30 ml of tetrahydrofuran which had been cooled to -78 °C. After the addition, the temperature was slowly raised to room temperature. The reaction solution was stirred for 2 hours at room temperature and then further stirred for another 4 hours under reflux.

The reaction solution was concentrated under reduced pressure, and the solid precipitated was washed with 50 ml of methylene chloride and filtered with a

glass filter to remove insolubles. The filtrate was concentrated under reduced pressure, and the solid precipitated was dissolved in 30 ml of diethyl ether. The solution was allowed to stand for one day at -20 °C in a nitrogen atmosphere to precipitate yellow crystals. The solid was separated by filtration, washed with hexane and then vacuum dried to obtain 1.09 g (1.63 mmol, yield: 54 %) of compound B-1 represented by the following formula as fluorescent yellow crystals.

Compound B-1



$^1\text{H-NMR}$  ( $\text{CDCl}_3$ ): 1.33 (s, 18H), 6.78-7.42 (m, 16H), 8.12 (s, 2H)

IR (KBr): 1550, 1590, 1605  $\text{cm}^{-1}$

FD-mass spectrometry: 664 (M<sup>+</sup>)

Elemental analysis:

Zr: 13.5 % (13.7)

C: 61.0 % (61.2), H: 5.5 % (5.4), N: 4.2 % (4.2)

Calculated values in parentheses.

Melting point: 287 °C

X-ray crystal structure analysis: The structure of compound B-1 is shown in Fig. 4.

5

Synthesis Example 3

Synthesis of compound C-1


To a 100 ml reactor thoroughly dried and purged  
with argon, 0.66 g (2.60 mmol) of compound (L1) and 8 ml  
10 of diethyl ether were introduced, and they were cooled  
to -78 °C and stirred. After 1.81 ml of n-butyllithium  
(1.55 mmol/ml n-hexane solution, 2.80 mmol) was dropwise  
added over a period of 5 minutes, the temperature was  
slowly raised to room temperature, and stirring was  
15 continued at room temperature for 2 hours. To the  
reaction solution was added 10 ml of tetrahydrofuran,  
and the mixture was slowly added to a solution of 0.385  
g of hafnium tetrachloride (purity: 99.9 %, 3.02 mmol)  
in 10 ml of tetrahydrofuran which had been cooled to -78  
20 °C. After the addition, the temperature was slowly  
raised to room temperature. The reaction solution was  
stirred for 2 hours at room temperature and then further  
stirred for another 2 hours under heating at 50 °C.

The reaction solution was concentrated under  
25 reduced pressure, and the solid precipitated was washed

with 20 ml of methylene chloride and filtered with a glass filter to remove insolubles. The filtrate was concentrated under reduced pressure, and the solid precipitated was reslurried in 10 ml of diethyl ether at room temperature for 1 hour and separated by filtration. The solid was washed with hexane and then vacuum dried to obtain 0.33 g (0.40 mmol, yield: 33 %) of compound C-1 represented by the following formula as fluorescent yellow white crystals.

10

Compound C-1



$^1\text{H-NMR}$  ( $\text{CDCl}_3$ ): 1.30 (s, 18H), 6.70-7.50 (m, 16H), 8.18 (s, 2H)

FD-mass spectrometry: 754 ( $\text{M}^+$ )

Elemental analysis:

Hf: 23.5 % (23.7)

C: 54.4 % (54.2), H: 4.8 % (4.8), N: 3.6 % (3.7)

Calculated values in parentheses.

Melting point: 277 °C

Synthesis Example 4


Synthesis of compound D-1

5 To a 100 ml reactor thoroughly dried and purged  
with argon, 0.61 g (2.40 mmol) of compound (L1) and 10  
ml of diethyl ether were introduced, and they were  
cooled to -78 °C and stirred. After 1.61 ml of n-  
butyllithium (1.55 mmol/ml n-hexane solution, 2.50 mmol)  
10 was dropwise added over a period of 5 minutes, the  
temperature was slowly raised to room temperature, and  
stirring was continued at room temperature for 4 hours.  
The reaction solution was slowly added to a solution of  
0.385 g of hafnium tetrachloride (purity: 99.9 %, 3.02  
15 mmol) in 10 ml of diethyl ether which had been cooled to  
-78 °C. After the addition, the temperature was slowly  
raised to room temperature, and the reaction solution  
was stirred for 4 hours at room temperature.

The reaction solution was concentrated under  
20 reduced pressure, and the solid precipitated was washed  
with 20 ml of methylene chloride and filtered with a  
glass filter to remove insolubles. The filtrate was  
concentrated under reduced pressure, and the solid  
precipitated was dissolved in 1 ml of diethyl ether. To  
25 the solution was slowly added 10 ml of hexane with

stirring to precipitate black green solid. The solid was separated by filtration, reslurried and washed with hexane at room temperature for 1 hour and then vacuum dried to obtain 0.55 g (0.88 mmol, yield: 73 %) of  
 5 compound D-1 represented by the following formula as a blue black powder.

Compound D-1



10

$^1\text{H-NMR}$  ( $\text{CDCl}_3$ ): unmeasurable because of paramagnetic metal complex.

FD-mass spectrometry: 625 ( $\text{M}^+$ )

15 Elemental analysis:

V: 8.4 % (8.1)

C: 65.3 % (65.2), H: 5.5 % (5.8), N: 4.5 % (4.8)

Calculated values in parentheses.

20 Synthesis Example 5

Synthesis of compound E-1



To a 100 ml reactor thoroughly dried and purged with argon, 0.61 g (2.40 mmol) of compound (L1) and 10 ml of diethyl ether were introduced, and they were cooled to -78 °C and stirred. After 1.60 ml of n-

5 butyllithium (1.55 mmol/ml n-hexane solution, 2.50 mmol) was dropwise added over a period of 5 minutes, the temperature was slowly raised to room temperature, and stirring was continued at room temperature for 4 hours. To the reaction solution was added 5 ml of

10 tetrahydrofuran, and the mixture was slowly added to a solution of 0.34 g of niobium pentachloride (purity: 95 %, 1.20 mmol) in 10 ml of tetrahydrofuran which had been cooled to -78 °C. After the addition, the temperature was slowly raised to room temperature, and the reaction

15 solution was stirred at room temperature for 15 hours.

The reaction solution was concentrated under reduced pressure, and the solid precipitated was washed with 20 ml of methylene chloride and filtered with a glass filter to remove insolubles. The filtrate was


20 concentrated under reduced pressure, and the solid precipitated was dissolved in 3 ml of diethyl ether. To the solution was slowly dropwise added 12 ml of hexane at room temperature with stirring to precipitate black solid. The solid was separated by filtration,

25 reslurried and washed with hexane at room temperature

for 1 hour and then vacuum dried to obtain 0.36 g (0.51 mmol, yield: 43 %) of fluorescent yellow white compound E-1 represented by the following formula.

5

Compound E-1



$^1\text{H-NMR}$  ( $\text{CDCl}_3$ ): 1.46 (s, 18H), 7.20-7.50 (m, 16H), 8.65

10 (s, 2H)

FD-mass spectrometry: 702 ( $\text{M}^+$ )

Elemental analysis:

Nb: 13.0 % (13.2)

C: 58.4 % (58.0), H: 5.0 % (5.2), N: 3.9 % (4.0)

15 Calculated values in pharenthesis


#### Synthesis Example 6

##### Synthesis of compound F-1

To a 100 ml reactor thoroughly dried and purged  
20 with argon, 0.61 g (2.40 mmol) of compound (L1) and 10 ml of toluene were introduced, and they were cooled to

-40 °C and stirred. To the mixture, 0.43 g of solid tantalum pentachloride (purity: 99.99 %, 1.20 mmol) was slowly added. After the addition, the temperature was slowly raised to room temperature, then further raised to 60 °C, and stirring was continued for 16 hours.

To the reaction solution was added 30 ml of methylene chloride, and the insolubles were filtered. The filtrate was concentrated under reduced pressure, and to the concentrate was added 8 ml of hexane to separate out an orange viscous oil. The oil portion was separated and dissolved in 1 ml of diethyl ether. To the solution was slowly dropwise added 9 ml of hexane with stirring to precipitate bright yellow solid. The solid was separated by filtration, reslurried and washed hexane at room temperature for 1 hour and then vacuum dried to obtain 0.15 g (0.26 mmol, yield: 22 %) of compound F-1 represented by the following formula as a bright yellow powder.



$^1\text{H-NMR}$  ( $\text{CDCl}_3$ ): 1.50 (s, 9H), 6.80-7.75 (m, 8H), 8.23 (s, 1H)

5 FD-mass spectrometry: 575 ( $\text{M}^+$ )

Elemental analysis:

Ta: 31.0 % (31.5)

C: 58.4 % (58.0), H: 3.3 % (3.2), N: 4.5 % (4.8)

Calculated values in parentheses.

10


#### Synthesis Example 7

##### Synthesis of compound A-2

After charging 0.91 g (3.0 mmol) of compound L2 and 20 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise adding 1.90 ml of n-butyllithium (1.54 mmol/ml n-hexane solution, 3.3 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a

lithium salt solution. The solution was cooled to  $-78^{\circ}\text{C}$  and then slowly added dropwise to a mixture of 3.0 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 1.50 mmol) and 10 ml of diethyl ether. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 8 hours at room temperature, the reaction solution was filtered with a glass filter. The resulting solid was dissolved and washed in 50 ml of methylene chloride, and the insoluble portion was removed by filtration. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with diethyl ether and hexane and dried under reduced pressure to obtain 0.53 g (0.73 mmol, 49% yield) of compound A-2 as dark brown crystals represented by the formula given below.

Compound A-2



$^1\text{H-NMR}(\text{CDCl}_3)$ : 0.86 (s, 18H), 6.85-7.05 (m, 6H), 7.15-7.30 (m, 4H), 7.35-7.90 (m, 10H), 8.45 (s, 2H)

FD-mass spectrometry: 722 (M<sup>+</sup>)

5 Elemental analysis: Ti: 6.6% (6.6)

C: 69.9% (69.7), H: 5.5% (5.6), N: 3.4% (3.9)

Calculated values in parentheses.


#### Synthesis Example 8

##### 10 Synthesis of compound B-2

After charging 0.91 g (3.0 mmol) of compound L2 and 20 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to -78°C and stirred. After dropwise adding 15 1.94 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 3.0 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly 20 added dropwise to a 10 ml tetrahydrofuran solution containing zirconium tetrachloride (0.35 g, 1.50 mmol) which had been cooled to -78°C. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After 25 further stirring for 8 hours at room temperature, the

reaction solution was concentrated to dryness, the residue was dissolved and washed in 50 ml of methylene chloride, and then the insoluble portion was removed by filtration. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with diethyl ether and hexane and dried under reduced pressure to obtain 0.21 g (0.73 mmol, 18% yield) of compound B-2 as yellow crystals represented by the formula given below.

Compound B-2



$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.11-1.70 (m, 18H), 6.80-8.30 (m, 20H), 8.33-8.48 (m, 2H)

FD-mass spectrometry: 766 (M<sup>+</sup>)

Elemental analysis: Zr: 12.1% (11.9)

Calculated value in parentheses.


Synthesis Example 9

Synthesis of compound A-3

After charging 0.70 g (3.0 mmol) of compound L3 and 30 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise adding 1.90 ml of n-butyllithium (1.54 mmol/ml n-hexane solution, 3.3 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was cooled to  $-78^{\circ}\text{C}$  and then 3.0 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 1.50 mmol) was slowly added dropwise. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the reaction solution was filtered with a glass filter. The resulting solid was dissolved and washed in 50 ml of methylene chloride, and the insoluble portion was removed by filtration. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with diethyl ether and hexane and dried under reduced pressure to obtain 0.15 g (0.26 mmol, 17% yield) of compound A-3 as yellow brown crystals represented by the formula given below.



Compound A-3



5

$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.20 (s, 18H), 1.41 (s, 18H), 6.85-7.05 (m, 2H), 7.20-7.80 (m, 4H), 8.58 (s, 2H)

FD-mass spectrometry: 582 (M+)

Elemental analysis: Ti: 8.2% (8.2)

10 C: 62.1% (61.8), H: 7.1% (7.6), N: 4.7% (4.8)

Calculated values in parentheses.

#### Synthesis Example 10


##### Synthesis of compound B-3

15 After charging 0.70 g (3.0 mmol) of compound L3 and 30 ml of tetrahydrofuran into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise adding 1.90 ml of n-butyllithium (1.54 mmol/ml n-hexane

20 solution, 3.3 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a

lithium salt solution. The solution was cooled to  $-78^{\circ}\text{C}$  and solid zirconium tetrachloride (0.38 g, 1.65 mmol) was added. After completion of the addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the solvent was distilled off from the reaction solution, the resulting solid was dissolved and washed in 50 ml of methylene chloride, and the insoluble portion was removed by filtration. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with methylene chloride and hexane and dried under reduced pressure to obtain 0.31 g (0.50 mmol, 30% yield) of compound B-3 as a yellow powder represented by the formula given below.

Compound B-3



$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.34 (s, 18H), 1.44 (s, 18H), 6.79 (dd, 2H), 7.11 (d, 2H), 7.27 (d, 2H), 8.34 (s, 2H)  
 FD-mass spectrometry: 626 ( $\text{M}^+$ )

Elemental analysis: Zr: 15.0% (14.6)

C: 52.9 (57.5), H: 7.2 (7.1), N: 4.7 (4.8)

Calculated values in parentheses.


5 Synthesis Example 11

Synthesis of compound A-4

After charging 0.50 g (2.02 mmol) of compound L4 and 30 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to -78°C and stirred. After dropwise adding 1.36 ml of n-butyllithium (1.54 mmol/ml n-hexane solution, 2.09 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was cooled to -78°C, and then 2.00 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 1.00 mmol) was slowly added dropwise. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 8 hours at room temperature, the reaction solution was filtered with a glass filter. The resulting solid was dissolved and washed in 50 ml of methylene chloride, and the insoluble portion was removed by filtration. The filtrate was concentrated

under reduced pressure, and the deposited solid was reprecipitated with methylene chloride and hexane and dried under reduced pressure to obtain 0.34 g (0.56 mmol, 56% yield) of compound A-4 as a dark brown powder  
 5 represented by the formula given below.

Compound A-4



10

$^1\text{H-NMR}(\text{CDCl}_3)$ : 7.00-7.90 (m, 22H), 8.35-8.55 (m, 2H)

FD-mass spectrometry: 610 (M<sup>+</sup>)

Elemental analysis: Ti: 7.8% (7.8)

C: 62.4% (66.8), H: 4.9% (4.4), N: 4.2% (4.6)

15 Calculated values in parentheses.

### Synthesis Example 12


#### Synthesis of compound B-4

After charging 0.46 g (1.86 mmol) of compound L4  
 20 and 30 ml of diethyl ether into a 100 ml reactor which

had been adequately dried and substituted with argon, they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise adding 1.30 ml of n-butyllithium (1.54 mmol/ml n-hexane solution, 2.00 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was cooled to  $-78^{\circ}\text{C}$ , and then solid zirconium tetrachloride (0.21 g, 0.91 mmol) was added. After completion of the addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 16 hours at room temperature, 20 ml of diethyl ether was added and the insoluble portion was removed with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with diethyl ether and hexane and dried under reduced pressure to obtain 0.25 g (0.38 mmol, 42% yield) of compound B-4 as a yellow-brownish green powder represented by the formula given below.

Compound B-4

194



$^1\text{H-NMR}(\text{CDCl}_3)$ : 6.90-7.95 (m, 22H), 8.40-8.60 (m, 2H)

FD-mass spectrometry: 652 (M<sup>+</sup>)

5 Elemental analysis: Zr: 14.3% (13.9)

Calculated value in parentheses.


#### Synthesis Example 13

##### Synthesis of compound A-5

- 10 After charging 0.83 g (3.00 mmol) of compound L5 and 30 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise adding 2.00 ml of n-butyllithium (1.54 mmol/ml n-hexane
- 15 solution, 3.08 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was cooled to  $-78^\circ\text{C}$ , and then 3.00 ml of a titanium tetrachloride

solution (0.5 mmol/ml heptane solution, 1.50 mmol) was slowly added dropwise. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the reaction solution was filtered with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with methylene chloride and hexane and dried under reduced pressure to obtain 0.07 g (0.10 mmol, 7% yield) of compound A-5 as an ocher powder represented by the formula given below.

Compound A-5



15

FD-mass spectrometry: 666 (M+)

Elemental analysis: Ti: 7.3% (7.2)

Calculated value in parentheses.

20


Synthesis Example 14Synthesis of compound B-5

After charging 0.50 g (1.82 mmol) of compound L5 and 15 ml of tetrahydrofuran into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to -78°C and stirred. After dropwise adding 1.36 ml of n-butyllithium (1.54 mmol/ml n-hexane solution, 2.09 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was cooled to -78°C and then a 10 ml tetrahydrofuran solution containing a zirconium tetrachloride·2THF complex (0.38 g, 1.00 mmol) was added dropwise. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 10 hours at room temperature and 4 hours at 50°C, the insoluble portion was removed with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with methylene chloride, diethyl ether and hexane and dried under reduced pressure to obtain 0.04 g (0.05 mmol, 5% yield) of compound B-5 as a yellow-brownish green powder represented by the formula given below.



197

Compound B-5



5 FD-mass spectrometry: 710 (M+)

Elemental analysis: Zr: 13.3% (12.8)

Calculated value in parentheses.


Synthesis Example 15

10 Synthesis of compound A-6

After charging 0.93 g (3.01 mmol) of compound L6 and 30 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to -78°C and stirred. After dropwise adding 2.1 ml of n-butyllithium (1.54 mmol/ml n-hexane solution, 3.23 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was cooled to -78°C and then 3.0 ml of a titanium tetrachloride solution

(0.5 mmol/ml heptane solution, 1.50 mmol) was slowly added dropwise. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the reaction solution was filtered with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was recrystallized with hexane at  $-78^{\circ}\text{C}$  and dried under reduced pressure to obtain 0.41 g (0.56 mmol, 37% yield) of compound A-6 as a brown powder represented by the formula given below.

Compound A-6



15

$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.21 (s, 18H), 1.30 (s, 18H), 6.70-7.70 (m, 14H), 8.08 (s, 2H)

FD-mass spectrometry: 734 (M $^{+}$ )

Elemental analysis: Ti: 6.6% (6.5)

20 C: 67.9% (68.6), H: 7.4% (7.1), N: 3.9% (3.8)


Calculated values in parentheses.

Synthesis Example 16

Synthesis of compound B-6

- 5        After charging 0.93 g (3.01 mmol) of compound L6  
and 30 ml of diethyl ether into a 100 ml reactor which  
had been adequately dried and substituted with argon,  
they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise  
adding 2.1 ml of n-butyllithium (1.54 mmol/ml n-hexane  
10    solution, 3.23 mmol) over 5 minutes, the temperature was  
slowly increased to room temperature and stirring was  
continued for 4 hours at room temperature to prepare a  
lithium salt solution. The solution was cooled to  $-78^{\circ}\text{C}$   
and then solid zirconium tetrachloride (0.35 g, 1.50  
15    mmol) was added. After completion of the addition,  
stirring was continued while slowly increasing the  
temperature to room temperature. After further stirring  
for 14 hours at room temperature, 20 ml of methylene  
chloride was added, and the insoluble portion was  
20    removed with a glass filter. The filtrate was  
concentrated under reduced pressure, and the deposited  
solid was recrystallized with hexane at  $-78^{\circ}\text{C}$  and dried  
under reduced pressure to obtain 0.55 g (0.71 mmol, 47%  
yield) of compound B-6 as a brownish green powder  
25    represented by the formula given below.

Compound B-6



5

$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.20-1.80 (m, 36H), 6.70-7.70 (m, 14H),

7.80-7.90 (m, 2H)

FD-mass spectrometry: 776 (M+)

Elemental analysis: Zr: 11.2% (11.7)

10 Calculated value in parentheses.


#### Synthesis Example 17

##### Synthesis of compound A-7

After charging 1.0 g (3.66 mmol) of compound L7 and  
 15 20 ml of diethyl ether into a 100 ml reactor which had  
 been adequately dried and substituted with argon, they  
 were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise adding  
 2.48 ml of n-butyllithium (1.55 mmol/ml n-hexane  
 solution, 3.84 mmol) over 5 minutes, the temperature was  
 20 slowly increased to room temperature and stirring was  
 continued for 4 hours at room temperature to prepare a

lithium salt solution. The solution was then slowly added dropwise to a mixture of 3.66 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 1.83 mmol) and 20 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the reaction solution was filtered with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reslurried with hexane. The slurry was filtered to remove the solvent, and the solid was dried under reduced pressure to obtain 0.95 g (1.43 mmol, 78% yield) of compound A-7 as a brown powder represented by the formula given below.

Compound A-7



$^1\text{H-NMR}(\text{CDCl}_3)$ : 6.90-7.90 (m, 26H), 8.00 (s, 2H)

FD-mass spectrometry: 662 (M+)

Elemental analysis: Ti: 6.5% (6.5)

C: 62.0% (62.2), H: 3.7% (3.8), N: 3.8% (3.8)

5 Calculated values in parentheses.


#### Synthesis Example 18

##### Synthesis of compound B-7

After charging 1.0 g (3.66 mmol) of compound L7 and  
10 20 ml of diethyl ether into a 100 ml reactor which had  
been adequately dried and substituted with argon, they  
were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise adding  
2.48 ml of n-butyllithium (1.55 mmol/ml n-hexane  
solution, 3.84 mmol) over 5 minutes, the temperature was  
15 slowly increased to room temperature and stirring was  
continued for 4 hours at room temperature to prepare a  
lithium salt solution. The solution was then added  
dropwise to a mixture of zirconium tetrachloride (0.41  
g, 1.77 mmol) in 30 ml of diethyl ether cooled to  $-78^\circ\text{C}$ .  
20 After completion of the dropwise addition, stirring was  
continued while slowly increasing the temperature to  
room temperature. After further stirring for 15 hours  
at room temperature, 20 ml of methylene chloride was  
added, and the insoluble portion was removed with a  
25 glass filter. The filtrate was concentrated under

reduced pressure, and the deposited solid was reslurried with hexane. The slurry was filtered to remove the solvent and the solid was dried under reduced pressure to obtain 0.94 g (1.33 mmol, 73% yield) of compound B-7 as a yellow green powder represented by the formula given below.

Compound B-7



$^1\text{H-NMR}(\text{CDCl}_3)$ : 7.00-7.90 (m, 26H), 8.20 (s, 2H)

FD-mass spectrometry: 704 (M<sup>+</sup>)

Elemental analysis: Zr: 11.5% (11.7)

Calculated values in parentheses.

#### Synthesis Example 19


##### Synthesis of compound A-8

After charging 1.0 g (2.93 mmol) of compound L8 and 20 ml of diethyl ether into a 100 ml reactor which had

been adequately dried and substituted with argon, they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise adding 2.0 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 3.10 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly added dropwise to a mixture containing 2.9 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 1.45 mmol) and 20 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the reaction solution was filtered with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reslurried with hexane. The slurry was filtered to remove the solvent and the solid was dried under reduced pressure to obtain 1.06 g (1.33 mmol, 91% yield) of compound A-8 as a brown powder represented by the formula given below.

Compound A-8





$^1\text{H-NMR}(\text{CDCl}_3)$ : 0.90-1.70 (m, 18H), 3.40-3.80 (m, 4H),  
7.00-7.70 (m, 20H), 7.80-8.20 (m, 2H)

- 5 FD-mass spectrometry: 798 (M+)  
Elemental analysis: Ti: 6.0% (6.0)  
Calculated value in parentheses.


#### Synthesis Example 20

##### 10 Synthesis of compound B-8

- After charging 1.0 g (2.93 mmol) of compound L8 and  
20 ml of diethyl ether into a 100 ml reactor which had  
been adequately dried and substituted with argon, they  
were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise adding  
15 2.0 ml of n-butyllithium (1.55 mmol/ml n-hexane  
solution, 3.10 mmol) over 5 minutes, the temperature was  
slowly increased to room temperature and stirring was  
continued for 4 hours at room temperature to prepare a

lithium salt solution. The solution was then added dropwise to a mixture of zirconium tetrachloride (0.34 g, 1.44 mmol) in 20 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 8 hours at room temperature, 20 ml of diethyl ether was added, and the insoluble portion was removed with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reslurried with hexane. The slurry was filtered to remove the solvent and the solid was dried under reduced pressure to obtain 1.02 g (1.21 mmol, 83% yield) of compound B-8 as a yellow green powder represented by the formula given below.

Compound B-8



$^1\text{H-NMR}(\text{CDCl}_3)$ : 0.90-1.80 (m, 18H), 3.40-3.90 (m, 4H),  
6.40-7.90 (m, 20H), 8.00-8.30 (m, 2H)

FD-mass spectrometry: 842 (M+)

5 Elemental analysis: Zr: 11.1% (10.8)

Calculated value in parentheses.


#### Synthesis Example 21

##### Synthesis of compound A-9

10 After charging 0.50 g (1.23 mmol) of compound L9  
and 15 ml of diethyl ether into a 100 ml reactor which  
had been adequately dried and substituted with argon,  
they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise  
adding 0.84 ml of n-butyllithium (1.55 mmol/ml n-hexane  
15 solution, 1.30 mmol) over 5 minutes, the temperature was  
slowly increased to room temperature and stirring was  
continued for 4 hours at room temperature to prepare a  
lithium salt solution. The solution was then slowly  
added dropwise to a mixed solution containing 1.2 ml of  
20 a titanium tetrachloride solution (0.5 mmol/ml heptane  
solution, 0.60 mmol) and 15 ml of diethyl ether which  
had been cooled to  $-78^\circ\text{C}$ . After completion of the  
dropwise addition, stirring was continued while slowly  
increasing the temperature to room temperature. After  
25 further stirring for 8 hours at room temperature, the

reaction solution was filtered with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reslurried with hexane. The slurry was filtered to remove the solvent and the solid was dried under reduced pressure to obtain 0.33 g (0.36 mmol, 58% yield) of compound A-9 as a brown powder represented by the formula given below.

Compound A-9



$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.70-1.90 (m, 18H), 6.60-7.80 (m, 34H)

FD-mass spectrometry: 926 (M<sup>+</sup>)

15 Elemental analysis: Ti: 5.3% (5.2)

Calculated value in parentheses.


Synthesis Example 22Synthesis of compound B-9

After charging 0.50 g (1.23 mmol) of compound L9 and 15 ml of diethyl ether into a 100 ml reactor which  
5 had been adequately dried and substituted with argon, they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise adding 0.84 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 1.30 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was  
10 continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly added dropwise to a mixed solution of zirconium tetrachloride (0.14 g, 0.60 mmol) and 15 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion  
15 of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the solvent was distilled off, the resulting solid was dissolved in 50 ml of methylene chloride and 10 ml of  
20 diethyl ether, and then the insoluble portion was removed with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reslurried with hexane. The slurry was filtered to remove the solvent and the solid was dried  
25 under reduced pressure to obtain 0.19 g (0.20 mmol, 32%

yield) of compound B-9 as a light yellow powder represented by the formula given below.

Compound B-9

5



$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.28-1.52 (m, 18H), 6.70-7.76 (m, 34H)

FD-mass spectrometry: 970 ( $\text{M}^+$ )

10 Elemental analysis: Zr: 9.6% (9.4)

Calculated value in parentheses.


### Synthesis Example 23

#### Synthesis of compound A-10

15 After charging 0.32 g (1.03 mmol) of compound L10 and 10 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon,

they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise adding 0.77 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 1.19 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly added dropwise to a solution containing 1.0 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 0.50 mmol) and 10 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the reaction solution was filtered with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with methylene chloride and hexane and dried under reduced pressure to obtain 0.16 g (0.22 mmol, 43% yield) of compound A-10 as a brown powder represented by the formula given below.

Compound A-10



$^1\text{H-NMR}(\text{CDCl}_3)$ : 0.40-0.90 (m, 30H), 6.60-7.80 (m, 18H)

FD-mass spectrometry: 739 (M<sup>+</sup>)

5 Elemental analysis: Ti: 5.3% (5.2)

Calculated value in parentheses.

#### Synthesis Example 24

##### Synthesis of compound A-11

10 After charging 0.68 g (2.40 mmol) of compound L11 and 30 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise adding 1.49 ml of n-butyllithium (1.61 mmol/ml n-hexane


15 solution, 2.40 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly added dropwise to a solution containing 2.4 ml of a

20 titanium tetrachloride solution (0.5 mmol/ml heptane



solution, 1.20 mmol) and 15 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the solvent of the reaction solution was distilled off, the resulting solid was dissolved in 50 ml of methylene chloride, and the insoluble portion was filtered off with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with methylene chloride and hexane at  $0^{\circ}\text{C}$  and dried under reduced pressure to obtain 0.37 g (0.54 mmol, 45% yield) of compound A-11 as a red brown powder.

Compound A-11



$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.20-1.40 (m, 9H), 1.50-1.55 (m, 9H), 3.70-3.85 (m, 6H), 6.52-7.40 (m, 14H), 8.05-8.20 (m, 2H)

FD-mass spectrometry: 682 ( $\text{M}^+$ )

Elemental analysis: Ti: 7.0% (7.0)

Calculated value in parentheses.

Synthesis Example 25


5        Synthesis of compound B-11

After charging 0.64 g (2.26 mmol) of compound L11 and 20 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise  
10 adding 1.40 ml of n-butyllithium (1.61 mmol/ml n-hexane solution, 2.26 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly  
15 added dropwise to a solution of zirconium tetrachloride $\cdot$ 2THF (0.42 g, 1.10 mmol) in 20 ml of tetrahydrofuran which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to  
20 room temperature. After further stirring for 15 hours at room temperature, the solvent of the reaction solution was distilled off. The resulting solid was dissolved in 50 ml of methylene chloride, and the insoluble portion was filtered off with a glass filter.  
25 The filtrate was concentrated under reduced pressure,

and the deposited solid was reprecipitated with methylene chloride and hexane and dried under reduced pressure to obtain 0.25 g (0.34 mmol, 31% yield) of compound B-11 as a yellow green powder represented by

5 the formula given below.

Compound B-11



10

$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.20-1.60 (m, 18H), 3.66-3.86 (m, 6H),  
6.50-7.50 (m, 14H), 8.05-8.20 (m, 2H)

FD-mass spectrometry: 726 (M<sup>+</sup>)

Elemental analysis: Zr: 12.4% (12.6)

15 Calculated value in parentheses.


#### Synthesis Example 26

##### Synthesis of compound A-12

After charging 1.0 g (2.31 mmol) of compound L12

20 and 20 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon,

they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise adding 1.56 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 2.42 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly added dropwise to a mixed solution containing 2.3 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 1.15 mmol) and 20 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the insoluble portion was filtered off with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reslurried with hexane. The slurry was filtered to remove the solvent and the solid was dried under reduced pressure to obtain 0.45 g (0.45 mmol, 40% yield) of compound A-12 as a red brown powder.



$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.30-2.20 (m, 24H), 6.20-7.40 (m, 34H),  
7.50-7.70 (m, 2H)

- 5 FD-mass spectrometry: 982 ( $\text{M}^+$ )  
Elemental analysis: Ti: 5.0% (4.9)  
Calculated value in parentheses.

#### Synthesis Example 27

##### 10 Synthesis of compound B-12


- After charging 1.0 g (2.31 mmol) of compound L12 and 20 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise
- 15 adding 1.56 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 2.42 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly
- 20 added dropwise to a mixed solution of zirconium

tetrachloride (0.27 g, 1.15 mmol) and 20 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature.

- 5 After further stirring for 15 hours at room temperature, the insoluble portion was removed with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with diethyl ether, hexane, heptane and pentane, reslurried and
- 10 washed, and then dried under reduced pressure to obtain 0.02 g (0.02 mmol, 1% yield) of compound B-12 as a yellow green powder represented by the formula given below.

15

Compound B-12



- $^1\text{H-NMR}(\text{CDCl}_3)$ : 1.20-2.10 (m, 24H), 6.20-7.40 (m, 34H),
- 20 7.50-8.00 (m, 2H)

FD-mass spectrometry: 1026 ( $\text{M}^+$ )

Elemental analysis: Zr: 9.1% (8.9)

Calculated value in parentheses.

Synthesis Example 28


5        Synthesis of compound A-13

After charging 1.10 g (3.26 mmol) of compound L13 and 22 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise  
10 adding 2.2 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 3.41 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly  
15 added dropwise to a mixed solution containing 3.26 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 1.13 mmol) and 22 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly  
20 increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the solvent of the reaction solution was distilled off, the insoluble portion of the reaction solution was filtered off with a glass filter. The filtrate was concentrated  
25 under reduced pressure, and the deposited solid was

reprecipitated with diethyl ether and pentane and dried under reduced pressure to obtain 0.22 g (0.28 mmol, 17% yield) of compound A-13 as a red brown powder.

5

Compound A-13



$^1\text{H-NMR}(\text{CDCl}_3)$ : 0.60-2.41 (m, 44H), 6.70-7.60 (m, 34H),

10 7.91-8.10 (m, 2H)

FD-mass spectrometry: 790 (M<sup>+</sup>)

Elemental analysis: Ti: 6.3% (6.1)

Calculated value in parentheses.

15 Synthesis Example 29


Synthesis of compound B-13

After charging 1.03 g (3.02 mmol) of compound L13 and 20 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, 20 they were cooled to -78°C and stirred. After dropwise



adding 2.0 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 3.10 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly added dropwise to a mixed solution of zirconium tetrachloride (0.35 g, 1.50 mmol) and 20 ml of diethyl ether which had been cooled to -78°C. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the insoluble portion was removed with a glass filter. The filtrate was concentrated under reduced pressure, the deposited solid was recrystallized with pentane and dried under reduced pressure to obtain 0.27 g (0.32 mmol, 21% yield) of compound B-13 as a yellow green powder represented by the formula given below.

Compound B-13



$^1\text{H-NMR}(\text{CDCl}_3)$ : 0.30-2.32 (m, 44H), 6.70-7.60 (m, 14H),  
7.90-8.20 (m, 2H)

5 FD-mass spectrometry: 834 (M<sup>+</sup>)

Elemental analysis: Zr: 10.9% (10.9)

Calculated value in parentheses.

#### Synthesis Example 30

##### 10 Synthesis of compound A-14

After charging 0.98 g (2.97 mmol) of compound L14 and 30 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to -78°C and stirred. After dropwise  
15 adding 2.0 ml of n-butyllithium (1.61 mmol/ml n-hexane solution, 3.22 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly


added dropwise to a mixed solution containing 3.0 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 1.50 mmol) and 15 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the

5 dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the insoluble portion of the reaction solution was filtered off, the filtered substance was dissolved in 30 ml of

10 diethyl ether and 50 ml of methylene chloride, and the insoluble portion was filtered off with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was recrystallized with diethyl ether and dried under reduced pressure to obtain 0.66 g

15 (0.85 mmol, 57% yield) of compound A-14 as a dark brown powder.

Compound A-14



$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.41 (s, 18H), 6.70-7.90 (m, 24H), 8.18 (s, 2H)

FD-mass 'spectrometry: 774 (M+)

Elemental analysis: Ti: 6.2% (6.2)

5 Calculated value in parentheses.

### Synthesis Example 31


#### Synthesis of compound B-14

After charging 1.01 g (3.05 mmol) of compound L14  
10 and 20 ml of diethyl ether into a 100 ml reactor which  
had been adequately dried and substituted with argon,  
they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise  
adding 2.0 ml of n-butyllithium (1.61 mmol/ml n-hexane  
solution, 3.22 mmol) over 5 minutes, the temperature was  
15 slowly increased to room temperature and stirring was  
continued for 4 hours at room temperature to prepare a  
lithium salt solution. The solution was then slowly  
added dropwise to a tetrahydrofuran solution containing  
zirconium tetrachloride (0.36 g, 1.52 mmol) which had  
20 been cooled to  $-78^\circ\text{C}$ . After completion of the dropwise  
addition, stirring was continued while slowly increasing  
the temperature to room temperature. After further  
stirring for 8 hours at room temperature, the insoluble  
portion was removed with a glass filter. The filtrate  
25 was concentrated to dryness, and the deposited solid was

reprecipitated with methylene chloride and hexane and dried under reduced pressure to obtain 0.61 g (0.74 mmol, 49% yield) of compound B-14 as a fluorescent yellow powder represented by the formula given below.

5

Compound B-14



10  $^1\text{H-NMR}(\text{CDCl}_3)$ : 1.41 (s, 18H), 6.80-7.90 (m, 24H), 8.24 (s, 2H)

FD-mass spectrometry: 818 (M<sup>+</sup>)

Elemental analysis: Zr: 11.0% (11.1)

Calculated value in parentheses.


15

#### Synthesis Example 32

##### Synthesis of compound A-15

After charging 0.40 g (1.01 mmol) of compound L15 and 10 ml of diethyl ether into a 100 ml reactor which  
 20 had been adequately dried and substituted with argon, they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise

adding 0.77 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 1.19 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly added dropwise to a mixed solution containing 1.0 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 0.50 mmol) and 10 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the insoluble portion was filtered off with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with diethyl ether and hexane and dried under reduced pressure to obtain 0.19 g (0.21 mmol, 42% yield) of compound A-15 as a red brown powder.



$^1\text{H-NMR}(\text{CDCl}_3)$ : 0.60-1.30 (m, 6H), 6.50-7.80 (m, 36H),

7.80-7.90 (m, 2H)

5 FD-mass spectrometry: 900 (M<sup>+</sup>)

Elemental analysis: Ti: 5.5% (5.3)

Calculated value in parentheses.

### Synthesis Example 33

#### 10 Synthesis of compound B-15


After charging 0.40 g (1.02 mmol) of compound L15 and 10 ml of tetrahydrofuran into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise

15 adding 0.77 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 1.19 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. After cooling the solution to

20  $-78^\circ\text{C}$ , solid zirconium tetrachloride (0.12 g, 0.50 mmol)

was added. After completion of the addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the solvent of the reaction solution was distilled off. The resulting solid was dissolved in 50 ml of methylene chloride, and the insoluble portion was removed with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with diethyl ether and hexane and dried under reduced pressure to obtain 0.20 g (0.21 mmol, 42% yield) of compound B-15 as a grayish white powder represented by the formula given below.

Compound B-15



$^1\text{H-NMR}(\text{CDCl}_3)$ : 0.70-1.00 (m, 6H), 6.60-7.60 (m, 36H),

7.70-7.80 (m, 2H)

FD-mass spectrometry: 944 ( $\text{M}^+$ )



Elemental analysis: Zr: 9.4% (9.6)

Calculated value in parentheses.

Synthesis Example 34


5      Synthesis of compound A-16

After charging 1.0 g (4.73 mmol) of compound L16 and 20 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise  
10 adding 3.2 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 4.96 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly  
15 added dropwise to a mixed solution containing 4.7 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 2.35 mmol) and 20 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly  
20 increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the reaction solution was filtered, and the filtered substance was dissolved in 50 ml of methylene chloride. The insoluble portion was removed, the filtrate was  
25 concentrated under reduced pressure, and the deposited

solid was reprecipitated with methylene chloride and hexane and dried under reduced pressure to obtain 0.96 g (1.78 mmol, 75% yield) of compound A-16 as a pale brown powder.

5

Compound A-16



10  $^1\text{H-NMR}(\text{CDCl}_3)$ : 1.90 (s, 6H), 6.50–7.30 (m, 16H), 7.90 (s, 2H)

FD-mass spectrometry: 538 (M<sup>+</sup>)

Elemental analysis: Ti: 9.0% (8.9)

Calculated value in parentheses.

15


#### Synthesis Example 35

##### Synthesis of compound B-16

After charging 1.0 g (4.73 mmol) of compound L16 and 20 ml of diethyl ether into a 100 ml reactor which  
 20 had been adequately dried and substituted with argon, they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise

adding 3.2 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 4.96 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then added dropwise to a mixed solution of zirconium tetrachloride (0.55 g, 2.36 mmol) and 20 ml of diethyl ether which had been cooled to -78°C. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the reaction solution was filtered off. The solvent of the filtrate was distilled off, and the resulting solid was recrystallized with diethyl ether, methylene chloride and hexane and dried under reduced pressure to obtain 0.49 g (0.84 mmol, 36% yield) of compound B-16 as a yellow green powder represented by the formula given below.

232



$^1\text{H-NMR}(\text{CDCl}_3)$ : 2.00 (s, 6H), 6.40-7.40 (m, 16H), 8.10 (s, 2H)

5 FD-mass spectrometry: 582 (M+)

Elemental analysis: Zr: 15.9% (15.7)

Calculated value in parentheses.

#### Synthesis Example 36

##### 10 Synthesis of compound A-17


After charging 1.0 g (2.77 mmol) of compound L17 and 20 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise adding 1.87 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 2.90 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly added dropwise to a mixed solution containing 2.76 ml of

15

20

a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 1.38 mmol) and 20 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the insoluble portion was filtered off with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reslurried with hexane. The slurry was filtered to remove the solvent and the solid was dried under reduced pressure to obtain 0.15 g (0.18 mmol, 13% yield) of compound A-17 as a brown powder.

Compound A-17



$^1\text{H-NMR}(\text{CDCl}_3)$ : 3.20-3.80 (m, 4H), 6.90-7.81 (m, 30H), 8.15 (s, 2H)

FD-mass spectrometry: 838 (M+)

Elemental analysis: Ti: 5.9% (5.7)

Calculated value in parentheses.

5 Synthesis Example 37


Synthesis of compound B-17

After charging 1.0 g (2.77 mmol) of compound L17 and 20 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to -78°C and stirred. After dropwise adding 1.87 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 2.90 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then added dropwise to a mixed solution of zirconium tetrachloride (0.32 g, 1.37 mmol) and 20 ml of diethyl ether which had been cooled to -78°C. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the insoluble portion in the reaction solution was removed with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reslurried with hexane. The slurry was filtered to remove the

solvent and the solid was dried under reduced pressure to obtain 0.71 g (0.88 mmol, 58% yield) of compound B-17 as a yellow green powder represented by the formula given below.

5

Compound B-17



10  $^1\text{H-NMR}(\text{CDCl}_3)$ : 3.30-3.80 (m, 4H), 6.71-7.72 (m, 30H), 8.25 (s, 2H)

FD-mass spectrometry: 882 (M<sup>+</sup>)

Elemental analysis: Zr: 10.6% (10.3)

Calculated value in parentheses.

15


#### Synthesis Example 38

##### Synthesis of compound A-18

After charging 0.59 g (2.20 mmol) of compound L18 and 10 ml of diethyl ether into a 100 ml reactor which

had been adequately dried and substituted with argon, they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise adding 1.49 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 2.31 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly added dropwise to a mixed solution containing 2.2 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 1.10 mmol) and 10 ml of tetrahydrofuran which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the mixture was concentrated to dryness, and the resulting solid was dissolved in 20 ml of methylene chloride. The insoluble portion was filtered off with a glass filter, the filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with diethyl ether and hexane at  $-78^{\circ}\text{C}$  and dried under reduced pressure to obtain 0.27 g (0.41 mmol, 37% yield) of compound A-18 as a brown powder.





$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.22 (s, 18H), 2.40 (s, 6H), 6.44-7.80

(m, 14H), 8.21 (s, 2H)

5 FD-mass spectrometry: 650 (M<sup>+</sup>)

Elemental analysis: Ti: 7.1% (7.4)

Calculated value in parentheses.

#### Synthesis Example 39

##### 10 Synthesis of compound B-18


After charging 0.60 g (2.25 mmol) of compound L18 and 10 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to -78°C and stirred. After dropwise

15 adding 1.52 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 2.36 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then added

20 dropwise to a solution of zirconium tetrachloride (0.26

g, 1.12 mmol) in 10 ml of tetrahydrofuran which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 8 hours at room temperature, the solvent of the reaction solution was distilled off. The resulting solid was dissolved in 20 ml of methylene chloride, and the insoluble portion was removed with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with diethyl ether and hexane and dried under reduced pressure to obtain 0.16 g (0.24 mmol, 21% yield) of compound B-18 as a yellow green powder represented by the formula given below.

Compound B-18



$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.13 (s, 18H), 2.39 (s, 6H), 6.50-7.75 (m, 14H), 8.26 (s, 2H)

FD-mass spectrometry: 694 (M+)

Elemental analysis: Zr: 13.1% (13.1)

Calculated value in parentheses.

5 Synthesis Example 40


Synthesis of compound B-19

After charging 0.70 g (2.25 mmol) of compound L19 and 10 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to -78°C and stirred. After dropwise adding 1.52 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 2.36 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then added dropwise to a solution of zirconium tetrachloride (0.26 g, 1.12 mmol) in 10 ml of tetrahydrofuran which had been cooled to -78°C. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the solvent of the reaction solution was distilled off. The resulting solid was dissolved in 20 ml of methylene chloride, and the insoluble portion was removed with a glass filter. The filtrate was concentrated under

reduced pressure, and the deposited solid was reprecipitated with diethyl ether and hexane and dried under reduced pressure to obtain 0.16 g (0.20 mmol, 18% yield) of compound B-19 as a yellow green powder

5 represented by the formula given below.

Compound B-19



10

$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.43 (s, 18H), 1.47 (s, 18H), 6.90-7.60 (m, 14H), 8.40 (s, 2H)

FD-mass spectrometry: 778 ( $\text{M}^+$ )

Elemental analysis: Zr: 12.1% (11.7)

15 Calculated value in parentheses.

#### Synthesis Example 41


##### Synthesis of compound B-20

After charging 0.63 g (2.25 mmol) of compound L20  
20 and 10 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon,

they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise adding 1.52 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 2.36 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then added dropwise to a solution of zirconium tetrachloride (0.26 g, 1.12 mmol) in 10 ml of tetrahydrofuran which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the solvent of the reaction solution was distilled off. The resulting solid was dissolved in 25 ml of methylene chloride, and the insoluble portion was removed with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with diethyl ether and hexane and dried under reduced pressure to obtain 0.35 g (0.48 mmol, 43% yield) of compound B-20 as a yellow powder represented by the formula given below.

Compound B-20

242



$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.40 (s, 18H), 1.50 (s, 18H), 2.21 (s, 12H),  
6.70-7.40 (m, 12H), 8.33 (s, 2H)

5 FD-mass spectrometry: 720 (M<sup>+</sup>)

Elemental analysis: Zr: 12.8% (12.6)

Calculated value in parentheses.

#### Synthesis Example 42


##### 10 Synthesis of compound A-21

After charging 0.80 g (2.50 mmol) of compound L21  
and 10 ml of diethyl ether into a 100 ml reactor which  
had been adequately dried and substituted with argon,  
they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise  
15 adding 1.7 ml of n-butyllithium (1.55 mmol/ml n-hexane  
solution, 2.64 mmol) over 5 minutes, the temperature was  
slowly increased to  $0^\circ\text{C}$ , and stirring was continued for  
4 hours at  $0^\circ\text{C}$  to prepare a lithium salt solution. The  
solution was then slowly added dropwise to a mixed  
20 solution containing 2.5 ml of a titanium tetrachloride

solution (0.5 mmol/ml heptane solution, 1.25 mmol) and 10 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 8 hours at room temperature, the mixture was concentrated to dryness, and the resulting solid was dissolved in 50 ml of diethyl ether and 60 ml of methylene chloride. The insoluble portion was filtered off with a glass filter, the filtrate was concentrated under reduced pressure, and the deposited solid was recrystallized with diethyl ether and dried under reduced pressure to obtain 0.07 g (0.09 mmol, 8% yield) of compound A-21 as a red brown powder.

15

Compound A-21



$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.34 (s, 18H), 6.75-7.75 (m, 14H), 8.10 (s, 2H)

FD-mass spectrometry: 758 (M+)

Elemental analysis: Ti: 6.5% (6.3)

5 Calculated value in parentheses.

#### Synthesis Example 43


##### Synthesis of compound B-21

After charging 1.03 g (3.20 mmol) of compound L21  
10 and 10 ml of diethyl ether into a 100 ml reactor which  
had been adequately dried and substituted with argon,  
they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise  
adding 2.0 ml of n-butyllithium (1.61 mmol/ml n-hexane  
solution, 3.22 mmol) over 5 minutes, the temperature was  
15 slowly increased to  $-15^\circ\text{C}$  and stirring was continued for  
2 hours at  $-15^\circ\text{C}$  to prepare a lithium salt solution.  
The solution was then added dropwise to a solution of  
zirconium tetrachloride (0.36 g, 1.54 mmol) in 10 ml of  
tetrahydrofuran which had been cooled to  $-78^\circ\text{C}$ . After  
20 completion of the dropwise addition, stirring was  
continued while slowly increasing the temperature to  
room temperature. After further stirring for 15 hours  
at room temperature, the solvent of the reaction  
solution was distilled off. The residue was dissolved  
25 in 20 ml of toluene, and the reaction was continued for



3 hours under reflux conditions. The solvent was distilled off, the resulting solid was dissolved in 50 ml of methylene chloride, and the insoluble portion was removed with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with diethyl ether and hexane and dried under reduced pressure to obtain 0.33 g (0.41 mmol, 27% yield) of compound B-21 as an other powder represented by the formula given below.

Compound B-21



<sup>1</sup>H-NMR(CDCl<sub>3</sub>): 1.24 (s, 18H), 6.80-7.78 (m, 14H), 8.15 (s, 2H)

FD-mass spectrometry: 802 (M<sup>+</sup>)

Elemental analysis: Zr: 11.7% (11.4)

Calculated value in parentheses.

Synthesis Example 44Synthesis of compound A-22


After charging 0.50 g (1.77 mmol) of compound L22 and 40 ml of diethyl ether into a 100 ml reactor which  
5 had been adequately dried and substituted with argon, they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise adding 1.20 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 1.86 mmol) over 5 minutes, the temperature was slowly increased to room temperature, and stirring was  
10 continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly added dropwise to a mixed solution containing 1.77 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 0.89 mmol) and 50 ml of diethyl ether which  
15 had been cooled to  $-78^{\circ}\text{C}$ .

After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the reaction solution was filtered  
20 with a glass filter. After washing the filtered substance with diethyl ether, it was dissolved in methylene chloride. The insoluble portion was removed, the filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with diethyl  
25 ether and hexane at  $-78^{\circ}\text{C}$  and dried under reduced

pressure to obtain 0.31 g (0.45 mmol, 51% yield) of compound A-22 as a brown powder.

5

Compound A-22



$^1\text{H-NMR}$  ( $\text{CDCl}_3$ ): 0.70-1.80 (m, 18H), 3.50-4.00 (m, 6H),  
6.40-7.70 (m, 14H), 8.05 (s, 2H)

10 FD-mass spectrometry: 682 ( $\text{M}^+$ )  
Elemental analysis: Ti: 7.3% (7.0)  
Calculated value in parentheses.

#### Synthesis Example 45

15


#### Synthesis of compound B-22

After charging 0.50 g (1.77 mmol) of compound L22 and 25 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise  
20 adding 1.20 ml of n-butyllithium (1.55 mmol/ml n-hexane

solution, 1.86 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then added dropwise to a mixed solution of zirconium tetrachloride (0.21 g, 0.99 mmol) in 10 ml of diethyl ether and 60 ml of tetrahydrofuran which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the solvent of the reaction solution was distilled off. The resulting solid was reslurried with 70 ml of hexane, and the insoluble portion was separated off with a glass filter. The filtered substance was dissolved in 100 ml of diethyl ether and 70 ml of hexane. After removing out the insoluble portion, the filtrate was concentrated under reduced pressure. The deposited solid was washed with hexane and dried under reduced pressure to obtain 0.08 g (0.11 mmol, 11% yield) of compound B-22 as a yellow green powder represented by the formula given below.

Compound B-22

249



$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.40 (s, 18H), 3.75 (s, 6H), 6.40–7.70 (m, 14H), 8.10 (s, 2H)

5 FD-mass spectrometry: 726 (M<sup>+</sup>)

Elemental analysis: Zr: 12.3% (12.6)

Calculated value in parentheses.

#### Synthesis Example 46

##### 10 Synthesis of compound A-23


After charging 1.01 g (4.33 mmol) of compound L23 and 22 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise adding 2.9 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 4.50 mmol) over 5 minutes, the temperature was slowly increased to room temperature, and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly

added dropwise to a mixed solution containing 4.25 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 2.13 mmol) and 20 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the

5 dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the reaction solution was filtered, the filtrate was concentrated to dryness, and the resulting solid was reprecipitated with methylene chloride, diethyl ether and hexane and dried under reduced pressure to obtain 10 0.26 g (0.44 mmol, 21% yield) of compound A-23 as a brown powder.

15

Compound A-23



$^1\text{H-NMR}(\text{CDCl}_3)$ : 0.82-1.40 (m, 12H), 2.90-3.30 (m, 2H),

20 6.60-7.40 (m, 16H), 8.10 (s, 2H)

FD-mass spectrometry: 594 ( $\text{M}^+$ )

Elemental analysis: Ti: 8.0% (8.0)

Calculated value in parentheses.

Synthesis Example 47


5        Synthesis of compound B-23

After charging 1.02 g (4.25 mmol) of compound L23 and 20 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise  
10 adding 3.43 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 5.32 mmol) over 5 minutes, the temperature was slowly increased to room temperature, and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then added  
15 dropwise to a mixed solution of zirconium tetrachloride (0.50 g, 2.15 mmol) and 20 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further  
20 stirring for 15 hours at room temperature, the insoluble portion was removed with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with diethyl ether, methylene chloride and hexane and dried under reduced  
25 pressure to obtain 0.61 g (0.96 mmol, 45% yield) of

compound B-23 as a yellow green powder represented by the formula given below.

Compound B-23

5



$^1\text{H-NMR}(\text{CDCl}_3)$ : 0.80-1.30 (m, 12H), 2.90-3.25 (m, 2H),  
6.72-7.43 (m, 16H), 8.20 (s, 2H)

10 FD-mass spectrometry: 638 (M+)

Elemental analysis: Zr: 14.0% (14.3)

Calculated value in parentheses.

#### Synthesis Example 48

15

#### Synthesis of compound A-24


After charging 0.52 g (2.05 mmol) of compound L24 and 40 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise adding 1.36 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 2.11 mmol) over 5 minutes, the temperature was

20



slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt slurry. The solution was slowly added dropwise to a mixed solution containing 2.04 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 1.02 mmol), 40 ml of diethyl ether and 20 ml of tetrahydrofuran which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the solvent of the reaction solution was distilled off. The resulting solid was reslurried with 100 ml of diethyl ether, and the insoluble portion was separated off with a glass filter. The filtered substance was washed with diethyl ether and dissolved in methylene chloride. After removing the insoluble portion, the filtrate was concentrated under reduced pressure, and the deposited solid was washed with hexane and dried under reduced pressure to obtain 0.12 g (0.19 mmol, 19% yield) of compound A-24 as an orange powder.

254



$^1\text{H-NMR}(\text{CDCl}_3)$ : 0.80-2.30 (m, 18H), 6.30-9.20 (m, 14H),  
8.35 (brs, 2H)

5 FD-mass spectrometry: 624 (M+)

Elemental analysis: Ti: 8.1% (7.7)

Calculated value in parentheses.

#### Synthesis Example 49

##### 10 Synthesis of compound B-24

After charging 0.76 g (2.99 mmol) of compound L24  
and 40 ml of diethyl ether into a 100 ml reactor which  
had been adequately dried and substituted with argon,  
they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise  
15 adding 1.91 ml of n-butyllithium (1.61 mmol/ml n-hexane  
solution, 3.08 mmol) over 5 minutes, the temperature was  
slowly increased to room temperature and stirring was  
continued for 4 hours at room temperature to prepare a  
lithium salt slurry. The solution was then added  
20 dropwise to a mixed solution of zirconium

tetrachloride·2THF complex (0.563 g, 1.49 mmol) in 80 ml of tetrahydrofuran which had been cooled to -78°C.

After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to

5 room temperature. After further stirring for 15 hours at room temperature, 50 ml of toluene was added, and the reaction solution was heated at 80°C for 10 hours and then at 90°C for 30 hours while stirring. The solvent of the reaction solution was distilled off, the


10 resulting solid was reslurried with 150 ml of diethyl ether, and the insoluble portion was separated off with a glass filter. After washing the filtered substance with diethyl ether, it was dissolved in methylene chloride, the insoluble portion was removed out, and

15 then the filtrate was concentrated under reduced pressure. The deposited solid was washed with hexane and dried under reduced pressure to obtain 0.43 g (0.64 mmol, 43% yield) of compound B-24 as a yellow powder represented by the formula given below.

20

Compound B-24

256



$^1\text{H-NMR}(\text{CDCl}_3)$ : 0.60-2.30 (m, 18H), 6.30-9.40 (m, 14H),  
8.35 (brs, 2H)

5 FD-mass spectrometry: 668 (M+)

Elemental analysis: Zr: 13.2% (13.6)

Calculated value in parentheses.


#### Synthesis Example 50

##### 10 Synthesis of compound A-25

After charging 0.50 g (1.93 mmol) of compound L25 and 20 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise  
15 adding 1.42 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 2.20 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was slowly added  
20 dropwise to a mixed solution containing 1.93 ml of a

titanium tetrachloride solution (0.5 mmol/ml heptane solution, 0.97 mmol) and 50 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the reaction solution was filtered with a glass filter, and the filtered substance was washed with diethyl ether and dissolved in methylene chloride. After removing the insoluble portion, the filtrate was concentrated under reduced pressure, and the deposited solid was washed with hexane and dried under reduced pressure to obtain 0.11 g (0.17 mmol, 18% yield) of compound A-25 as a red brown powder.

Compound A-25



$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.65 (s, 18H), 0.50-2.40 (m, 20H), 3.85 (brdt, 2H), 6.90-7.70 (m, 6H), 8.20 (s, 2H)

FD-mass spectrometry: 634 (M+)

Elemental analysis: Ti: 7.6% (7.5)

Calculated value in parentheses.

5 Synthesis Example 51


Synthesis of compound B-25

After charging 0.50 g (1.93 mmol) of compound L25 and 20 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to -78°C and stirred. After dropwise adding 1.42 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 2.20 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then added dropwise to a solution of zirconium tetrachloride (0.23 g, 0.99 mmol) in 50 ml of diethyl ether which had been cooled to -78°C. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 15 hours at room temperature, the reaction solution was filtered with a glass filter, and the filtrate was concentrated under reduced pressure. The deposited solid was washed with hexane and dried under reduced pressure to obtain 0.28 g (0.41 mmol, 43% yield)

of compound B-25 as an other powder represented by the formula given below.

Compound B-25

5



$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.65 (s, 18H), 0.70-2.50 (m, 20H), 3.85 (brdt, 2H), 6.70-7.70 (m, 6H), 8.25 (s, 2H)

10 FD-mass spectrometry: 678 (M+)

Elemental analysis: Zr: 13.3% (13.4)

Calculated value in parentheses.

#### Synthesis Example 52


15 Synthesis of compound A-26

After charging 0.61 g (2.28 mmol) of compound L26 and 10 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise adding 1.6 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 2.48 mmol) over 5 minutes, the temperature was

20

slowly increased to room temperature, and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly added dropwise to a mixed solution containing 2.2 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 1.10 mmol) and 10 ml of tetrahydrofuran which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 12 hours at room temperature, the insoluble portion was filtered out with a glass filter, the filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with diethyl ether and hexane at  $-78^{\circ}\text{C}$  and dried under reduced pressure to obtain 0.36 g (0.55 mmol, 51% yield) of compound A-26 as a brown powder.

Compound A-26





$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.33 (s, 18H), 2.14 (s, 6H), 6.60-7.68 (m, 14H), 8.03 (s, 2H)

FD-mass 'spectrometry: 650 (M+)

Elemental analysis: Ti: 7.4% (7.3)

5 Calculated value in parentheses.


### Synthesis Example 53

#### Synthesis of compound B-26

After charging 0.61 g (2.28 mmol) of compound L26  
10 and 10 ml of diethyl ether into a 100 ml reactor which  
had been adequately dried and substituted with argon,  
they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise  
adding 1.6 ml of n-butyllithium (1.55 mmol/ml n-hexane  
solution, 2.48 mmol) over 5 minutes, the temperature was  
15 slowly increased to room temperature, and stirring was  
continued for 4 hours at room temperature to prepare a  
lithium salt solution. The solution was then added  
dropwise to a solution of zirconium tetrachloride (0.27  
g, 1.15 mmol) in 10 ml of diethyl ether which had been  
20 cooled to  $-78^\circ\text{C}$ . After completion of the dropwise  
addition, stirring was continued while slowly increasing  
the temperature to room temperature. After further  
stirring for 12 hours at room temperature, the insoluble  
portion was removed with a glass filter. The filtrate  
25 was concentrated under reduced pressure, and the

deposited solid was reprecipitated with diethyl ether and hexane and dried under reduced pressure to obtain 0.14 g (0.20 mmol, 18% yield) of compound B-26 as a yellow green powder represented by the formula given below.

Compound B-26



10

$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.31 (s, 18H), 2.14 (s, 6H), 6.69-7.65 (m, 14H), 8.09 (s, 2H)

FD-mass spectrometry: 694 ( $\text{M}^+$ )

Elemental analysis: Zr: 13.1% (13.1)

15 Calculated value in parentheses.

#### Synthesis Example 54

##### Synthesis of compound A-27


After charging 0.30 g (1.00 mmol) of compound L27 and 10 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon,

20

they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise adding 0.65 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 1.00 mmol) over 5 minutes, the temperature was slowly increased to room temperature, and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly added dropwise to a mixed solution containing 1.0 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 0.50 mmol) and 10 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After first stirring for 12 hours at room temperature and then stirring for one hour under reflux, the insoluble portion was filtered out with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with diethyl ether and hexane and dried under reduced pressure to obtain 0.18 g (0.25 mmol, 50% yield) of compound A-27 as an orange powder.

Compound A-27

264



$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.13 (s, 18H), 1.25 (brd, 6H), 1.28  
 (brd, 6H), 3.29 (brdq, 2H), 6.45-6.70 (m, 2H), 6.80-7.20  
 5 (m, 4H), 7.20-7.50 (m, 8H), 8.23 (s, 2H)

FD-mass spectrometry: 706 ( $\text{M}^+$ )

Elemental analysis: Ti: 6.8% (6.8)

Calculated value in parentheses.


## 10 Synthesis Example 55

### Synthesis of compound B-27

After charging 0.95 g (3.20 mmol) of compound L27  
 and 10 ml of diethyl ether into a 100 ml reactor which  
 had been adequately dried and substituted with argon,  
 15 they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise  
 adding 2.08 ml of n-butyllithium (1.55 mmol/ml n-hexane  
 solution, 3.22 mmol) over 5 minutes, the temperature was  
 slowly increased to room temperature, and stirring was  
 continued for 4 hours at room temperature to prepare a  
 20 lithium salt solution. The solution was then added

dropwise to a solution of zirconium tetrachloride (0.37 g, 1.60 mmol) in 10 ml of tetrahydrofuran which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After first stirring for 12 hours at room temperature and then stirring for 6 hours under reflux, the solvent of the reaction solution was distilled off. The resulting solid was dissolved in 50 ml of methylene chloride, and the insoluble portion was removed with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with methylene chloride and hexane and dried under reduced pressure to obtain 0.18 g (0.24 mmol, 15% yield) of compound B-27 as a yellow powder.

Compound B-27



$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.10 (s, 18H), 1.10-1.40 (m, 12H), 3.20-3.30 (m, 2H), 6.30-6.60 (m, 2H), 6.70-7.10-7.60 (m, 8H), 8.28 (s, 2H)

FD-mass spectrometry: 750 (M+)

5 Elemental analysis: Zr: 12.0% (12.2)

C: 63.5% (64.0) H: 6.6% (6.4) N: 3.5% (3.7)

Calculated values in parentheses.

#### Synthesis Example 56


##### 10 Synthesis of compound A-28

After charging 0.50 g (1.37 mmol) of compound L28 and 40 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise  
15 adding 0.92 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 1.43 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly  
20 added dropwise to a mixed solution containing 1.37 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane, 0.69 mmol) and 40 ml of diethyl ether which had been cooled to  $-78^\circ\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing  
25 the temperature to room temperature. After further

stirring for 8 hours at room temperature, the reaction solution was filtered with a glass filter, the filtered substance was washed with diethyl ether, and then the insoluble portion was removed out by filtration. The  
 5 filtrate was concentrated under reduced pressure, and the deposited solid was washed with hexane and dried under reduced pressure to obtain 0.17 g (0.20 mmol, 29% yield) of compound A-28 as a brown powder.

10

Compound A-28



$^1\text{H-NMR}(\text{CDCl}_3)$ : 0.70-1.40 (m, 54H), 6.65-7.75 (m, 12H),

15 8.35 (s, 2H)

FD-mass spectrometry: 846 (M<sup>+</sup>)

Elemental analysis: Ti: 5.5% (5.7)

Calculated value in parentheses.

20 Synthesis Example 57


Synthesis of compound B-28

After charging 0.50 g (1.37 mmol) of compound L28 and 40 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise adding 0.92 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 1.43 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then added dropwise to a mixed solution of zirconium tetrachloride (0.16 g, 0.69 mmol) in 20 ml of anhydrous diethyl ether and 50 ml of tetrahydrofuran which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 12 hours at room temperature, the solvent of the reaction solution was distilled off. The resulting solid was reslurried with diethyl ether, the insoluble portion was removed off with a glass filter, and the filtrate was concentrated under reduced pressure. The deposited solid was reprecipitated with hexane at  $-78^{\circ}\text{C}$  and dried under reduced pressure to obtain 0.26 g (0.29 mmol, 43% yield) of compound B-28 as a yellow powder represented by the formula given below.



269

Compound B-28



5  $^1\text{H-NMR}(\text{CDCl}_3)$ : 0.80-1.30 (m, 54H), 6.65 (m, 12H), 8.35 (s, 2H)

FD-mass spectrometry: 890 (M+)

Elemental analysis: Zr: 9.9% (10.2)

Calculated value in parentheses.

10

Synthesis Example 58

Synthesis of compound A-29

After charging 0.60 g (1.79 mmol) of compound L29 and 40 ml of diethyl ether into a 100 ml reactor which  
15 had been adequately dried and substituted with argon, they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise adding 1.17 ml of n-butyllithium (1.55 mmol/ml n-hexane solution, 1.81 mmol) over 5 minutes, the temperature was slowly increased to room temperature, and stirring was  
20 continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly


added dropwise to a mixed solution containing 1.79 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 0.90 mmol) and 50 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the

5 dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After stirring for 12 hours at room temperature, the reaction solution was filtered with a glass filter to remove the insoluble portion. The filtrate was concentrated under

10 reduced pressure, and the deposited solid was washed with hexane and dried under reduced pressure to obtain 0.10 g (0.13 mmol, 14% yield) of compound A-29 as a red brown powder.

15

Compound A-29



$^1\text{H-NMR}(\text{CDCl}_3)$ : 0.80-2.30 (m, 20H), 1.55 (s, 18H), 3.65

20 (brdt, 2H), 6.60-8.10 (m, 16H)

FD-mass spectrometry: 786 ( $\text{M}^+$ )

Elemental analysis: Ti: 6.4% (6.1)

Calculated value in parentheses.


Synthesis Example 59

5        Synthesis of compound B-29

After charging 0.50 g (1.48 mmol) of compound L29 and 40 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to -78°C and stirred. After dropwise  
10 adding 1.02 ml of n-butyllithium (1.61 mmol/ml n-hexane solution, 1.64 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then added  
15 dropwise to a solution of zirconium tetrachloride·2THF complex (0.26 g, 0.69 mmol) in 40 ml of tetrahydrofuran which had been cooled to -78°C. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After  
20 further stirring for 8 hours at room temperature, 70 ml of toluene was added, the reaction solution was heated at 80°C for 20 hours while stirring. The solvent of the reaction solution was distilled off, the resulting solid was reslurried with 50 ml of diethyl ether. The slurry  
25 was filtered with a glass filter to remove off the

insoluble portion, and then the filtrate was concentrated under reduced pressure. The deposited solid was reprecipitated with hexane at  $-78^{\circ}\text{C}$  and dried under reduced pressure to obtain 0.04 g (0.05 mmol, 7%  
 5 yield) of compound B-29 as a yellowish white powder represented by the formula given below.

Compound B-29



10

$^1\text{H-NMR}(\text{CDCl}_3)$ : 0.90-1.90 (m, 20H), 1.55 (s, 18H), 3.25 (brdt, 2H), 6.40-7.90 (m, 16H)

FD-mass spectrometry: 830 (M+)

15 Elemental analysis: Zr: 11.3% (11.0)

Calculated value in parentheses.


#### Synthesis Example 60

##### Synthesis of compound A-30

20 After charging 0.51 g (1.86 mmol) of compound L30 and 50 ml of diethyl ether into a 100 ml reactor which

had been adequately dried and substituted with argon, they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise adding 1.20 ml of n-butyllithium (1.61 mmol/ml n-hexane solution, 1.93 mmol) over 5 minutes, the temperature was slowly increased to room temperature, and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly added dropwise to a solution containing 1.85 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 0.93 mmol) and 60 ml of tetrahydrofuran which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. Further stirring for 8 hours at room temperature, the reaction solution was heated at  $60^{\circ}\text{C}$  for 8 hours while stirring, and the solvent was then distilled off. The resulting solid was reslurried with diethyl ether and filtered with a glass filter, and the filtered substance was washed with diethyl ether and then dissolved in methylene chloride. After removal of the insoluble portion by filtration, the filtrate was concentrated under reduced pressure, and the deposited solid was washed with hexane and dried under reduced pressure to obtain 0.14 g (0.21 mmol, 23% yield) of compound A-30 as a red orange powder.

Compound A-30



5

$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.10-2.10 (m, 20H), 1.45 (s, 18H), 2.40 (s, 6H), 3.85 (brdt, 2H), 6.70-7.70 (m, 6H)

FD-mass spectrometry: 662 (M<sup>+</sup>)

Elemental analysis: Ti: 7.1% (7.2)

10 Calculated value in parentheses.

#### Synthesis Example 61

##### Synthesis of compound B-30


After charging 0.51 g (1.86 mmol) of compound L30  
 15 and 50 ml of diethyl ether into a 100 ml reactor which  
 had been adequately dried and substituted with argon,  
 they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise  
 adding 1.20 ml of n-butyllithium (1.61 mmol/ml n-hexane  
 solution, 1.93 mmol) over 5 minutes, the temperature was  
 20 slowly increased to room temperature and stirring was  
 continued for 4 hours at room temperature to prepare a

lithium salt solution. The solution was added dropwise to a solution of zirconium tetrachloride (0.22 g, 0.94 mmol) in 60 ml of tetrahydrofuran which had been cooled to -78°C. After completion of the dropwise addition,

5 stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 12 hours at room temperature, 60 ml of toluene was added, and the reaction solution was heated at 85°C for 12 hours while stirring.

10 The solvent of the reaction solution was distilled off. The resulting solid was reslurried with 100 ml of diethyl ether, the slurry was filtered with a glass filter to remove off the insoluble portion, and then the filtrate was concentrated under reduced pressure. The  
15 deposited solid was washed with hexane and dried under reduced pressure to obtain 0.10 g (0.14 mmol, 15% yield) of compound B-30 as a milky white powder represented by the formula given below.

276



$^1\text{H-NMR}(\text{CDCl}_3)$ : 0.80-2.10 (m, 20H), 1.45 (s, 18H), 2.40 (s, 6H), 3.75 (brdt, 2H), 6.50-7.80 (m, 6H)

5 FD-mass spectrometry: 704 ( $\text{M}^+$ )

Elemental analysis: Zr: 13.3% (12.9)

Calculated value in parentheses.

#### Synthesis Example 62

##### 10 Synthesis of compound A-31

After charging 1.00 g (4.22 mmol) of compound L31 and 20 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise adding 2.75 ml of n-butyllithium (1.61 mmol/ml n-hexane solution, 4.43 mmol) over 5 minutes, the temperature was slowly increased to room temperature, and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly added dropwise to a mixed solution containing 4.22 ml of

15


20



a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 2.11 mmol) and 20 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ .

After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After stirring for 12 hours at room temperature, the reaction solution was filtered with a glass filter. The filtered substance was dissolved in 50 ml of methylene chloride, and the insoluble portion was removed. The filtrate was evaporated to dryness under reduced pressure, and the resulting solid was reprecipitated with methylene chloride and diethyl ether and dried under reduced pressure to obtain 0.90 g (1.55 mmol, 72% yield) of compound A-31 as a brown powder.

Compound A-31



$^1\text{H-NMR}(\text{CDCl}_3)$ : 6.70-7.40 (m, 16H), 7.90-8.20 (m, 2H)

FD-mass spectrometry: 578 (M $^{+}$ )

Elemental analysis: Ti: 8.0% (8.3)

Calculated value in parentheses.

Synthesis Example 63


5        Synthesis of compound B-31

After charging 1.20 g (5.18 mmol) of compound L31 and 24 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise  
10 adding 3.38 ml of n-butyllithium (1.61 mmol/ml n-hexane solution, 5.44 mmol) over 5 minutes, the temperature was slowly increased to room temperature, and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then added  
15 dropwise to a mixed solution containing zirconium tetrachloride (0.60 g, 2.57 mmol) and 24 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature.  
20 After stirring for 12 hours at room temperature, the reaction solution was filtered with a glass filter. The filtered substance was dissolved in 60 ml of methylene chloride and the insoluble portion was removed. The filtrate was concentrated under reduced pressure, and  
25 the deposited solid was reprecipitated with methylene

chloride and hexane and dried under reduced pressure to obtain 0.20 g (0.32 mmol, 12% yield) of compound B-31 as a green powder.

5

Compound B-31



$^1\text{H-NMR}(\text{CDCl}_3)$ : 6.70-7.45 (m, 16H), 7.90-8.25 (m, 2H)

10 FD-mass spectrometry: 621 (M+)

Elemental analysis: Zr: 14.9% (14.6)

Calculated value in parentheses.


#### Synthesis Example 64

15 Synthesis of compound A-32

After charging 1.00 g (5.05 mmol) of compound L32 and 50 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise  
 20 adding 3.25 ml of n-butyllithium (1.63 mmol/ml n-hexane solution, 5.30 mmol) over 5 minutes, the temperature was

slowly increased to room temperature, and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was cooled to -78°C, and then 2.52 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 1.26 mmol) was slowly added dropwise. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 12 hours at room temperature, the reaction solution was filtered with a glass filter and the filtered substance was washed with diethyl ether followed by dissolution in methylene chloride. After removal of the insoluble portion, the filtrate was concentrated under reduced pressure, and the deposited solid was washed with hexane and dried under reduced pressure to obtain 0.23 g (0.45 mmol, 18% yield) of compound A-32 as an orange powder.

Compound A-32



FD-mass spectrometry: 512 (M+)

Synthesis Example 65


5        Synthesis of compound A-33

After charging 1.09 g (4.39 mmol) of compound L33 and 70 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to -78°C and stirred. After dropwise  
10 adding 2.80 ml of n-butyllithium (1.63 mmol/ml n-hexane solution, 4.56 mmol) over 5 minutes, the temperature was slowly increased to room temperature, and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was cooled to  
15 -78°C, and then 8.78 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 4.39 mmol) was slowly added dropwise. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further  
20 stirring for 12 hours at room temperature, the reaction solution was filtered with a glass filter and the filtered substance was washed with diethyl ether followed by dissolution in methylene chloride. After removal of the insoluble portion, the filtrate was  
25 concentrated under reduced pressure, and the deposited

solid was washed with diethyl ether and dried under reduced pressure to obtain 0.22 g (0.36 mmol, 16% yield) of compound A-33 as a brown powder.

5

Compound A-33



FD-mass spectrometry: 612 (M<sup>+</sup>)

10


#### Synthesis Example 66

##### Synthesis of compound A-34

After charging 0.60 g (2.13 mmol) of compound L34 and 40 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to -78°C and stirred. After dropwise adding 2.75 ml of n-butyllithium (1.63 mmol/ml n-hexane solution, 4.48 mmol) over 5 minutes, the temperature was slowly increased to room temperature, and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was cooled to

5 temperature. After further stirring for 8 hours at room  
temperature, the reaction solution was filtered with a  
glass filter and the filtered substance was washed with  
diethyl ether followed by dissolution in methylene  
chloride. After removal of the insoluble portion, the  
0 filtrate was concentrated under reduced pressure, and  
the deposited solid was washed with hexane and dried  
under reduced pressure to obtain 0.19 g (0.48 mmol, 23%  
yield) of compound A-34 as a red powder.

## 15



20

Synthesis of compound A-35

After charging 0.19 g of sodium hydride (60 wt% product, 4.75 mmol) and 50 ml of tetrahydrofuran into a 100 ml reactor which had been adequately dried and substituted with argon, a solution of 1.00 g (2.30 mmol) of compound L35 in 20 ml of tetrahydrofuran was added dropwise over 5 minutes while stirring at room temperature, after which the temperature was slowly increased to room temperature, and stirring was continued for 2 hours at 50°C to prepare a sodium salt solution. The solution was then slowly added dropwise to a solution of 0.77 g (2.31 mmol) of a titanium tetrachloride·tetrahydrofuran complex in 50 ml of tetrahydrofuran while stirring at room temperature. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 8 hours at room temperature, the reaction solution was filtered with a glass filter and the filtered substance was washed with diethyl ether followed by removal of the insoluble portion. The filtrate was concentrated under reduced pressure, the deposited solid was reslurried with diethyl ether, the reaction solution was filtered with a glass filter. The filtered substance was washed with diethyl ether and dissolved in methylene chloride, and the impurities were removed. The filtrate was



5

The chemical structure of the catalyst complex (10) is shown. It features a central titanium atom (Ti) bonded to two chlorine atoms (Cl) and two oxygen atoms (O). The oxygen atoms are part of two phenyl rings, each substituted with a phenyl group (Ph) and a nitrogen atom (N). The nitrogen atoms are further substituted with a phenyl group (Ph) and a chlorine atom (Cl). The structure is symmetrical, with the titanium atom at the center and the phenyl rings extending outwards.

15

Synthesis of compound A-36


20

[illegible]

solution. The solution was cooled to  $-78^{\circ}\text{C}$ , and then 4.50 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 2.25 mmol) was slowly added dropwise. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 8 hours at room temperature, the reaction solution was filtered with a glass filter and the filtered substance was washed with diethyl ether and dissolved in methylene chloride. After removal of the insoluble portion, the filtrate was concentrated under reduced pressure, and the deposited solid was washed with hexane and dried under reduced pressure to obtain 0.55 g (0.97 mmol, 44% yield) of compound A-36 as an orange powder.

15

Compound A-36



20 FD-mass spectrometry: 564 (M+)


Synthesis of compound B-37

After charging 0.30 g of sodium hydride (60 wt% product; 7.50 mmol) and 50 ml of tetrahydrofuran into a 100 ml reactor which had been adequately dried and substituted with argon, a solution of 1.00 g (3.16 mmol) of compound L37 in 20 ml of tetrahydrofuran was added dropwise over 5 minutes while stirring at room temperature, after which the temperature was slowly increased to room temperature, and stirring was continued for 2 hours at 60°C to prepare a sodium salt solution. The solution was then slowly added dropwise to a solution of 1.19 g (3.15 mmol) of zirconium tetrachloride·2THF complex in 50 ml of tetrahydrofuran while stirring at room temperature. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 8 hours at room temperature, the reaction solution was filtered with a glass filter, the filtered substance was washed with tetrahydrofuran and the insoluble portion was removed. The filtrate was concentrated under reduced pressure to about 1/3, the deposited solid was filtered with a glass filter, and the filtered substance was washed with cold tetrahydrofuran and dried under reduced pressure to

obtain 1.00 g (2.10 mmol, 66% yield) of compound B-37 as a yellow powder.

Compound B-37

5



FD-mass spectrometry: 474 (M+)


10 Synthesis Example 70

Synthesis of compound B-38

After charging 0.23 g of sodium hydride (60 wt% product, 5.75 mmol) and 50 ml of tetrahydrofuran into a 100 ml reactor which had been adequately dried and substituted with argon, a solution of 1.00 g (2.73 mmol) of compound L38 in 20 ml of tetrahydrofuran was added dropwise over 5 minutes while stirring at room temperature, after which the temperature was slowly increased to room temperature, and stirring was continued for 2 hours at 50°C to prepare a sodium salt solution. The solution was then slowly added dropwise

- to a solution of 1.03 g (2.73 mmol) of zirconium tetrachloride·2THF complex in 50 ml of tetrahydrofuran while stirring at room temperature. After completion of the dropwise addition, stirring was continued while
- 5 slowly increasing the temperature to room temperature. After further stirring for 8 hours at room temperature, the reaction solution was filtered with a glass filter, the filtered substance was washed with tetrahydrofuran and the insoluble portion was removed by filtration.
- 10 The filtrate was allowed to stand for 2 hours, upon which a solid was deposited. The deposited solid was filtered with a glass filter, and the filtered substance was washed with cold tetrahydrofuran and dried under reduced pressure to obtain 1.15 g (2.18 mmol, 80% yield)
- 15 of compound B-38 as a yellow powder.

Compound B-38



FD-mass spectrometry: 524 (M+)

Synthesis Example 71


Synthesis of compound A-39

5        After charging 0.50 g (1.87 mmol) of compound L39  
and 50 ml of diethyl ether into a 100 ml reactor which  
had been adequately dried and substituted with argon,  
they were cooled to -78°C and stirred. After dropwise  
adding 1.20 ml of n-butyllithium (1.61 mmol/ml n-hexane  
10       solution, 1.93 mmol) over 5 minutes, the temperature was  
slowly increased to room temperature, and stirring was  
continued for 4 hours at room temperature to prepare a  
lithium salt solution. The solution was slowly added  
dropwise to a mixed solution containing 1.87 ml of a  
15       titanium tetrachloride solution (0.5 mmol/ml heptane  
solution, 0.94 mmol) and 70 ml of diethyl ether which  
had been cooled to -78°C. After completion of the  
dropwise addition, stirring was continued while slowly  
increasing the temperature to room temperature. After  
20       further stirring for 8 hours at room temperature, the  
reaction solution was filtered with a glass filter, and  
the filtered substance was washed with diethyl ether and  
then dissolved in methylene chloride. The insoluble  
portion was removed, the filtrate was then concentrated  
25       under reduced pressure, and the deposited solid was

washed with hexane and dried under reduced pressure to obtain 0.11 g (0.17 mmol, 18% yield) of compound A-39 as a red powder.

5

Compound A-39



$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.65 (s, 18H), 4.65 (d, 2H), 5.00 (d, 2H),  
 10 6.75-7.70 (m, 16H), 7.75 (s, 2H)  
 FD-mass spectrometry: 650 (M+)  
 Elemental analysis: Ti: 7.2% (7.3)  
 Calculated value in parentheses.

## 15 Synthesis Example 72

### Synthesis of compound B-39


After charging 0.50 g (1.87 mmol) of compound L39 and 40 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon,  
 20 they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise adding 1.20 ml of n-butyllithium (1.61 mmol/ml n-hexane solution, 1.93 mmol) over 5 minutes, the temperature was

slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then added dropwise to a solution of zirconium tetrachloride·2THF complex (0.352 g, 0.93 mmol) in 50 ml of tetrahydrofuran which had been cooled to -78°C. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 8 hours at room temperature, the reaction solution was heated at 60°C for 3 hours while stirring, and the solvent was then distilled off. The resulting solid was reslurried with 50 ml of diethyl ether and the insoluble portion was separated off with a glass filter. The filtered substance was washed with 100 ml of diethyl ether and dissolved in methylene chloride, the insoluble portion was removed off, and the filtrate was concentrated under reduced pressure. The deposited solid was washed with hexane and dried under reduced pressure to obtain 0.30 g (0.43 mmol, 46% yield) of compound B-39 as a yellowish white powder represented by the formula given below.

Compound B-39



293



$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.60 (s, 18H), 4.65 (d, 2H), 4.95 (d, 2H),  
6.70-7.70 (m, 16H), 7.85 (s, 2H)

5 FD-mass spectrometry: 694 (M<sup>+</sup>)

Elemental analysis: Zr: 12.9% (13.1)

Calculated value in parentheses.

#### Synthesis Example 73

##### 10 Synthesis of compound A-40


After charging 0.58 g (2.02 mmol) of compound L40 and 40 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to -78°C and stirred. After dropwise adding 1.50 ml of n-butyllithium (1.61 mmol/ml n-hexane solution, 2.42 mmol) over 5 minutes, the temperature was slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly added dropwise to a mixed solution containing 2.00 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane

15

20

solution, 1.00 mmol) and 80 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 8 hours at room temperature, the reaction solution was filtered with a glass filter, the insoluble portion was removed, and the filtrate was concentrated under reduced pressure. The deposited solid was reprecipitated with hexane at  $-78^{\circ}\text{C}$  and dried under reduced pressure to obtain 0.19 g (0.28 mmol, 28% yield) of compound A-40 as a red orange powder.

Compound A-40



$^1\text{H-NMR}(\text{CDCl}_3)$ : 0.80-1.80 (m, 18H), 6.50-7.90 (m, 14H),  
8.00-8.20 (m, 2H)

FD-mass spectrometry: 692 (M $^{+}$ )

Elemental analysis: Ti: 7.0% (6.9)


Calculated value in parentheses.

Synthesis Example 74Synthesis of compound B-40

After charging 0.58 g (2.02 mmol) of compound L40  
5 and 40 ml of diethyl ether into a 100 ml reactor which  
had been adequately dried and substituted with argon,  
they were cooled to -78°C and stirred. After dropwise  
adding 1.50 ml of n-butyllithium (1.61 mmol/ml n-hexane  
solution, 2.42 mmol) over 5 minutes, the temperature was  
10 slowly increased to room temperature and stirring was  
continued for 4 hours at room temperature to prepare a  
lithium salt solution. The solution was then slowly  
added dropwise to a mixed solution containing a  
zirconium tetrachloride·2THF complex (0.38 g, 1.00 mmol)  
15 and 80 ml of tetrahydrofuran which had been cooled to  
-78°C. After completion of the dropwise addition,  
stirring was continued while slowly increasing the  
temperature to room temperature. After further stirring  
for 8 hours at room temperature, the solvent of the  
20 reaction solution was distilled off. The resulting  
solid was reslurried with 150 ml of diethyl ether, the  
insoluble portion was removed off with a glass filter,  
and then the filtrate was concentrated under reduced  
pressure. The deposited solid was reprecipitated with  
25 hexane at -78°C and dried under reduced pressure to

obtain 0.23 g (0.31 mmol, 31% yield) of compound B-40 as a yellow powder represented by the formula given below.

Compound B-40



$^1\text{H-NMR}(\text{CDCl}_3)$ : 0.80-1.70 (m, 18H), 6.50-7.90 (m, 14H),  
8.20 (s, 2H)

FD-mass spectrometry: 734 (M+)

Elemental analysis: Zr: 12.2% (12.4)

Calculated value in parentheses.

#### Synthesis Example 75


##### 15      Synthesis of compound A-41

After charging 0.50 g (1.15 mmol) of compound L41 and 10 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^\circ\text{C}$  and stirred. After dropwise  
20 adding 1.47 ml of n-butyllithium (1.61 mmol/ml n-hexane solution, 2.36 mmol) over 5 minutes, the temperature was

slowly increased to room temperature and stirring was continued for 4 hours at room temperature to prepare a lithium salt solution. The solution was then slowly added dropwise to a mixed solution containing 2.3 ml of a titanium tetrachloride solution (0.5 mmol/ml heptane solution, 1.15 mmol) and 10 ml of diethyl ether which had been cooled to  $-78^{\circ}\text{C}$ . After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After further stirring for 8 hours at room temperature, the solvent of the reaction solution was distilled off, and the resulting solid was dissolved in 25 ml of methylene chloride. The insoluble portion was filtered off with a glass filter, the filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with diethyl ether, methylene chloride and hexane and dried under reduced pressure to obtain 0.49 g (0.93 mmol, 76% yield) of compound A-41 as an orange powder.

20

Compound A-41



FD-mass spectrometry: 525 (M+)

Elemental analysis: Ti: 8.9% (9.1)

5 Calculated value in parentheses.


#### Synthesis Example 76

##### Synthesis of compound B-41

After charging 0.50 g (1.15 mmol) of compound L41  
 10 and 10 ml of diethyl ether into a 100 ml reactor which  
 had been adequately dried and substituted with argon,  
 they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise  
 adding 1.47 ml of n-butyllithium (1.61 mmol/ml n-hexane  
 solution, 2.36 mmol) over 5 minutes, the temperature was  
 15 slowly increased to room temperature, and stirring was  
 continued for 4 hours at room temperature to prepare a  
 lithium salt solution. The solution was then added  
 dropwise to a solution of zirconium tetrachloride $\cdot$ 2THF  
 (0.43 g, 1.15 mmol) in 10 ml of tetrahydrofuran which  
 20 had been cooled to  $-78^{\circ}\text{C}$ . After completion of the

dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After first stirring for 8 hours at room temperature and then stirring for 12 hours under reflux, the solvent of the reaction solution was distilled off. The resulting solid was dissolved in 25 ml of methylene chloride, and the insoluble portion was removed with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with methylene chloride, diethyl ether and hexane and dried under reduced pressure to obtain 0.36 g (0.63 mmol, 51% yield) of compound B-41 as a yellow powder.

Compound B-41



$^1\text{H-NMR}(\text{CDCl}_3)$ : 1.41 (s, 18H), 2.10 (s, 2H), 3.70 (s, 2H), 6.94 (t, 2H), 7.30 (dd, 2H), 7.50 (dd, 2H), 8.39 (s, 2H)

FD-mass spectrometry: 568 ( $\text{M}^+$ )

Elemental analysis: Zr: 16.2% (16.0)

Calculated value in parentheses.

Synthesis Example 77Synthesis of compound A-42


After charging 0.500 g (1.22 mmol) of compound L42  
5 and 10 ml of diethyl ether into a 100 ml reactor which  
had been adequately dried and substituted with argon,  
they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise  
adding 1.52 ml of n-butyllithium (1.61 mmol/ml n-hexane  
solution, 2.45 mmol) over 5 minutes, the temperature was  
10 slowly increased to room temperature, and stirring was  
continued for 4 hours at room temperature to prepare a  
lithium salt solution. The solution was then slowly  
added dropwise to a mixed solution containing 2.45 ml of  
a titanium tetrachloride solution (0.5 mmol/ml heptane  
15 solution, 1.23 mmol) and 10 ml of diethyl ether which  
had been cooled to  $-78^{\circ}\text{C}$ . After completion of the  
dropwise addition, stirring was continued while slowly  
increasing the temperature to room temperature. After  
stirring for 8 hours at room temperature, the solvent of  
20 the reaction solution was distilled off, and the  
resulting solid was dissolved in 25 ml of methylene  
chloride. After filtering the insoluble portion with a  
glass filter, the filtrate was concentrated under  
reduced pressure, and the deposited solid was  
25 reprecipitated with diethyl ether, methylene chloride



and hexane and dried under reduced pressure to obtain 0.25 g (0.45 mmol, 40% yield) of compound A-42 as a red brown powder.

5

Compound A-42



FD-mass spectrometry: 552 (M+)

10 Elemental analysis: Ti: 9.0% (8.7)

Calculated value in parentheses.

#### Synthesis Example 78


##### Synthesis of compound B-42

15 After charging 0.50 g (1.22 mmol) of compound L42 and 10 ml of diethyl ether into a 100 ml reactor which had been adequately dried and substituted with argon, they were cooled to  $-78^{\circ}\text{C}$  and stirred. After dropwise adding 1.52 ml of n-butyllithium (1.61 mmol/ml n-hexane solution, 2.45 mmol) over 5 minutes, the temperature was

20 slowly increased to room temperature, and stirring was continued for 4 hours at room temperature to prepare a

lithium salt solution. The solution was then added dropwise to a solution of zirconium tetrachloride·2THF (0.46 g, 1.22 mmol) in 10 ml of tetrahydrofuran which had been cooled to -78°C. After completion of the dropwise addition, stirring was continued while slowly increasing the temperature to room temperature. After first stirring for 8 hours at room temperature and then stirring for 6 hours under reflux, the solvent of the reaction solution was distilled off. The resulting solid was dissolved in 25 ml of methylene chloride, and the insoluble portion was removed with a glass filter. The filtrate was concentrated under reduced pressure, and the deposited solid was reprecipitated with methylene chloride, diethyl ether and hexane and dried under reduced pressure to obtain 0.22 g (0.37 mmol, 32% yield) of compound B-42 as a yellow powder represented by the formula given below.

Compound B-42



FD-mass spectrometry: 596 (M+)

Elemental analysis: Zr: 15.5% (15.3)

Calculated value in parentheses.

5 All the procedures for transition metal complex synthesis were conducted under an argon or nitrogen atmosphere, and the solvent employed was a commercially available anhydrous solvent.

10 Specific examples for polymerization processes according to the present invention are given below.

Example 1

15 To a 500 ml glass autoclave thoroughly purged with nitrogen, 250 ml of toluene was introduced, and the liquid phase and the gas phase were saturated with 100 l/hr of ethylene. Thereafter, 1.1875 mmol (in terms of aluminum atom) of methylaluminoxane (MAO) was added, and successively 0.00475 mmol of the compound A-1 obtained  
20 in Synthesis Example 1 was added to initiate polymerization. The reaction was conducted at 25 °C for 30 minutes in an ethylene gas atmosphere at normal pressure, and then a small amount of isobutanol was added to terminate the polymerization. After the  
25 polymerization was completed, the reaction product was introduced into a large amount of methanol to

precipitate a polymer in the whole amount. Then, hydrochloric acid was added, and filtration was effected using a glass filter. The resulting polymer was vacuum dried at 80 °C for 10 hours, to obtain 8.02 g of  
5 polyethylene (PE).

The polymerization activity was 3,400 g/mmol-Ti·hr, and the intrinsic viscosity  $[\eta]$  of the polyethylene was 8.44 dl/g.

10 Example 2

To a 500 ml glass autoclave thoroughly purged with nitrogen, 250 ml of toluene was introduced, and the liquid phase and the gas phase were saturated with 100 l/hr of ethylene. Thereafter, 1.25 mmol (in terms of  
15 aluminum atom) of methylaluminoxane and 0.005 mmol of the compound A-1 were added to initiate polymerization. The polymerization was conducted at 50 °C for 10 minutes, and then a small amount of isobutanol was added to terminate the polymerization.

20 The polymer suspension obtained was introduced into 1.5 liters of methanol containing a small amount of hydrochloric acid to precipitate a polymer. Then, filtration was effected using a glass filter to remove the solvent. The resulting polymer was washed with  
25 methanol and vacuum dried at 80 °C for 10 hours, to

obtain 3.30 g of polyethylene. The polymerization activity was 3,960 g/mmol-Ti·hr, and the intrinsic viscosity  $[\eta]$  of the polyethylene was 6.37 dl/g.

5    Example 3

Polymerization was carried out in the same manner as in Example 2, except that the polymerization temperature was varied to 75 °C. The results are set forth in Table 1.

10

Example 4

Polymerization was carried out in the same manner as in Example 2, except that the polymerization temperature was varied to 25 °C and 2 l/hr of hydrogen was fed together with ethylene. The results are set forth in Table 1.

15

Example 5 (TA-1, B)

To a 500 ml glass autoclave thoroughly purged with nitrogen, 250 ml of toluene was introduced, and the liquid phase and the gas phase were saturated with 100 l/hr of ethylene. Thereafter, 0.25 mmol of triisobutylaluminum (TIBA) was added, and successively 0.005 mmol of the compound A-1 and 0.006 mmol of triphenylcarbeniumtetrakis(pentafluorophenyl)borate

25

(TrB) were added to initiate polymerization. The reaction was conducted at 25 °C for 1 hour in an ethylene gas atmosphere at normal pressure, and then a small amount of isobutanol was added to terminate the polymerization. After the polymerization was completed, the reaction product was introduced into a large amount of methanol to precipitate a polymer in the whole amount. Then, hydrochloric acid was added, and filtration was effected using a glass filter. The resulting polymer was vacuum dried at 80 °C for 10 hours, to obtain 0.50 g of polyethylene.

The polymerization activity was 100 g/mmol-Ti·hr, and the intrinsic viscosity  $[\eta]$  of the polyethylene was 10.6 dl/g.

#### Example 6

To a 500 ml glass autoclave thoroughly purged with nitrogen, 250 ml of toluene was introduced, and the liquid phase and the gas phase were saturated with 100 l/hr of ethylene. Thereafter, 0.25 mmol of triisobutylaluminum, 0.005 mmol of the compound A-1 and 0.006 mmol of triphenylcarbeniumtetrakis(pentafluorophenyl)borate were added to initiate polymerization. The polymerization was conducted at 75 °C for 30 minutes, and then a small

amount of isobutanol was added to terminate the polymerization.

The polymer suspension obtained was introduced into 1.5 liters of methanol containing a small amount of hydrochloric acid to precipitate a polymer. Then, filtration was effected using a glass filter to remove the solvent. The resulting polymer was washed with methanol and vacuum dried at 80 °C for 10 hours, to obtain 0.71 g of polyethylene. The polymerization activity was 280 g/mmol-Ti·hr, and the intrinsic viscosity  $[\eta]$  of the polyethylene was 7.22 dl/g.

#### Example 7

To a 500 ml glass autoclave thoroughly purged with nitrogen, 250 ml of toluene was introduced, and the liquid phase and the gas phase were saturated with 100 l/hr of ethylene. Thereafter, 2.5 mmol (in terms of aluminum atom) of methylaluminoxane was added, and successively 0.005 mmol of the zirconium compound B-1 was added to initiate polymerization. The reaction was conducted at 25 °C for 5 minutes in an ethylene gas atmosphere at normal pressure, and then a small amount of isobutanol was added to terminate the polymerization. After the polymerization was completed, the reaction product was introduced into a large amount of methanol

to precipitate a polymer in the whole amount. Then, hydrochloric acid was added, and filtration was effected using a glass filter. The resulting polymer was vacuum dried at 80 °C for 10 hours, to obtain 6.10 g of

5 polyethylene.

The polymerization activity was 14,600 g/mmol-Zr·hr, and the intrinsic viscosity  $[\eta]$  of the polyethylene was 0.30 dl/g.

10 Examples 8 - 24

Ethylene polymerization was carried out in the same manner as in Example 7, except that the polymerization conditions were varied to those shown in Table 1. The results are set forth in Table 1.

15

Example 25

To a 500 ml glass autoclave thoroughly purged with nitrogen, 250 ml of toluene was introduced, and the liquid phase and the gas phase were saturated with 100  
20 1/hr of ethylene. Thereafter, 0.25 mmol of triisobutylaluminum was added, and then a pre-mixed solution of 0.05 mmol of triisobutylaluminum, 0.005 mmol of the compound B-1 and 0.006 mmol of triphenylcarbeniumtetrakis(pentafluoro-phenyl)borate was  
25 added to initiate polymerization. The polymerization



was conducted at 25 °C for 5 minutes, and then a small amount of isobutanol was added to terminate the polymerization. The polymer solution obtained was introduced into 1.5 liters of methanol containing a small amount of hydrochloric acid to precipitate a polymer. The polymer was washed with methanol and vacuum dried at 80 °C for 10 hours, to obtain 0.99 g of polyethylene. The polymerization activity was 2,380 g/mmol-Zr·hr, and the intrinsic viscosity  $[\eta]$  of the polyethylene was 22.4 dl/g.

#### Example 26

To a 500 ml glass autoclave thoroughly purged with nitrogen, 250 ml of toluene was introduced, and the liquid phase and the gas phase were saturated with ethylene. Thereafter, 0.25 mmol of triisobutylaluminum was added, and successively 0.0005 mmol of the zirconium compound B-1 and 0.001 mmol of triphenylcarbeniumtetrakis(pentafluoro-phenyl)borate were added to initiate polymerization. The reaction was conducted at 25 °C for 10 minutes in an ethylene gas atmosphere at normal pressure. After the polymerization was completed, the reaction product was introduced into a large amount of methanol to precipitate a polymer in the whole amount. Then, hydrochloric acid was added,

and filtration was effected using a glass filter. The resulting polymer was vacuum dried at 80 °C for 10 hours, to obtain 0.34 g of polyethylene (PE).

The polymerization activity was 4,080 g/mmol-Zr·hr,  
5 and the intrinsic viscosity  $[\eta]$  of the polyethylene was 12.6 dl/g.

#### Examples 27 - 31

Ethylene polymerization was carried out in the same  
10 manner as in Example 26, except that the polymerization conditions were varied to those shown in Table 1. The results are set forth in Table 1.

Table 1

Results of ethylene polymerization at normal pressure

Ex.	Compound	Amount (mmol)	Cocatalyst	Amount (mmol)	Temp. (°C)	Time (min)	Yield (g)	Activity (g/mmol-M·h)	[ $\eta$ ] (dl/g)
1	A-1	0.00475	MAO	1.1875	25	30	8.02	3400	8.44
2	A-1	0.005	MAO	1.25	50	10	3.30	3960	6.37
3	A-1	0.005	MAO	1.25	75	10	3.14	3770	5.48
4	A-1	0.005	MAO	1.25	25	10	3.23	3880	3.53
5	A-1	0.005	TrB/TIBA	0.006/0.25	25	60	0.50	100	10.6
6	A-1	0.005	TrB/TIBA	0.006/0.25	75	30	0.71	280	7.22
7	B-1	0.005	MAO	2.5	25	5	6.10	14600	0.30
8	B-1	0.0005	MAO	0.5	25	5	4.85	116000	0.31
9	B-1	0.0002	MAO	1.25	25	5	3.29	197000	0.32
10	B-1	0.0001	MAO	0.5	25	5	2.72	326000	0.21
11	B-1	0.00002	MAO	1.25	25	5	0.77	462000	0.28
12	B-1	0.00002	MAO	1.25	40	5	0.90	540000	0.33
13	B-1	0.0002	MAO	1.25	0	5	3.09	185000	0.27
14	B-1	0.0002	MAO	1.25	10	5	3.64	218000	0.29
15	B-1	0.0002	MAO	1.25	30	5	3.70	222000	0.26
16	B-1	0.0002	MAO	1.25	40	5	4.21	253000	0.33
17	B-1	0.0002	MAO	1.25	50	5	2.95	177000	0.30
18	B-1	0.0002	MAO	1.25	60	5	2.99	179000	0.39
19	B-1	0.0002	MAO	1.25	70	5	2.11	127000	0.41
20	B-1	0.00008	MAO	1.25	25	5	2.67	401000	0.28
21	B-1	0.00008	MAO	1.25	25	15	7.58	379000	0.30
22	B-1	0.00008	MAO	1.25	25	30	12.42	311000	0.31
23	B-1	0.0002	MAO	1.25	50	15	5.89	118000	0.60
24	B-1	0.0002	MAO	1.25	50	30	9.67	96700	1.23
25	B-1	0.005	TrB/TIBA	0.006/0.30	25	5	0.99	2380	22.40
26	B-1	0.0005	TrB/TIBA	0.001/0.25	25	10	0.34	4080	12.6
27	B-1	0.001	TrB/TIBA	0.002/0.25	25	10	0.31	1860	15.0
28	B-1	0.0025	TrB/TIBA	0.005/0.25	25	10	1.28	3070	14.8
29	B-1	0.0005	TrB/TIBA	0.001/0.25	25	10	0.27	3240	20.1
30	B-1	0.0005	TrB/TIBA	0.001/0.25	50	10	0.22	2640	21.1
31	B-1	0.0005	TrB/TIBA	0.001/0.25	75	10	0.12	1440	16.3

MAO : Methylaluminoxane

TIBA: Triisobutylaluminum

TrB : Triphenylcarbeniumtetrakis(pentafluorophenyl)borate

Examples 32 - 36

Ethylene polymerization was carried out in the same manner as in Example 7, except that the compounds shown in Table 2 were used and the polymerization conditions were varied to those shown in Table 2. The results are set forth in Table 2.

## Results of ethylene polymerization at normal pressure

[illegible]

Examples 37 - 52

In the case where methylaluminoxane was used as a cocatalyst, ethylene polymerization was carried out in the same manner as in Example 7, except that the compounds shown in Table 3 were used and the polymerization conditions were varied to those shown in Table 3. In the case where triisobutylaluminum and triphenylcarbeniumtetrakis(pentafluorophenyl)borate were used as cocatalysts, ethylene polymerization was carried out in the same manner as in Example 26, except that the compounds shown in Table 3 were used and the polymerization conditions were varied to those shown in Table 3. The results are set forth in Table 3.

Table 3

EX.	Compound	Amount (mmol)	Cocatalyst	Amount (mmol)	Temp. (°C)	Time (min)	Yield (g)	Activity (g/mmol-M·h)	[ $\eta$ ] (dl/g)
37	B-2	0.005	MAO	1.25	25	30	0.69	270	8.32
38	B-3	0.005	MAO	1.25	25	30	2.15	860	0.4
39	A-6	0.005	MAO	1.25	25	5	0.54	1300	4.31
40	A-6	0.005	MAO	1.25	75	5	0.76	1820	4.31
41	B-6	0.0005	MAO	1.25	25	5	1.38	33100	0.24
42	A-7	0.005	MAO	1.25	25	5	1.93	4630	6.84
43	A-7	0.005	MAO	1.25	75	5	1.48	3550	5.34
44	B-7	0.005	MAO	1.25	25	5	1.72	4130	0.10
45	A-8	0.005	MAO	1.25	25	30	0.90	360	5.70
46	A-8	0.005	TrB/TIBA	0.006/0.25	25	30	1.03	410	4.70
47	B-8	0.0001	MAO	0.5	25	5	1.01	121000	0.21
48	B-8	0.005	TrB/TIBA	0.006/0.25	25	30	2.57	1030	14.2
49	A-9	0.005	TrB/TIBA	0.006/0.25	25	30	0.25	100	11.7
50	B-9	0.0001	MAO	0.5	25	5	0.27	32400	0.24
51	B-9	0.005	TrB/TIBA	0.006/0.25	25	5	2.87	6890	0.30
52	A-10	0.005	MAO	1.25	25	60	0.48	96	11.0

Examples 53 - 78

In the case where methylaluminoxane was used as a cocatalyst, ethylene polymerization was carried out in the same manner as in Example 7, except that the

5 compounds shown in Table 4 were used and the polymerization conditions were varied to those shown in Table 4. In the case where triisobutylaluminum and triphenylcarbeniumtetrakis(pentafluorophenyl)borate were used as cocatalysts, ethylene polymerization was carried

10 out in the same manner as in Example 26, except that the compounds shown in Table 4 were used and the polymerization conditions were varied to those shown in Table 4. The results are set forth in Table 4.



Table 4

EX.	Compound	Amount (mmol)	Cocatalyst	Amount (mmol)	Temp. (°C)	Time (min)	Yield (g)	Activity (g/mmol-M·h)	[ $\eta$ ] (dl/g)
53	A-11	0.005	MAO	1.25	25	5	2.57	6160	3.71
54	A-11	0.005	TrB/TIBA	0.006/0.25	25	30	0.95	380	7.22
55	B-11	0.0005	MAO	1.25	25	5	3.34	80000	0.42
56	B-11	0.005	TrB/TIBA	0.006/0.25	25	5	2.59	6220	0.48
57	A-12	0.005	MAO	1.25	25	5	3.28	7870	4.40
58	A-12	0.005	TrB/TIBA	0.006/0.25	25	30	1.81	724	10.0
59	B-12	0.0001	MAO	1.25	25	5	3.71	445200	0.45
60	B-12	0.005	TrB/TIBA	0.006/0.25	25	5	4.63	11100	0.46
61	A-13	0.005	MAO	1.25	25	5	1.13	2710	3.54
62	A-13	0.005	TrB/TIBA	0.006/0.25	25	30	0.92	370	5.57
63	B-13	0.0001	MAO	1.25	25	5	2.78	333600	0.22
64	B-13	0.005	TrB/TIBA	0.006/0.25	25	10	3.30	3960	10.7
65	A-14	0.005	MAO	1.25	25	5	1.93	4640	4.86
66	A-14	0.005	TrB/TIBA	0.006/0.25	25	30	0.29	120	7.63
67	B-14	0.0001	MAO	1.25	25	5	2.02	242400	0.31
68	B-14	0.005	TrB/TIBA	0.006/0.25	25	5	1.83	4390	0.69
69	A-15	0.005	MAO	1.25	25	10	2.05	2460	4.90
70	B-15	0.005	MAO	1.25	25	10	3.22	3870	0.74
71	A-16	0.005	MAO	1.25	25	30	0.71	280	3.47
72	B-16	0.005	MAO	1.25	25	10	0.41	490	0.58
73	A-17	0.005	MAO	1.25	25	30	1.52	608	5.50
74	B-17	0.005	MAO	1.25	25	30	2.16	860	0.40
75	A-18	0.005	MAO	1.25	25	30	0.34	136	3.98
76	B-18	0.0005	MAO	1.25	25	5	1.68	40300	4.42
77	B-18	0.005	TrB/TIBA	0.006/0.25	25	5	2.22	5330	1.87
78	B-19	0.005	TrB/TIBA	0.006/0.25	25	30	0.50	200	24.40

Examples 79 - 111

In the case where methylaluminoxane was used as a cocatalyst, ethylene polymerization was carried out in the same manner as in Example 7, except that the

5 compounds shown in Table 5 were used and the polymerization conditions were varied to those shown in Table 5. In the case where triisobutylaluminum and triphenylcarbeniumtetrakis(pentafluorophenyl)borate were used as cocatalysts, ethylene polymerization was carried

10 out in the same manner as in Example 26, except that the compounds shown in Table 5 were used and the polymerization conditions were varied to those shown in Table 5. The results are set forth in Table 5.

Table 5

EX.	Com- pound	Amount (mmol)	Cocatalyst	Amount (mmol)	Temp (°C)	Time (min)	Yield (g)	Activity (g/mmol·M·h)	[ $\eta$ ] (dl/g)
79	A-21	0.005	MAO	1.25	25	5	3.22	7730	6.34
80	A-21	0.005	TrB/TIBA	0.006/0.25	25	30	0.57	230	9.06
81	B-21	0.0001	MAO	1.25	25	5	1.24	148800	0.27
82	B-21	0.005	TrB/TIBA	0.006/0.25	25	5	1.18	2830	3.06
83	A-22	0.005	MAO	1.25	25	5	1.78	4270	4.00
84	B-22	0.0002	MAO	1.25	25	5	1.60	96000	0.41
85	B-22	0.005	TrB/TIBA	0.006/0.25	25	5	4.64	11100	0.24
86	A-23	0.005	MAO	1.25	25	10	0.38	460	1.53
87	B-23	0.005	MAO	1.25	25	30	2.34	940	0.31
88	A-24	0.005	TrB/TIBA	0.006/0.25	25	30	0.44	176	7.11
89	B-24	0.005	MAO	1.25	25	15	1.62	1300	2.03
90	B-24	0.005	TrB/TIBA	0.006/0.25	25	30	1.10	440	0.57
91	A-25	0.005	MAO	1.25	25	5	1.71	4100	6.55
92	A-25	0.005	TrB/TIBA	0.006/0.25	25	15	1.30	1040	10.5
93	B-25	0.0002	MAO	1.25	25	5	1.89	113000	0.44
94	B-25	0.005	TrB/TIBA	0.006/0.25	25	5	4.34	10400	0.44
95	A-26	0.005	MAO	1.25	25	5	1.04	2450	3.44
96	B-26	0.0001	MAO	61.25	25	5	2.62	314000	0.43
97	B-26	0.005	TrB/TIBA	0.006/0.25	25	5	0.95	2300	12.5
98	A-27	0.005	MAO	1.25	25	15	0.31	240	1.81
99	B-27	0.005	MAO	1.25	25	5	5.11	12300	6.34
100	B-27	5E-05	MAO	0.25	25	5	2.41	57800	10.6
101	B-27	2E-05	MAO	0.25	25	5	1.31	78400	7.73
102	B-27	0.005	TrB/TIBA	0.006/0.25	25	5	1.98	4750	5.67
103	A-28	0.005	MAO	1.25	25	5	1.35	3240	4.92
104	A-28	0.005	TrB/TIBA	0.006/0.25	25	30	0.34	140	12.4
105	B-28	0.0001	MAO	1.25	25	5	2.03	244000	0.76
106	B-28	0.005	TrB/TIBA	0.006/0.25	25	10	4.20	5040	19.6
107	A-29	0.005	TrB/TIBA	0.006/0.25	25	30	0.18	72	13.2
108	B-29	0.005	MAO	1.25	25	30	0.49	200	8.43
109	A-30	0.005	TrB/TIBA	0.006/0.25	25	30	0.16	60	19.7
110	B-30	0.005	MAO	1.25	25	30	0.30	120	12.0
111	B-30	0.005	TrB/TIBA	0.006/0.25	25	30	0.45	180	23.0

Examples 112 - 121

In the case where methylaluminoxane was used as a cocatalyst, ethylene polymerization was carried out in the same manner as in Example 7, except that the

5 compounds shown in Table 6 were used and the polymerization conditions were varied to those shown in Table 6. In the case where triisobutylaluminum and triphenylcarbeniumtetrakis(pentafluorophenyl)borate were used as cocatalysts, ethylene polymerization was carried

10 out in the same manner as in Example 26, except that the compounds shown in Table 6 were used and the polymerization conditions were varied to those shown in Table 6.

The results are set forth in Table 6.

Table 6

EX.	Compound	Amount (mmol)	Cocatalyst	Amount (mmol)	Temp. (°C)	Time (min)	Yield (g)	Activity (g/mmol-M·h)	[ $\eta$ ] (dl/g)
112	A-31	0.005	MAO	1.25	25	30	0.63	250	5.49
113	A-31	0.005	TrB/TIBA	0.006/0.25	25	30	0.49	200	15.30
114	B-31	0.005	MAO	1.25	25	30	1.38	550	0.99
115	A-32	0.005	MAO	1.25	25	60	0.02	2	8.81
116	A-35	0.005	MAO	1.25	25	60	0.01	4	9.09
117	A-39	0.005	MAO	1.25	25	30	0.10	40	1.66
118	B-39	0.005	MAO	1.25	25	5	1.06	2540	0.29
119	B-39	0.005	TrB/TIBA	0.006/0.25	25	20	1.10	660	4.42
120	A-40	0.005	MAO	1.25	25	30	1.10	440	4.59
121	B-40	0.005	MAO	1.25	25	30	0.25	200	1.28

Examples 122 - 130

In the case where methylaluminoxane was used as a cocatalyst, ethylene polymerization was carried out in the same manner as in Example 7, except that the

5 compounds shown in Table 7 were used and the polymerization conditions were varied to those shown in Table 7. In the case where triisobutylaluminum and triphenylcarbeniumtetrakis(pentafluorophenyl)borate were used as cocatalysts, ethylene polymerization was carried

10 out in the same manner as in Example 26, except that the compounds shown in Table 7 were used and the polymerization conditions were varied to those shown in Table 7.

The results are set forth in Table 7.

Table 7

EX.	Compound	Amount (mmol)	Cocatalyst	Amount (mmol)	Temp (°C)	Time (min)	Yield (g)	Activity (g/mmol-M·h)	[ $\eta$ ] (dl/g)
122	A-34	0.005	MAO	1.25	25	60	0.01	2	6.31
123	A-35	0.005	MAO	1.25	25	60	0.05	10	5.88
124	A-36	0.005	MAO	1.25	25	60	0.03	6	7.77
125	B-37	0.005	MAO	1.25	25	60	0.01	2	6.09
126	B-38	0.005	MAO	1.25	25	60	0.01	2	8.03
127	A-41	0.005	MAO	1.25	25	15	0.96	770	4.00
128	B-41	0.005	TrB/TIBA	0.006/0.25	25	5	0.59	1420	7.07
129	A-43	0.005	TrB/TIBA	0.006/0.25	25	15	0.18	140	6.81
130	B-43	0.005	TrB/TIBA	0.006/0.25	25	15	1.35	1080	0.84

20120303 09:22:50

Example 131

To a 500 ml glass autoclave thoroughly purged with nitrogen, 250 ml of toluene was introduced, and the liquid phase and the gas phase were saturated with a mixed gas of 50 l/hr of ethylene and 150 l/hr of propylene. Thereafter, 1.25 mmol (in terms of aluminum atom) of methylaluminoxane and 0.005 mmol of the compound A-1 were added to initiate polymerization. The polymerization was conducted at 25 °C for 15 minutes, and then a small amount of isobutanol was added to terminate the polymerization.

The polymer suspension obtained was introduced into 1.5 liters of methanol containing a small amount of hydrochloric acid to precipitate a polymer. Then, filtration was effected using a glass filter to remove the solvent. The resulting polymer was washed with methanol and vacuum dried at 80 °C for 10 hours, to obtain 0.95 g of an ethylene/propylene copolymer. The polymerization activity was 760 g/mmol-Ti·hr, the propylene content as measured by IR was 4.67 % by mol, and the intrinsic viscosity  $[\eta]$  of the copolymer was 2.21 dl/g.

Example 132



To a 500 ml glass autoclave thoroughly purged with nitrogen, 250 ml of toluene was introduced, and the liquid phase and the gas phase were saturated with a mixed gas of 100 l/hr of ethylene and 100 l/hr of propylene. Thereafter, 0.25 mmol of triisobutylaluminum was added, and then a pre-mixed solution of 0.025 mmol of triisobutylaluminum, 0.0025 mmol of the compound B-1 and 0.005 mmol of triphenylcarbeniumtetrakis(pentafluorophenyl)borate (TrB) was added to initiate polymerization. The polymerization was conducted at 50 °C for 5 minutes, and then a small amount of isobutanol was added to terminate the polymerization.

The polymer solution obtained was introduced into 1.5 liters of methanol containing a small amount of hydrochloric acid to precipitate a polymer. The polymer was washed with methanol and vacuum dried at 130 °C for 10 hours, to obtain 1.63 g of an ethylene/propylene copolymer. The polymerization activity was 7,820 g/mmol-Zr·hr, the propylene content as measured by IR was 20.7 % by mol, and the intrinsic viscosity  $[\eta]$  of the copolymer was 13.4 dl/g.

Example 133

Copolymerization was carried out in the same manner as in Example 132, except that the compound B-1 was used, the flow rates of ethylene and propylene were varied to 50 l/hr and 150 l/hr, respectively, and the  
5 polymerization temperature and the amounts of the catalysts were varied to those shown in Table 8.

The results are set forth in Table 8.

Examples 134 - 149

10 Copolymerization was carried out in the same manner as in Example 131, except that the compounds shown in Table 8 were used.

The results are set forth in Table 8.

Table 8

Results of ethylene/propylene copolymerization  
at normal pressure

Ex.	Compound	Amount (mmol)	Cocatalyst	Amount (mmol)	Temp. (°C)	Time (min)	Yield (g)	Activity (g/mmol-M·h)	$[\eta]$ (dl/g)	Propylene content (mol%)
131	A-1	0.005	MAO	1.25	25	15	0.95	760	2.21	4.67
132	B-1	0.0025	TrB/TIBA	0.005/0.275	50	5	1.63	7820	13.40	20.7
133	B-1	0.005	TrB/TIBA	0.006/0.3	25	10	1.28	1540	12.40	31.3
134	B-1	0.005	MAO	1.25	25	10	8.42	10100	0.03	29.2
135	C-1	0.005	MAO	1.25	25	10	2.30	2760	0.32	7.19
136	B-6	0.005	MAO	1.25	25	10	3.64	4370	0.14	10.2
137	B-8	0.005	MAO	1.25	25	10	4.15	4980	0.13	12.43
138	B-9	0.005	MAO	1.25	25	10	3.31	3970	0.13	8.3
139	A-11	0.005	MAO	1.25	25	10	0.69	830	0.80	7.8
140	A-12	0.005	MAO	1.25	25	10	0.37	400	0.41	3.8
141	B-12	0.005	MAO	1.25	25	10	4.14	4970	0.11	18.5
142	B-13	0.005	MAO	1.25	25	10	7.86	9430	0.05	30.1
143	B-18	0.005	MAO	1.25	25	10	1.92	2300	3.63	3.09
144	A-21	0.005	MAO	1.25	25	10	0.74	890	1.92	8.2
145	A-22	0.005	MAO	1.25	25	10	6.85	8220	0.08	15.4
146	B-25	0.005	MAO	1.25	25	10	3.36	4630	0.16	12.1
147	B-26	0.005	MAO	1.25	25	10	4.28	5140	0.05	26.3
148	B-27	0.005	MAO	1.25	25	10	3.55	4260	1.11	6.5
149	B-28	0.005	MAO	1.25	25	10	4.51	5410	0.19	14.5

Example 150

To a 500 ml glass autoclave thoroughly purged with nitrogen, 250 ml of toluene was introduced. Then, 100 l/hr of ethylene and 20 l/hr of butadiene were passed through the system. After 10 minutes, 5.0 mmol (in terms of aluminum atom) of methylaluminoxane was added, and successively 0.01 mmol of the titanium compound A-1 was added to initiate polymerization. The reaction was conducted at 25 °C for 20 minutes with passing the mixed gas of ethylene and butadiene at normal pressure, and then a small amount of methanol was added to terminate the polymerization. The reaction product was introduced into a large amount of hydrochloric acid/methanol to precipitate a polymer in the whole amount. The polymer was filtered with a glass filter and vacuum dried at 80 °C for 10 hours, to obtain 0.53 g of an ethylene/butadiene copolymer.

The polymerization activity per 1 mmol of titanium was 149 g, and the intrinsic viscosity  $[\eta]$  of the copolymer was 1.46 dl/g. The content of all the butadiene units in the copolymer, as determined by NMR analysis, was 0.9 % by mol (1,4-cis form + 1,4-trans form: 0.8 % by mol, 1,2-vinyl form: 0.1 % by mol, cyclopentane skeleton: less than 0.1 % by mol (lower than the detection limit)).

Example 151

Polymerization was carried out in the same manner as in Example 150, except that a zirconium compound B-1 was used in place of the titanium compound A-1. The yield of the copolymer was 2.65 g.

The polymerization activity per 1 mmol of zirconium was 3,180 g, and the intrinsic viscosity  $[\eta]$  of the copolymer was 0.70 dl/g. The content of all the butadiene units in the copolymer, as determined by NMR analysis, was 1.2 % by mol (1,4-cis form + 1,4-trans form: 1.1 % by mol, 1,2-vinyl form: 0.1 % by mol, cyclopentane skeleton: less than 0.1 % by mol (lower than the detection limit)).

15

Example 152

Polymerization was carried out in the same manner as in Example 151, except that the polymerization time was varied to 20 minutes and the flow rates of ethylene and butadiene were varied to 20 l/hr and 80 l/hr, respectively. The yield of the copolymer was 0.74 g.

The polymerization activity per 1 mmol of zirconium was 446 g, and the intrinsic viscosity  $[\eta]$  of the copolymer was 0.87 dl/g. The content of all the butadiene units in the copolymer, as determined by NMR

25

analysis, was 5.3 % by mol (1,4-cis form + 1,4-trans form: 4.7 % by mol, 1,2-vinyl form: 0.6 % by mol, cyclopentane skeleton: less than 0.1 % by mol (lower than the detection limit)).

5

Example 153

Polymerization was carried out in the same manner as in Example 151, except that the polymerization time was varied to 5 minutes and the flow rates of ethylene and butadiene were varied to 50 l/hr and 50 l/hr, respectively. The yield of the copolymer was 0.57 g.

The polymerization activity per 1 mmol of zirconium was 342 g, and the intrinsic viscosity  $[\eta]$  of the copolymer was 0.34 dl/g. The content of all the butadiene units in the copolymer, as determined by NMR analysis, was 2.4 % by mol (1,4-cis form + 1,4-trans form: 2.3 % by mol, 1,2-vinyl form: 0.1 % by mol, cyclopentane skeleton: less than 0.1 % by mol (lower than the detection limit)).

20

Example 154

Polymerization was carried out in the same manner as in Example 153, except that the polymerization temperature was varied to 50 °C. The yield of the copolymer was 0.627 g.

25

The polymerization activity was 1,488 g/mmol-Zr·hr, and the intrinsic viscosity  $[\eta]$  of the copolymer was 0.16 dl/g. The content of the butadiene units in the copolymer, as determined by NMR analysis, was 3.3 % by mol (1,4-cis form + 1,4-trans form: 3.2 % by mol, 1,2-vinyl form: 0.1 % by mol, cyclopentane skeleton: less than 0.1 % by mol (lower than the detection limit)).

#### Example 155

10 Polymerization was carried out in the same manner as in Example 153, except that the polymerization temperature was varied to 50 °C and the flow rates of ethylene and butadiene were varied to 40 l/hr and 60 l/hr, respectively. The yield of the copolymer was 0.37  
15 g.

The polymerization activity was 888 g/mmol-Zr·hr, and the intrinsic viscosity  $[\eta]$  of the copolymer was 0.17 dl/g. The content of the butadiene units in the copolymer, as determined by NMR analysis, was 4.8 % by  
20 mol (1,4-cis form + 1,4-trans form: 4.6 % by mol, 1,2-vinyl form: 0.2 % by mol, cyclopentane skeleton: less than 0.1 % by mol (lower than the detection limit)).

#### Example 156

Polymerization was carried out in the same manner as in Example 153, except that the polymerization temperature was varied to 60 °C and the flow rates of ethylene and butadiene were varied to 40 l/hr and 60  
5 l/hr, respectively. The yield of the copolymer was 0.417 g.

The polymerization activity was 984 g/mmol-Zr·hr, and the intrinsic viscosity  $[\eta]$  of the copolymer was 0.12 dl/g. The content of the butadiene units in the  
10 copolymer, as determined by NMR analysis, was 5.8 % by mol (1,4-cis form + 1,4-trans form: 5.6 % by mol, 1,2-vinyl form: 0.2 % by mol, cyclopentane skeleton: less than 0.1 % by mol (lower than the detection limit)). The molecular weight distribution ( $M_w/M_n$ ) as measured by  
15 the GPC was 1.85.

#### Example 157

Polymerization was carried out in the same manner as in Example 153, except that the polymerization  
20 temperature was varied to 50 °C and the flow rates of ethylene and butadiene were varied to 30 l/hr and 70 l/hr, respectively. The yield of the copolymer was 0.24 g.

The polymerization activity was 576 g/mmol-Zr·hr,  
25 and the intrinsic viscosity  $[\eta]$  of the copolymer was



0.14 dl/g. The content of the butadiene units in the copolymer, as determined by NMR analysis, was 6.6 % by mol (1,4-cis form + 1,4-trans form: 6.3 % by mol, 1,2-vinyl form: 0.2 % by mol, cyclopentane skeleton: less than 0.1 % by mol (lower than the detection limit)). The molecular weight distribution (Mw/Mn) as measured by the GPC was 2.05.

#### Example 158

10 To a 1-liter SUS autoclave thoroughly purged with nitrogen, 500 ml of heptane was introduced, and the gas phase and the liquid were saturated with ethylene at 50 °C. Then, 1.25 mmol (in terms of aluminum) of methylaluminoxane and 0.001 mmol of the compound A-1  
15 were added, and polymerization was performed for 15 minutes under an ethylene pressure of 8 kg/cm<sup>2</sup>-G.

To the polymer suspension obtained, 1.5 liters of methanol containing a small amount of hydrochloric acid was added to precipitate a polymer. Then, filtration  
20 was effected using a glass filter to remove the solvent. The resulting polymer was washed with methanol and vacuum dried at 80 °C for 10 hours, to obtain 11.22 g of polyethylene. The polymerization activity was 44.9 g/mmol-Ti·hr, and the intrinsic viscosity  $[\eta]$  of the  
25 polyethylene was 7.91 dl/g.

Examples 159 - 162

Polymerization was carried out in the same manner as in Example 158, except that the compounds shown in Table 9 were used and the polymerization conditions were varied to those shown in Table 9.

The results are set forth in Table 9.

20160101 09:00:00

Table 9

Examples of ethylene polymerization under pressure

Ex.	Compound	Amount (mmol)	Cocatalyst	Amount (mmol)	Temp. (°C)	Time (min)	Yield (g)	Activity (g/mmol-M·h)	[ $\eta$ ] (dl/g)
158	A-1	0.001	MAO	1.25	50	15	11.22	44.9	7.91
159	A-1	0.001	MAO	1.25	75	15	11.96	47.8	7.31
160	B-1	0.00005	MAO	1.25	50	15	14.90	1192	1.15
161	C-1	0.00025	MAO	1.25	50	15	8.28	132	2.30
162	A-7	0.001	MAO	1.25	50	15	4.83	19.3	4.44

158 159 160 161 162  
 A-1 A-1 B-1 C-1 A-7  
 0.001 0.001 0.00005 0.00025 0.001  
 MAO MAO MAO MAO MAO  
 1.25 1.25 1.25 1.25 1.25  
 50 75 50 50 50  
 15 15 15 15 15  
 11.22 11.96 14.90 8.28 4.83  
 44.9 47.8 1192 132 19.3  
 7.91 7.31 1.15 2.30 4.44

Example 163Preparation of solid catalyst component

In 154 liters of toluene, 10 kg of silica having been dried at 250 °C for 10 hours was suspended, and the suspension was cooled to 0 °C. Then, 57.5 liters of a methylaluminoxane solution ( $\text{Al} = 1.33 \text{ mol/l}$ ) was dropwise added over a period of 1 hour. During the addition, the temperature of the system was maintained at 0 °C, and the reaction was conducted at 0 °C for 30 minutes. Then, the temperature of the system was raised up to 95 °C over a period of 1.5 hours, and at this temperature the reaction was conducted for 20 hours. The temperature of the system was then lowered to 60 °C, and the supernatant liquid was removed by decantation.

15 The resulting solid catalyst component was washed twice with toluene and resuspended in toluene, to obtain a solid catalyst component (A) (whole volume: 200 liters).

22.4 Milliliters of the suspension of the solid catalyst component (A) as obtained above was transferred into a 200 ml glass flask, and then 175 ml of toluene and 4.8 ml of a toluene solution of the compound A-1 ( $\text{Ti} = 0.01 \text{ mmol/l}$ ) were added. The mixture was stirred at room temperature for 2 hours. The resulting suspension was washed three times with 200 ml of hexane, and hexane

was added to give 200 ml of a suspension and a solid catalyst component (B).

#### Polymerization

To a 2-liter SUS autoclave thoroughly purged with  
5 nitrogen, 1 liter of heptane was introduced, and the gas  
phase and the liquid were saturated with ethylene at 50  
°C. Then, 1.0 mmol of triisobutylaluminum and 0.005  
mmol (in terms of Ti atom) of the solid catalyst  
component (B) were added, and polymerization was  
10 performed for 90 minutes under an ethylene pressure of 8  
kg/cm<sup>2</sup>-G.

The polymer suspension obtained was filtered with a  
glass filter, washed twice with 500 ml of hexane and  
vacuum dried at 80 °C for 10 hours, to obtain 8.96 g of  
15 polyethylene. The polymerization activity was 1,790  
g/mmol-Ti·hr, and the intrinsic viscosity [ $\eta$ ] of the  
polyethylene was 11.7 dl/g.

#### Example 164

20 To a 200 ml reactor thoroughly purged with  
nitrogen, 60 ml of heptane and 40 ml of 1-hexene were  
introduced, and they were stirred at 25 °C. Thereafter,  
0.25 mmol of triisobutylaluminum was added, and then a  
mixed solution of 0.1 mmol of triisobutylaluminum, 0.01  
25 mmol of the compound A-1 and 0.012 mmol of

triphenylcarbeniumtetrakis(penta-fluorophenyl)borate was added to initiate polymerization. The reaction was conducted at 25 °C for 1 hour, and then a small amount of isobutanol was added to terminate the polymerization.

- 5        The polymer suspension obtained was added little by little to 1 liter of acetone to precipitate a polymer. The polymer was separated from the solvent and vacuum dried at 130 °C for 10 hours, to obtain 3.15 g of polyhexene. The polymerization activity was 315 g/mmol-Ti·hr. The molecular weight (Mw), as measured by GPC, was 1,460,000 (in terms of polystyrene), and the molecular weight distribution (Mw/Mn) was 2.06.

#### Example 165

- 15        To a 500 ml reactor thoroughly purged with nitrogen, 250 ml of toluene was introduced, and the liquid phase and the gas phase were saturated with ethylene at 25 °C. Thereafter, while passing 80 l/hr of butadiene, 1.0 mmol of triisobutylaluminum was added, and successively 0.01 mmol of the titanium compound A-1 and 0.02 mmol of triphenylcarbeniumtetrakis(pentafluorophenyl)borate were added to initiate polymerization. The reaction was conducted at 25 °C for 20 minutes, and then a small amount of isobutanol was added to terminate the
- 25

polymerization. After the polymerization was completed, the reaction product was introduced into a large amount of methanol to precipitate a polymer in the whole amount. Then, hydrochloric acid was added, and  
5 filtration was effected using a glass filter. The resulting polymer was vacuum dried at 80 °C for 10 hours, to obtain 1.481 g of polybutadiene.

The polymerization activity was 444 g/mmol-Ti·hr, and the molecular weight (Mw) of the copolymer was  
10 1,760,000 (in terms of polystyrene).